



AREST ADVANCE PU BASED WATER PROOF & HEAT REFLECTING ROOF COAT



Product Description

Arest Advance Pu Based Water Proof & heat reflecting Roof Coat is a synthetic fiber reinforced non toxic single pack Polyurethane Based Elastomeric Acrylic Emulsion gives a water proofing membrane. On curing it form a thick & elastomeric membrane which gives an ultimate water proofing. Its a aliphatic Polyurethane & Acrylic hybrid formation.

Strong Benefits

- **Adhesion:**
Very strong adhesion with masonry surfaces.
- **Water Proofing:**
Waterproofing protection of up to 6-7 bars of positive hydrostatic pressure.
- **Crack Bridging ability:**
Excellent crack bridging ability for elastomeric film properties.
- **High Solar Reflectance:**
Sparkling white color & thick film thickness gives high levels of heat reflectance.
- **Room Temperature Reduction:**
It is white in color so reflect heat & light highly effectively. It gives temperature reduction between inside & outside up to 10° centigrade.
- **Mechanical Strength of the film:**
As the product reinforced with synthetic fiber so provides high mechanical strength.
- **Anti Carbonation:**
Damp proof system provides excellent carbon dioxide diffusion resistance & strongly prevents corrosion of rebar within the concrete matrix & gives better structural protection.
- **Use:**
Product is in liquid form & single pack ready to apply.

Performance Characteristics as per ASTM Standard

Value for Arest Waterproof Roof Coat

Pull off Adhesion Strength
(ASTM 454) Dry Concrete

Minimum 1.5 MPa (S/F) MPa

Tensile Strength
(ASTM D 2370/98: 14 days)

1.5+/- 0.15 MPa
1.8+/- 0.15 MPa

% Elongation
(ASTM D2370/98: 14 Days)

350+/- 10% (Horizontal)
220+/- 10% (Vertical)

Crack Bridging
(ASNZ 4548, 14 Days)

3.6+/- 0.125 mm for(Horizontal)
1.27 +/- mm for (Vertical)

Water Vapour permeability
(EN ISO 7783)

4.12 g/m2/day

% Solid (ASTM C 1250)

55 to 61% @ 120DC 1 hr.

Over Coating Interval

Overnight.

Specific Gravity

1.22 to 1.32 at 30DC

Temperature Reduction
(In house method)

10 DC

DISCLAIMER:

Information provided herein is based upon tests believed to be reliable. It does not guarantee the results to be obtained. Nor does it make any express and implied warranty of merchantability or fitness for a particular purpose concerning the effects or result of such cases. It does not release you from the obligation to test the products supplied by us as to their suitability for the intended uses. The application, surface preparation, and use of the products are beyond our control and, therefore, entirely your responsibility.

AREST ADVANCE PU BASED WATER PROOF & HEAT REFLECTING ROOF COAT



Application

Surface Preparation:

- **Cleaning:** Free the surface from loose particles and peeling paint. Remove any previous growth of algae, fungi or moss by thorough wire brushing and cleaning with water. Antifungal wash after cleaning the algae & fungi has been proved very effective.
- **Filling:** Any surface imperfections like holes, dents and fine cracks are to be filled with Cement Putty or Acrylic Putty.
- **Primer:** Ensure that fresh plastered surfaces are completely cured and dry. Apply a coat of Arest Flexible Base Coat Primer WT thinning with clean water. Allow drying for 4-6 hours.

Topcoat:

Apply 2 coats of Arest Water Proofing Top Coat Exterior Emulsion with clean water. Maintain an interval of one day between successive coats. For First two of top Coat dilute with 30% clean Water and for last coat apply paint without water addition. Every coat will apply at 90° angle to previous coat

For darker shades additional coat is recommended for complete hiding.

Special notes:

Over Flexible Base Coat apply First Coat of Water Proofing Roof Coat at 90° direction to Base Coat application allow for proper dry for overnight. Apply Second Coat of Water Proofing Roof Coat next day at a direction of 90° to first coat & allow to dry overnight for next coat. Apply third coat of Water Proofing Roof Coat without any dilution at a direction of 90° to previous coat and allow to dry overnight. Do not use the roof for another three days.

	Brush	Roller	Spray
Application	✓	✓	✓
Dilution	15-20% by volume with clean potable water Final topcoat should be without dilution	10-15% by volume with clean potable water	30-35% by volume with clean potable water
One coat Arest Universel Basecoat with 30% dilution covers 50 sq ft/liter*			
Drying time	Within 1 hr	Topcoat Coverage (Theoretical)	24-25* sq ft/litre for two coats finish under ideal conditions
Overcoating Time	4 – 6 hrs		
No. of coats specified	2 Coats	Stability of Thinned Paint	Use within 24 hrs.
Precautions while Painting	● Avoid painting when the temperature is below 10°C. ● Painting is not recommended if the moisture content and alkalinity of the surface is high. ● For newly plastered walls painting is recommended after 12 weeks of curing. ● Please do not over-thin or over-extend the brush while painting.		
Cleaning up equipments	Wash all tools with water immediately after application.		
Post Application Instructions	For best performance of paint, surfaces should be washed and cleaned at regular intervals of six months.		

VOC Level: VOC content does not exceed 30 ppm & complies with applicable low-VOC requirements.