Chemical resistance

Flexible spill containment berm EFB Standard, Plus version (EVA fabric)

Resistance of the fabric during **two years of contact** with the liquid.

A good B poor C not compatible ( ) = approximate value

LIQUID	RESISTANCE
Water/Salt Solutions	
Water	A
2% Potassium Chloride brine solution	A
10% Potassium Chloride brine solution	A
Seawater	A
10% Sodium Chloride brine solution	A
25% Sodium Chloride brine solution	A
38% Calcium Chloride brine solution	A
Organic Acids/Anhydrides	
50% Citric Acid solution	A
10% Acetic Acid solution	(B)
Glacial Acetic Acid	(C)
Acetic Anhydride	(C)
60/40 Acetic Acid/Acetic Anhydride	(C)
Acrylic Acid	(C)
Mineral Acids	
32% Hydrochloric Acid	C
20% Hydrochloric Acid	(C)
15% Hydrochloric Acid	B
Hydrochloric Acid/Acetic Acid blends	(C)
Alkalis	
50% Sodium Hydroxide solution	A
50% Potassium Hydroxide solution	A
50% Ammonium Hydroxide solution	A
50% Potassium Carbonate solution	A
KOH and Potassium Carbonate blends	A
Oxidizers	
Hydrogen peroxide	A
Sodium hypochlorite	A
Calcium hypochlorite	(A)

LIQUID	RESISTANCE
Alcohols/Other Organics	
100% Methanol	A
100% Ethanol	A
100% Isopropanol	A
100% Butanol	A
Alcohol blends	A
Ethoxylated C12+ alcohols	(A)
Acetylenic alcohols (e.g. propargyl alcohol)	(A)
100% Triethanolamine	(B)
100% Diethanolamine	(B)
100% Monoethanolamine	(B)
70% Tetramethyl ammonium chloride (quat)	(A)
50% Tetramethyl ammonium chloride (quat)	(A)
100% Glycerin	A
100% Ethylene glycol	A
100% Diethylene glycol	A
100% Ethylene glycol monobutyl ether	(B)
Fuels & Oils	
Gasoline (petrol)	B
Kerosene	A
Diesel	A
Xylene	(C)
Toluene	C
Heavy Aromatic Naphtha (HAN)	(A)
Mineral oil	A
Motor oil	A
Hydrogenated mineral oil, flash point > 80 °C	(A)
Palm oil	(A)
d-Limonene	(A)
Oxygen Scavengers	
Sodium thiosulfate	(A)

Data from the manufacturer. Is your liquid not listed, or are you unsure? Send us the safety data sheet and we will check it for you.