




SUBMITTED BY :
ADDRESS :
CITY :
COUNTRY :
PHONE # :
SAMPLE DESCRIPTION :
COLOR :
SIZE :
ORDER NO. :
DESIGN :
FABRIC CONSTRUCTION :
END USE : -
SUPPLIER NO. : -
SUPPLIER REF. NO. : -
MANUFACTURER : -
COUNTRY OF ORIGIN : -
CUSTOMER : -
FABRIC WEIGHT : -
PREVIOUS REPORT # : -
SAMPLE RECEIVING DATE :
SAMPLE REPORTING DATE :

CARE LABEL INSTRUCTION : 

----- Above Information provided by Customer. Lab. findings on next page(s) -----

Signed for and on behalf of
S. R. Laboratories (Pvt.) Ltd.

Zulfiqar Ali
Lab. Manager

SR.	TEST SUMMARY	Results
1	Dimensional Changes of Garments After	P
2	Appearance of Apparel and Other Textile End	
3	Colorfastness to Washing	F
4	Colourfastness to Crocking	P

REMARKS : P = TEST RESULT MEET AS PER REQUIRMENT
F = TESTS RESULTS DOES NOT MEET AS PER REQUIRMENT
S = SEE THE RESULTS

Test Conducted :

1 Dimensional Changes of Garments After Home Laundering (Results) (Requirment) AATCC TM 150 - 2018t

Machine Wash 40 °C Normal Cycle, Water Level 18 ± 1 Gallon,
Washing Load 1.8 Kg, Tumble Dry Low,
AATCC1993 Standard Ref. Detergent

	Original cm	After 3rd Wash cm	After 3rd Wash %	
<u>After 3rd Wash</u>				
Length	267.5	254.2	-5.0%	± 7.5 %
Width	231.5	219.3	-5.3%	± 7.5 %

2 Appearance of Apparel and Other Textile End Products after Repeated Home Laundering AATCC TM 143 - 2018t AS PER AATCC TM 150 - 2018t

OBSERVATIONS AFTER 3rd WASH:

Fairly Smooth, Appearance.
No Tearing or Bursting Noticed.
No Damages of Stitch Yarn Noticed.
No Significant Pilling Noticed.
Slight Fuzzing Noticed.
Some Fray Yarn Seen Along Side Seam.

No Holes.
Unraveled Seams.
Excessive Pinning

Change in Shade	4	-
-----------------	----------	---

Staining on Multifibre.

Acetate	4 - 5	-
Cotton	4 - 5	-
Nylon	4 - 5	-
Polyester	4 - 5	-
Acrylic	4 - 5	-
Wool	4 - 5	-

Test Conducted :

	(Results)	(Requirement)
2 Colorfastness to Washing		
AATCC TM 150 - 2018t		
Color Change	3.0	4.0
Staining On		
Acetate	4.0	3.0
Cotton	4.5	3.0
Nylon	4.5	3.0
Polyester	4.5	3.0
Acrylic	4.5	3.0
Wool	4.5	3.0
3 Colourfastness to Crocking		
AATCC TM 8 - 2016e		
Dry	4.5	4.0
Wet	4.5	3.0

End of Report