

# 2013-XE-53 to 65

i

EE24BTECH11038 - MALAKALA BALA SUBRAHMANYA ARAVIND

53) Match the conventional ceramic materials listed in Column I with their respective common applications in Column II

Column I	Column II
P. Lead Zirconate Titanate (PZT)	1. cutting tool
Q. Zinc Oxide (ZnO)	2. thermal barrier coating
R. Silicon Carbide (SiC)	3. actuator
S. Zirconia ( $ZrO_2$ )	4. varistor
	5. super conductor

TABLE 53

- a) P-1, Q-2, R-3, S-5
- b) P-3, Q-2, R-1, S-5
- c) P-2, Q-1, R-5, S-3
- d) P-3, Q-4, R-1, S-2

54) Match the terminologies given in Column I with their relations listed in Column II

Column I	Column II
P. domain wall	1. superconductors
Q. Fick's law	2. mechanical properties
R. Matthiessen's rule	3. ferromagnetic materials
S. Hall-Petch relation	4. resistivity of impure metals
T. Meissner effect	5. diffusion

TABLE 54

- a) P-1, Q-3, R-5, S-2, T-4
- b) P-3, Q-5, R-2, S-4, T-1
- c) P-3, Q- 5, R-4, S-2, T-1
- d) P-3, Q-4, R-3, S-2, T-4

55) Match the microscopes listed in Column I with their principle of operation listed in Column II

- a) P-2, Q-5, R-3, S-1
- b) P-3, Q-4, R-5, S-2
- c) P-4, Q-3, R-2, S-1
- d) P-4, Q-3, R-5, S-2

Column I	Column II
P. Scanning Electron Microscope (SEM)	1. van der Waals forces between atoms
Q. Transmission Electron Microscope (TEM)	2. electrons to jump across a potential barrier
R. Scanning Tunnelling Microscope (STM)	3. diffraction of electrons
S. Atomic Force Microscope (AFM)	4. detection of secondary electrons
	5. photo emission of electrons

TABLE 55

- 56) X-rays of unknown wavelength are diffracted by an FCC metal with a lattice parameter of 0.352nm. The measured ' $2\theta$ ' angle for the 200 peak is  $61.08^\circ$ . Calculate the wavelength of the X-ray used, in nm
- 57) A metal with HCP crystal structure has lattice constants  $a = 0.30$  nm and  $c = 0.56$  nm. Determine the volume of the unit cell of this metal, in  $\text{nm}^3$ .
- 58) The band gap of a semiconducting material used to make an LED is 1.43 eV. What will be the minimum wavelength of the radiation emitted by this LED, in  $\mu\text{m}$ ?
- 59) For automatic control of household electric water heater a relay switch is activated by thermal expansion of a brass rod of length 50 cm as shown in the schematic below. The distance between the rod and the lever,  $x$ , is adjusted by moving the base of the rod. As the water gets heated the rod expands and as soon as the rod touches the lever, the circuit is broken disconnecting the heater from the power supply. Find the distance,  $x$ , in mm, to be set at water temperature of  $20^\circ\text{C}$  such that the circuit is broke at  $70^\circ\text{C}$ . The coefficient of linear thermal expansion of brass is  $20 \times 10^{-6} \text{ }^\circ\text{C}^{-1}$

230V




Fig. 59.1

### Common Data Questions

Common Data for Questions 60 and 61:




Fig. 59.2

From tensile test of a particular alloy the following values were obtained. The material exhibits linear work hardening as shown in the figure given below.

- 60) If the cylindrical specimen had a dimension of diameter 10 mm and length 50 mm, find the length of the specimen at the yield point, in mm
- 61) Find the toughness of the material, in  $\text{M J m}^{-3}$

	At Yield	At Fracture
<b>Stress, GPa</b>	0.7	0.8
<b>Strain, %</b>	1	4

TABLE 59

Common Data for Questions 62 and 63:

An isomorphous alloy system contains 47 wt% of A and 53 wt % of B and is at 1300° C. Referring to the figure given below, answer the following:

62) What is the weight percentage of A in solid phase at this temperature?




Fig. 62.1

63) What weight percentage of this alloy is liquid? Statement for Linked Answer

Questions 64 and 65:

A stress of 10 MPa is applied to an elastomer to generate a strain of 50%. The

strain is held constant at this value. After 40 days at 20°C, the stress decreases to 5<sup>v</sup> MPa

64) What is the relaxation time constant for this material?

65) What will be the stress after 60 days at 20°C?