Construction Chemicals

Product Datasheet
Edition: 01 | Date: Nov 2026
Jointing and Tiling

Mixseal PU

One-Component Polyurethane
Joint Sealant & Elastic Adhesive



Product Description

Mixseal PU is a one-component, moisture-curing polyurethane sealant and elastic adhesive. It seals vertical and horizontal joints, including joints under water, resists chemicals and jet fuel, and in most cases adheres without a primer. It also bonds glass, ceramics, aluminium and concrete elastically.

Uses

- Expansion and connection joints in buildings, floors and façades.
- Joints in water tanks, channels and wet areas.
- Joints in airport aprons and fuel areas.
- Joints around windows, doors and precast panels.
- Elastic bonding of glass, ceramics, aluminium and concrete.

Advantages

- High elongation: 700 %.
- Strong adhesion, usually without primer.
- Resistant to chemicals and jet fuel.
- Suitable for joints under water.
- Non-sag: vertical and horizontal joints.

Application

1. **Joint Preparation**
   Clean, dry, sound joint faces; insert Back-fill backer rod to the correct depth; mask edges.
2. **Gun Application**
   Cut the sausage, load the gun and extrude the sealant into the joint in full contact with both faces.
3. **Tooling**
   Tool the surface within the skinning time using soapy water; remove the masking tape.

Consumption

6 m per 600 ml sausage
for a 10 × 10 mm joint
Consumption (m) = 600 / (width × depth in mm).

Packaging

600 ml sausages.

Storage & Shelf Life

12 months in original, unopened packaging. Store dry at +5 °C to +25 °C, away from direct sunlight.

Technical Data

Typical values at 25 °C

Property	Typical Value	Test Method
Type	One-component, moisture-curing polyurethane	—
Colours	Black, white, grey	—
Density	1.15 g/cm³	—
Hardness	Shore A 40	—
Modulus at 100 %	approx. 0.3 MPa	—
Elongation at break	700 %	—
Adhesion	> 2.0 N/mm² (20 kg/cm²)	—
Tack-free time	2.5 – 3.5 hours	—
Curing rate	2 – 3 mm / day	—
Joint width	4 – 30 mm	—
Width : depth ratio	1 : 1 to 2 : 1	—
Min. application temperature	+5 °C	—

Consumption

Joint size (W × D)	Length per 600 ml sausage
6 × 6 mm	approx. 16 m
10 × 10 mm	approx. 6 m
15 × 10 mm	approx. 4 m
20 × 10 mm	approx. 3 m
30 × 15 mm	approx. 1.3 m

Consumption is theoretical and varies with substrate porosity, profile and application method.

Application Conditions

- Do not apply below +5 °C.
- Joint faces clean, dry, sound and free of oil, dust and laitance.
- Joint width 4 – 30 mm; width : depth ratio 1 : 1 to 2 : 1.
- Use Back-fill backer rod to control depth and prevent three-sided adhesion.
- Concrete at least 28 days old.

Application Notes

- Prime porous or critical substrates where adhesion tests show it is needed.
- Mask joint edges for a neat finish.
- Tool with soapy water within the skinning time.
- Allow full cure before exposing to water or traffic; cure rate 2 – 3 mm per day.
- Do not use as a structural glazing sealant.

Health & Safety

- Wear gloves and safety glasses.
- Uncured material contains isocyanates and may cause sensitisation; avoid skin and eye contact.
- Ensure good ventilation in enclosed areas.

First Aid & Cleaning

- Eyes: rinse immediately with plenty of clean water for at least 15 minutes and seek medical advice.
- Skin: remove uncured sealant with a cloth, then wash with soap and water.
- Inhalation: move to fresh air.
- Clean tools with a suitable solvent before the sealant cures; cured material can only be removed mechanically.

The information in this datasheet is based on laboratory tests and practical experience and is given in good faith. Users should verify product suitability for their specific application. O MIX reserves the right to update this information without prior notice.