METHOD STATEMENT

O-Flex PVC — Three-Component Joint Sealing System Flexible Tape + Solvent-Free Epoxy Adhesive

Project Name		**Document No.**	OMX-MS-OFLEXPVC
Main Contractor		**Revision**	01
Consultant		**Date of Issue**	Nov 2026
Product	O-Flex PVC	**Status**	For Approval

1. Purpose

This method statement defines the procedure, sequence, resources, quality checks and safety measures for the supply and application of O-Flex PVC on site. It ensures that the work is carried out safely, in line with the approved drawings and project specification, and achieves the performance stated in the O MIX Technical Data Sheet.

2. Scope of Work

This method statement covers surface preparation, mixing of the epoxy adhesive and installation of the O-Flex PVC joint sealing tape system over construction and expansion joints, cracks and pipe penetrations in concrete structures.

- Inspection and acceptance of the substrate and the work area.
- Surface preparation and repair of defects.
- Priming of the prepared surface.
- Mixing and application of the material as described in this document.
- Curing, protection and handover of the completed area.
- Quality control, inspection and documentation of each stage.

3. Definitions

Term	Meaning
Pot life	Time the mixed material remains workable after Part A and Part B are combined.
Recoat interval	Minimum and maximum time between coats to achieve inter-coat adhesion.
WFT / DFT	Wet film thickness measured during application / dry film thickness after cure.
Dew point	Temperature at which moisture condenses; the substrate must be at least 3 °C above it.
Kit / set	Pre-weighed Part A and Part B supplied to be mixed completely.

4. Roles & Responsibilities

Role	Responsibility
Project Manager	Overall responsibility for planning, resources, approvals and coordination with the consultant and main contractor.

Role	Responsibility
Site Engineer	Supervises the work daily; confirms substrate readiness, climate conditions, mixing, consumption and sequence; keeps daily records.
QA/QC Inspector	Carries out inspections and tests at each stage, records results, raises inspection requests at hold points and signs the checklist.
HSE Officer	Conducts toolbox talks, checks PPE, ventilation, access and safe storage; stops work if unsafe conditions arise.
Foreman / Applicators	Carry out the work as per this method statement and report any deviation immediately.
Storekeeper	Receives, stores and issues materials in original packaging under the stated storage conditions; controls batch numbers.

5. Materials

Material	Description
O-Flex PVC — Part A	FPO / PVC sealing tape, 20 / 25 / 30 cm wide, 20 m rolls
O-Flex PVC — Parts B + C	Solvent-free epoxy adhesive: resin (Part B, pail) + hardener (Part C, jerrycan), 5 kg sets
Backing	Foam backing (Back-fill) or sealant in the joint for positive pressure; steel plate for negative pressure

5.1 Key product data

Property	Typical Value
Part A — tape material	Flexible FPO / PVC
Tape widths	20 / 25 / 30 cm
Tensile strength (tape)	115 N / 20 mm
Hardness (tape)	Shore A 70
Elongation at break (tape)	650 %
Water pressure resistance	> 1.5 bar
UV resistance	500 h
Service temperature	-30 °C to +90 °C

6. Tools & Equipment

- Grinder
- Industrial vacuum
- Slow-speed mixer
- Notched trowel
- Flat trowel
- Pressure roller
- Scissors

- Masking tape
- Thermo-hygrometer and surface thermometer (dew point check)
- Moisture meter
- Wet-film thickness gauge
- Measuring buckets and scale
- Masking tape and protective sheeting
- Lighting and extension cables

6.1 Personal protective equipment

- Gloves
- Goggles
- Overalls
- Safety shoes

7. Storage & Handling

- 12 months in original, unopened packaging. Store dry at +5 °C to +35 °C; keep tape rolls flat and away from direct sunlight.
- Store on pallets, off the ground, in a dry, covered and ventilated area.
- Keep containers closed until use; use materials on a first-in, first-out basis.
- Keep Part B and Part C of each adhesive set together and do not mix parts from different batches.
- Store away from heat, sparks and ignition sources.
- Handle with care to avoid damage to packaging; do not stack beyond the safe height.

8. Pre-Start Requirements

- Material submittal, this method statement and the inspection plan approved by the consultant.
- Work area handed over clean, free of other trades and with safe access.
- Adequate lighting, power supply and ventilation available.
- Climate conditions checked and recorded before work starts.
- A trial area prepared and approved where required by the project.
- Toolbox talk held with the work team covering this method statement and the safety measures.

9. Surface Preparation

1. Inspect the joint and edges; the substrate must be sound and at least 28 days old.
2. Grind both edges over the bonding width to remove laitance, coatings and contaminants.
3. Repair broken edges with epoxy mortar.
4. Vacuum all dust; remove standing water (damp surface is acceptable).
5. Insert foam backing or sealant in the joint where positive water pressure is expected.
6. Mask the outer edges of the bonding area.

7. Measure substrate temperature, air temperature and relative humidity; confirm the substrate is at least 3 °C above dew point.
8. Protect adjacent surfaces, drains and fixtures with masking tape and sheeting.
9. Obtain QA/QC approval of the prepared surface before starting the next step.

10. Mixing

1. Condition materials to between +15 °C and +25 °C before mixing.
2. Check the batch numbers and expiry dates of all three parts and record them.
3. Stir Part B (epoxy resin), then add the complete Part C (hardener).
4. Mix 2 – 3 minutes with a slow-speed mixer until uniform.
5. Mix complete sets only.
6. Mix only the quantity that can be applied within the pot life.

11. Application

1. Apply the adhesive with a notched trowel to both sides of the joint, approx. 1 mm thick.
2. Place the tape centrally over the joint and press firmly into the adhesive with a roller, removing air pockets.
3. Leave the centre of the tape free over moving joints, forming a loop where large movement is expected.
4. Apply a 1 mm cover layer of adhesive over the tape edges.
5. Overlap tape ends by at least 5 cm and bond with adhesive.
6. Remove masking tape before the adhesive sets.
7. Work in manageable bays, keeping a wet edge to avoid lap marks.
8. Check consumption by area and wet film thickness regularly during application and record the results.

12. Curing & Protection

- Protect from water, traffic and damage until the adhesive has cured.
- For negative water pressure, fix the steel cover plate after cure.
- Protect the applied area from water, dust, other trades and traffic until the stated cure times are reached.
- Barricade the area and display warning signs.

13. Quality Control & Inspection

Check	Stage	Acceptance Criteria	By
Substrate	Before bonding	Sound, ground, dust-free, no standing water	QA/QC
Climate	During work	+10 °C to +30 °C, RH ≤ 85 %	Site Engineer
Adhesive	Each set	Complete set (B + C), uniform colour	Site Engineer
Tape bonding	After installation	Fully bonded edges, no air pockets, free centre	QA/QC
Overlaps	After installation	Min. 5 cm, bonded	QA/QC
Water test	After cure	No leakage	QA/QC + Consultant

13.1 Inspection and test plan

Activity	Inspection / Test	Frequency	Record
Material receipt	Product, batch, expiry, packaging condition	Each delivery	Material inspection report
Climate	Air / substrate temperature, RH, dew point	Start of shift and every 4 hours	Daily climate log
Surface preparation	Visual, moisture, soundness	Each area	Inspection request (hold point)
Application	Consumption, thickness, appearance	Each coat / area	Daily progress report
Final inspection	Visual, continuity, finish	Each completed area	Handover checklist

14. Defects & Remedies

Defect	Likely Cause	Remedy
Tape debonding at edges	Dusty substrate; adhesive too thin	Remove, re-prepare and re-bond
Air pockets under tape	Insufficient rolling	Cut, inject adhesive or re-bond the section
Tape tearing at joint	No free centre over moving joint	Replace with free centre / loop
Leaks at overlaps	Overlap too short	Rebond with min. 5 cm overlap

15. Health, Safety & Environment

Hazard	Control Measures
Skin and eye contact	Gloves, goggles, overalls; eye-wash available
Inhalation of vapours / dust	Ventilation; masks as required
Slips and trips	Housekeeping; barricades and signs
Manual handling	Correct lifting technique; mechanical aids
Electrical tools	Inspected tools; protected cables

- Wear chemical-resistant gloves, safety goggles and overalls.
- Uncured epoxy may cause skin sensitisation; avoid skin and eye contact.
- Ensure good ventilation in enclosed areas.
- Eyes: rinse immediately with plenty of clean water for at least 15 minutes and seek medical advice.
- Skin: remove contaminated clothing and wash with soap and water; do not use solvents on skin.

15.1 Waste & environment

- Collect empty containers and residues in designated bins.
- Do not discharge material or washings into drains or soil.
- Allow small quantities of leftover mixed material to cure before disposal; dispose of according to local regulations.

16. Cleaning

- Clean tools with epoxy thinner before the adhesive cures.

17. Limitations

- Ambient and substrate temperature: +10 °C to +30 °C.
- Relative humidity: max. 85 %.
- Do not apply in rain or when rain is expected before the material has set.
- Any deviation from this method statement must be approved by the Site Engineer and the consultant.

Appendix A — Inspection Checklist

Inspection Item	Result	Remarks
Joint edges ground and clean	☐ Yes ☐ No	
Backing installed where required	☐ Yes ☐ No	
Edges masked	☐ Yes ☐ No	
Adhesive mixed in complete sets	☐ Yes ☐ No	
Adhesive applied both sides	☐ Yes ☐ No	
Tape pressed and rolled	☐ Yes ☐ No	
Centre left free	☐ Yes ☐ No	
Cover layer applied	☐ Yes ☐ No	
Overlaps min. 5 cm	☐ Yes ☐ No	
Water test passed	☐ Yes ☐ No	

Inspected by	Signature	Date