Construction Chemicals

Product Datasheet
Edition: 01 | Date: Nov 2026
Jointing and Tiling

O-Flex PVC

Three-Component Joint Sealing System
Flexible Tape + Solvent-Free Epoxy Adhesive



Product Description

O-Flex PVC is a three-component joint and crack sealing system: a flexible FPO/PVC sealing tape (Part A) bonded with a solvent-free epoxy adhesive supplied as epoxy resin (Part B) and hardener (Part C). It seals construction and expansion joints, cracks and pipe penetrations against water, bonds to damp surfaces and accommodates high movement.

Uses

- Construction and expansion joints.
- Static and moving cracks.
- Pipe penetrations.
- Basements, tunnels and swimming pools.
- Irrigation channels and wastewater treatment plants.
- Reinforcement of joints in Roofguard waterproofing systems.

Advantages

- High elongation: 650 %.
- Watertight above 1.5 bar.
- Bonds to damp substrates.
- Resists dilute acids, alkalis and sea water.
- UV resistance 500 h; service -30 °C to +90 °C.

Application

1. **Surface Preparation**
   Clean, sound joint edges; grind to remove laitance and contaminants; vacuum dust.
2. **Bonding**
   Mix the epoxy adhesive and apply with a notched trowel on both sides of the joint; press the tape in with a roller.
3. **Cover Layer**
   Apply a 1 mm layer of epoxy adhesive over the tape edges, leaving the centre free for movement.

Consumption

1.2 – 2.0 kg per linear metre
epoxy adhesive, depending on tape width
Tape: 1 m per 1 m of joint, widths 20 / 25 / 30 cm.

Packaging

Part A: tape rolls of 20 m (widths 20, 25 and 30 cm). Part B (epoxy resin, pail) + Part C (hardener, jerrycan): 5 kg adhesive sets.

Storage & Shelf Life

12 months in original, unopened packaging. Store dry at +5 °C to +35 °C; keep tape rolls flat and away from direct sunlight.

Technical Data

Typical values at 25 °C

Property	Typical Value	Test Method
Part A — tape material	Flexible FPO / PVC	—
Tape widths	20 / 25 / 30 cm	—
Tensile strength (tape)	115 N / 20 mm	—
Hardness (tape)	Shore A 70	—
Elongation at break (tape)	650 %	—
Water pressure resistance	> 1.5 bar	—
UV resistance	500 h	—
Service temperature	-30 °C to +90 °C	—
Adhesive	Solvent-free epoxy: Part B resin + Part C hardener	—
Adhesive mixing ratio (B : C)	As recommended — pre-weighed sets	—

Consumption

Tape width	Adhesive consumption
20 cm	approx. 1.2 kg/m
25 cm	approx. 1.6 kg/m
30 cm	approx. 2.0 kg/m

Consumption is theoretical and varies with substrate porosity, profile and application method.

Application Conditions

- Ambient and substrate temperature: +10 °C to +30 °C.
- Relative humidity: max. 85 %.
- Substrate sound, clean; may be damp but without standing water.
- Positive water pressure: support the tape in the joint with foam backing or sealant.
- Negative water pressure: cover the tape with a fixed steel plate.

Application Notes

- Mix complete adhesive sets (Part B + Part C) with a slow-speed mixer.
- Apply the adhesive with a notched trowel to both joint edges, at least 5 cm wider than the bonded tape edge.
- Press the tape into the fresh adhesive with a roller, removing air pockets.
- Leave the centre of the tape free of adhesive over moving joints (loop).
- Overlap tape joints by min. 5 cm and bond with adhesive, or weld where specified.

Health & Safety

- Wear chemical-resistant gloves, safety goggles and overalls.
- Uncured epoxy may cause skin sensitisation; avoid skin and eye contact.
- Ensure good ventilation in enclosed areas.

First Aid & Cleaning

- Eyes: rinse immediately with plenty of clean water for at least 15 minutes and seek medical advice.
- Skin: remove contaminated clothing and wash with soap and water; do not use solvents on skin.
- Inhalation: move to fresh air; seek medical advice if symptoms persist.
- Ingestion: do not induce vomiting; seek medical advice immediately.
- Clean tools with epoxy thinner before the adhesive cures.

The information in this datasheet is based on laboratory tests and practical experience and is given in good faith. Users should verify product suitability for their specific application. O MIX reserves the right to update this information without prior notice.