Construction Chemicals

Product Datasheet
Edition: 01 | Date: Nov 2026
Decorative Flooring

TerraFloor C

Cement-Based Terrazzo
Decorative Floor System



Product Description

TerraFloor C is a three-component, cement-based terrazzo flooring system consisting of a two-part binder (Part A and Part B) and engineered decorative aggregates (Part C). It produces a durable, seamless decorative floor that resists abrasion, impact, slipping and moisture, is UV stable, environmentally friendly and available in custom colours and textures.

Uses

- Factories and warehouses.
- Shops, offices and showrooms.
- Airports, malls and hospitals.
- Kitchens, basements and car parks.
- Decorative interior floors requiring a seamless finish.

Advantages

- Resistant to abrasion, impact and moisture.
- UV stable: colours do not fade.
- Custom colours, aggregates and textures.
- Slip resistant and easy to maintain.
- Fast installation: foot traffic after 24 hours.

Application

1. **Surface Preparation**
   Concrete ≥ 25 N/mm², moisture < 5 %; diamond grind or shot blast and remove oil; apply primer.
2. **Mixing**
   Mix binder Part A and Part B, then add the Part C aggregates and mix to a uniform consistency.
3. **Application**
   Spread with trowel, squeegee or roller to 4 – 10 mm, finish and cure for 24 – 48 hours.

Consumption

approx. 2.2 – 2.5 kg/m² per mm
binder : aggregate ≈ 2 : 3 by weight
E.g. approx. 13 – 15 kg/m² at 6 mm.

Packaging

Binder Part A and Part B in 30 kg pails; aggregates (Part C) in 25 kg or 30 kg bags.

Storage & Shelf Life

12 months in original, unopened packaging. Store dry at +5 °C to +35 °C; protect binder from frost and aggregates from moisture.

Technical Data

Typical values at 25 °C

Property	Typical Value	Test Method
Components	Binder Part A + Part B + aggregates Part C	—
Mixing ratio	Pre-weighed units — mix complete units as recommended	—
Layer thickness	4 – 10 mm	—
Compressive strength	≥ 40 MPa	—
Flexural strength	≥ 7 MPa	—
Bond strength	≥ 1.5 MPa	—
Heat resistance	up to 80 °C	—
Foot traffic	24 hours	—
Full service	48 – 72 hours	—
Application temperature	+10 °C to +30 °C	—
Relative humidity	max. 75 %	—

Consumption

Thickness	Total (A + B + C)	Binder (A + B) / Aggregate (C)
4 mm	approx. 9 – 10 kg/m²	3.6 – 4 / 5.4 – 6 kg/m²
6 mm	approx. 13 – 15 kg/m²	5.2 – 6 / 7.8 – 9 kg/m²
10 mm	approx. 22 – 25 kg/m²	8.8 – 10 / 13.2 – 15 kg/m²

Consumption is theoretical and varies with substrate porosity, profile and application method.

Application Conditions

- Surface and ambient temperature: +10 °C to +30 °C.
- Relative humidity: max. 75 %.
- Substrate moisture: < 5 %.
- Concrete compressive strength: ≥ 25 N/mm².
- Protect from direct sun, wind and rain during application and early curing.

Application Notes

- Prime the prepared substrate before applying the terrazzo layer.
- Mix complete units only to keep colour and aggregate ratio consistent.
- Use one batch of aggregates per area to avoid colour variation.
- Form joints in line with substrate joints.
- Cure for 24 – 48 hours before light traffic; full service after 48 – 72 hours.

Health & Safety

- Wear gloves, safety goggles and a dust mask when handling powders and aggregates.
- The binder contains cement and is alkaline when wet; avoid skin and eye contact.
- Use dust extraction during grinding.

First Aid & Cleaning

- Eyes: rinse immediately with plenty of clean water for at least 15 minutes and seek medical advice.
- Skin: wash with soap and water; cement is alkaline when wet.
- Inhalation of dust: move to fresh air.
- Ingestion: rinse mouth and seek medical advice.
- Clean tools and mixers with water immediately after use.