Construction Chemicals

Product Datasheet
Edition: 01 | Date: Nov 2026
Decorative Flooring

TerraFloor EP

Epoxy Terrazzo
Seamless Decorative Floor System



Product Description

TerraFloor EP is a solvent-free epoxy terrazzo floor system made of a pigmented epoxy binder (Part A + Part B) and a filler of decorative aggregates such as marble, stone or glass with marble powder (Part C). It is placed at 6 – 10 mm, then ground and polished to a seamless, decorative finish with excellent chemical and impact resistance.

Uses

- Restaurants and cafes.
- Car showrooms, hotels and malls.
- Hospitals and pharmaceutical plants.
- Airports and stations.
- Government and public buildings.
- Factories requiring decorative, hygienic floors.

Advantages

- Seamless, highly decorative finish.
- Excellent chemical resistance.
- High impact and abrasion resistance.
- Solvent-free, 100 % solids.
- Heat resistance up to 80 °C.

Application

1. **Primer**
   Apply O MIX epoxy primer at 0.2 – 0.3 kg/m² on the prepared substrate.
2. **Screed**
   Mix Parts A + B, add Part C in a pan mixer for 2 minutes; lay a 10 mm screed and power float.
3. **Grind & Polish**
   After 48 hours grind 1 – 2 mm (50 grit), grout, polish with 100 and 200 grit and apply the sealer.

Consumption

approx. 25 kg/m²
body layer at 10 mm (A + B + C)
Primer 0.2 – 0.3 kg/m²; grout layer 0.1 – 0.3 kg/m².

Packaging

Binder Part A and Part B in pails; filler Part C in 30 kg bags.

Storage & Shelf Life

12 months in original, unopened packaging. Store dry at +5 °C to +35 °C, away from direct sunlight.

Technical Data

Typical values at 25 °C

Property	Typical Value	Test Method
Components	Epoxy Part A + Part B + filler Part C	—
Mixing ratio	Pre-weighed units — mix complete units as recommended	—
Density (A + B + C)	approx. 2.5 kg/L	—
Solids content	100 %	—
Pot life	1 hour	—
Compressive strength	65 N/mm²	—
Flexural strength	25 N/mm²	—
Tensile strength	313 kg/cm²	—
Hardness	Shore D approx. 80	—
Abrasion	0.07 g	—
Impact resistance	1.75 kg·m	—
Water absorption	approx. 0.05 %	—
Initial cure / full cure	24 hours / 7 days	—
Heat resistance	up to 80 °C	—

Consumption

Layer	Consumption
Primer	0.2 – 0.3 kg/m²
Terrazzo body (10 mm)	approx. 25 kg/m²
Grout layer	0.1 – 0.3 kg/m²
Sealing coat	As specified

Consumption is theoretical and varies with substrate porosity, profile and application method.

Application Conditions

- Ambient and substrate temperature: +5 °C to +35 °C.
- Substrate moisture: < 4 %.
- Substrate at least 3 °C above dew point.
- Concrete sound, at least 28 days old.
- Relative humidity: max. 85 %.

Application Notes

- Mix Part A + Part B first, then add Part C in a pan (forced-action) mixer for 2 minutes.
- Lay the screed at 10 mm and compact with a power float.
- Cure 48 hours before grinding.
- Grind 1 – 2 mm with 50 grit, fill pores with grout, then polish with 100 and 200 grit.
- Apply the sealing coat after polishing.

Health & Safety

- Wear chemical-resistant gloves, safety goggles and overalls.
- Uncured epoxy may cause skin sensitisation; avoid skin and eye contact.
- Use dust extraction and masks during grinding.
- Ensure good ventilation in enclosed areas.

First Aid & Cleaning

- Eyes: rinse immediately with plenty of clean water for at least 15 minutes and seek medical advice.
- Skin: remove contaminated clothing and wash with soap and water; do not use solvents on skin.
- Inhalation: move to fresh air; seek medical advice if symptoms persist.
- Ingestion: do not induce vomiting; seek medical advice immediately.
- Clean tools and mixers with epoxy thinner before the material cures.

The information in this datasheet is based on laboratory tests and practical experience and is given in good faith. Users should verify product suitability for their specific application. O MIX reserves the right to update this information without prior notice.