Construction Chemicals

Product Datasheet
Edition: 01 | Date: Nov 2026
Concrete Admixture



Addmix WR

Powder Plasticiser
Water-Reducing Admixture

Product Description

Addmix WR is a powder plasticising and water-reducing admixture for concrete, dry-mix mortars and grouts, and for cement, gypsum and aluminate binders. It improves workability at lower water content, giving higher strength and lower permeability. Conforms to EN 934-2.

Uses

- Ready-mix and site concrete.
- Dry-mix mortars.
- Grouts and self-levelling compounds.
- Cement, gypsum and aluminate binder systems.

Advantages

- Reduces mixing water.
- Improves workability.
- Increases strength.
- Low chloride: < 0.05 %.
- Conforms to EN 934-2.

Application

1. **Mix Design**
   Set the dosage at 0.2 – 2.0 % of binder weight in the approved mix design.
2. **Dosing**
   Add with the dry materials or pre-blend in dry mixes.
3. **Mixing**
   Mix to a uniform consistency; adjust water to the required workability.

Consumption

0.2 – 2.0 %
of binder weight
Optimum dosage by trial mixes.

Packaging

25 kg bags; 30 bags per pallet.

Storage & Shelf Life

24 months in original, unopened bags. Store dry.

Technical Data

Typical values at 25 °C

Property	Typical Value	Test Method
Appearance	Off-white powder	—
pH	8.5 ± 1	—
Dry content	93.5 %	—
Chloride content	< 0.05 %	—
Alkali content	< 13 %	—
Standard	EN 934-2	—
Shelf life	24 months	—

Consumption

Use	Dosage (% of binder)
Concrete	0.2 – 2.0 %
Dry-mix mortars and grouts	0.2 – 2.0 %

Consumption is theoretical and varies with substrate porosity, profile and application method.

Application Conditions

- Use the approved dosage only.
- Store and use dry.

Application Notes

- Confirm dosage by trial mixes.
- Over-dosing may cause bleeding or retardation.
- Store dry.

Health & Safety

- Wear gloves, safety goggles and a dust mask when mixing.
- Contains cement; alkaline when wet. Avoid skin and eye contact.
- Avoid inhaling dust.

First Aid & Cleaning

- Eyes: rinse immediately with plenty of clean water for at least 15 minutes and seek medical advice.
- Skin: wash with soap and water; cement is alkaline when wet.
- Inhalation of dust: move to fresh air.
- Ingestion: rinse mouth and seek medical advice.
- Clean equipment with water.

The information in this datasheet is based on laboratory tests and practical experience and is given in good faith. Users should verify product suitability for their specific application. O MIX reserves the right to update this information without prior notice.