Construction Chemicals

Product Datasheet
Edition: 01 | Date: Nov 2026
Concrete Admixture

Bondmix EP

Solvent-Free Epoxy
Bonding Agent — Old to New Concrete



Product Description

Bondmix EP is a two-component, solvent-free epoxy bonding agent for bonding fresh concrete or mortar to hardened concrete. It is applied by brush, roller or spatula and the new concrete is placed while the bonding agent is still tacky.

Uses

- Bonding fresh to hardened concrete.
- Structural repairs and patching.
- Industrial floor toppings.
- Construction joints in concrete.

Advantages

- Bond strength ≥ 2.0 MPa.
- Tensile strength ≥ 15 MPa.
- Solvent-free.
- Pot life 30 – 45 min.
- Brush, roller or spatula application.

Application

1. **Surface Preparation**
   Remove laitance and weak concrete; clean, dry or matt-damp surface.
2. **Mixing**
   Add Part B to Part A (2 : 1 by weight) and mix 2 – 3 min.
3. **Application**
   Apply 0.30 – 0.60 kg/m² and place fresh concrete while still tacky.

Consumption

0.30 – 0.60 kg/m²
depending on roughness
Rougher surfaces need the higher rate.

Packaging

5 kg sets (3.33 kg A + 1.67 kg B) and 20 kg sets (13.33 kg A + 6.67 kg B).

Storage & Shelf Life

12 months in original, unopened packaging. Store dry at +5 °C to +35 °C, away from direct sunlight.

Technical Data

Typical values at 25 °C

Property	Typical Value	Test Method
Mixing ratio (A : B)	2 : 1 by weight	—
Density	1.40 – 1.50 kg/L	—
Pot life	30 – 45 min	—
Tensile strength	≥ 15 MPa	—
Bond strength	≥ 2.0 MPa	—
Application temperature	+10 °C to +35 °C	—

Consumption

Surface	Consumption
Smooth	0.30 – 0.40 kg/m²
Rough	0.40 – 0.60 kg/m²

Consumption is theoretical and varies with substrate porosity, profile and application method.

Application Conditions

- Ambient and substrate temperature: +10 °C to +35 °C.
- Substrate clean, sound, dry or matt-damp.
- Fresh concrete must be placed while the bonding agent is tacky.

Application Notes

- Mix complete sets.
- Work the bonding agent well into the surface.
- Place fresh concrete within the open (tacky) time.
- If the coat has cured, roughen and reapply.

Health & Safety

- Wear chemical-resistant gloves, safety goggles and overalls.
- Uncured epoxy may cause skin sensitisation; avoid skin and eye contact.
- Ensure good ventilation in enclosed areas.

First Aid & Cleaning

- Eyes: rinse immediately with plenty of clean water for at least 15 minutes and seek medical advice.
- Skin: remove contaminated clothing and wash with soap and water; do not use solvents on skin.
- Inhalation: move to fresh air; seek medical advice if symptoms persist.
- Ingestion: do not induce vomiting; seek medical advice immediately.
- Clean tools with epoxy thinner before the material cures.

The information in this datasheet is based on laboratory tests and practical experience and is given in good faith. Users should verify product suitability for their specific application. O MIX reserves the right to update this information without prior notice.