Construction Chemicals

Product Datasheet
Edition: 01 | Date: Nov 2026
Concrete Admixture



Micromix Deco 1

Micro-Cement Base Coat
for Floors & Walls

Product Description

Micromix Deco 1 is a cementitious micro-cement base coat for floors, walls and stairs. Applied in thin layers of 1 – 2 mm over concrete, screed, ceramic or terrazzo, it forms a strong, seamless base for Micromix Deco 2 finishing layers.

Uses

- Floors, walls and stairs.
- Bathrooms and kitchens.
- Showrooms and commercial interiors.
- Renovation over concrete, screed, ceramic tiles or terrazzo.

Advantages

- Seamless base coat, 1 – 2 mm per layer.
- Compressive strength ≥ 35 MPa.
- Adhesion ≥ 1.5 MPa.
- Applies over existing tiles and terrazzo.
- Base of the Micromix Deco system.

Application

1. **Surface Preparation**
   Sound, clean, stable substrate; prime with Bondmix WB.
2. **Mixing**
   Mix powder with water at a water/powder ratio of 0.28 – 0.32.
3. **Application**
   Apply 1 – 2 mm per layer with a steel trowel; next layer after 24 hours.

Consumption

1.6 – 1.8 kg/m² per mm
in 1 – 2 layers
Approx. 1 kg/m² per layer in the Micromix Deco systems.

Packaging

25 kg bags.

Storage & Shelf Life

12 months in original, unopened bags. Store dry, off the ground, protected from moisture.

Technical Data

Typical values at 25 °C

Property	Typical Value	Test Method
Form	Cementitious powder	—
Water / powder ratio	0.28 – 0.32	—
Layer thickness	1 – 2 mm	—
Working time	20 – 30 minutes	—
Drying time	approx. 3 hours	—
Next layer	after 24 hours	—
Adhesion	≥ 1.5 MPa	—
Flexural strength	≥ 7 MPa	—
Compressive strength	≥ 35 MPa	—
Density	approx. 1.8 kg/L	—
Application temperature	+10 °C to +35 °C	—

Consumption

Layer	Consumption
Per mm of thickness	1.6 – 1.8 kg/m²
Base layer in Micromix Deco systems	approx. 1 kg/m²

Consumption is theoretical and varies with substrate porosity, profile and application method.

Application Conditions

- Ambient and substrate temperature: +10 °C to +35 °C.
- Substrate sound, clean, dry and stable.
- Protect from direct sun, wind and rapid drying.
- Do not apply on substrates with rising damp.

Application Notes

- Water / powder ratio 0.28 – 0.32 (7.0 – 8.0 L per 25 kg bag).
- Embed Fiberlock reinforcement in the first layer on floors where specified.
- Lightly sand between layers.
- Finish with Micromix Deco 2 and protect with Decora PU.

Health & Safety

- Wear gloves, safety goggles and a dust mask when mixing.
- Contains cement; alkaline when wet. Avoid skin and eye contact.
- Use dust extraction when sanding.

First Aid & Cleaning

- Eyes: rinse immediately with plenty of clean water for at least 15 minutes and seek medical advice.
- Skin: wash with soap and water; cement is alkaline when wet.
- Inhalation of dust: move to fresh air.
- Ingestion: rinse mouth and seek medical advice.
- Clean tools with water immediately after use.

The information in this datasheet is based on laboratory tests and practical experience and is given in good faith. Users should verify product suitability for their specific application. O MIX reserves the right to update this information without prior notice.