Construction Chemicals

Product Datasheet
Edition: 01 | Date: Nov 2026
Concrete Admixture



Micromix Deco 2

Micro-Cement Fine Finish
Decorative Top Layer

Product Description

Micromix Deco 2 is a very fine cementitious micro-cement finishing layer. Applied in layers of 0.5 – 1 mm over Micromix Deco 1, it gives a smooth, decorative, seamless finish that is protected with Decora PU.

Uses

- Decorative floors and walls.
- Bathrooms, kitchens and wet areas.
- Showrooms, offices and residential interiors.
- Columns, stairs and furniture.

Advantages

- Smooth, decorative seamless finish.
- Compressive strength ≥ 45 MPa.
- Flexural strength ≥ 8 MPa.
- Thin layers: 0.5 – 1 mm.
- Grey or white base for colouring.

Application

1. **Surface Preparation**
   Apply over cured, sanded Micromix Deco 1 base.
2. **Mixing**
   Mix powder with water at a water/powder ratio of 0.30 – 0.33.
3. **Application**
   Apply 0.5 – 1 mm per layer with a steel trowel; sand lightly between layers; seal with Decora PU.

Consumption

1.7 – 1.8 kg/m² per mm
in 2 thin layers
Approx. 1 kg/m² in the Micromix Deco systems.

Packaging

25 kg bags.

Storage & Shelf Life

12 months in original, unopened bags. Store dry, off the ground, protected from moisture.

Technical Data

Typical values at 25 °C

Property	Typical Value	Test Method
Form	Fine cementitious powder	—
Colour	Grey / white	—
Water / powder ratio	0.30 – 0.33	—
Layer thickness	0.5 – 1 mm	—
Working time	15 – 20 minutes	—
Drying time	approx. 2 hours	—
Next layer	after 24 hours	—
Flexural strength	≥ 8 MPa	—
Compressive strength	≥ 45 MPa	—
Density	approx. 1.7 kg/L	—

Consumption

Layer	Consumption
Per mm of thickness	1.7 – 1.8 kg/m²
Finish layers in Micromix Deco systems	approx. 1 kg/m²

Consumption is theoretical and varies with substrate porosity, profile and application method.

Application Conditions

- Ambient and substrate temperature: +10 °C to +35 °C.
- Substrate sound, clean, dry and stable.
- Protect from direct sun, wind and rapid drying.
- Do not apply on substrates with rising damp.

Application Notes

- Water / powder ratio 0.30 – 0.33 (7.5 – 8.3 L per 25 kg bag).
- Apply thin layers with a stainless-steel trowel.
- Sand lightly between layers (180 – 220 grit).
- Seal with Decora PU after drying.

Health & Safety

- Wear gloves, safety goggles and a dust mask when mixing.
- Contains cement; alkaline when wet. Avoid skin and eye contact.
- Use dust extraction when sanding.

First Aid & Cleaning

- Eyes: rinse immediately with plenty of clean water for at least 15 minutes and seek medical advice.
- Skin: wash with soap and water; cement is alkaline when wet.
- Inhalation of dust: move to fresh air.
- Ingestion: rinse mouth and seek medical advice.
- Clean tools with water immediately after use.

The information in this datasheet is based on laboratory tests and practical experience and is given in good faith. Users should verify product suitability for their specific application. O MIX reserves the right to update this information without prior notice.