Construction Chemicals

Product Datasheet
Edition: 01 | Date: Nov 2026
Accessories



Addmix PP

Polypropylene Micro Fibres
for Concrete & Mortar

Product Description

Addmix PP is 100 % virgin polypropylene micro-monofilament fibre for concrete, mortar and shotcrete. It reduces plastic shrinkage cracking, reduces spalling in fire and improves impact and freeze-thaw resistance.

Uses

- Roads, bridges and tunnels.
- Airports and water structures.
- Buildings and slabs.
- Wall panels, putties and shotcrete.

Advantages

- Reduces plastic shrinkage cracks.
- Reduces spalling in fire.
- Improves impact resistance.
- > 120 million fibres per kg.
- Easy dispersion.

Application

1. **Mix Design**
   Include 600 – 900 g/m³ in the mix design.
2. **Dosing**
   Add fibres with aggregates or to the truck mixer.
3. **Mixing**
   Mix at least 5 minutes for uniform dispersion.

Consumption

600 – 900 g/m³
of concrete

Packaging

25 kg bags.

Storage & Shelf Life

Store dry, away from heat.

Technical Data

Typical values at 25 °C

Property	Typical Value	Test Method
Material	100 % virgin polypropylene	—
Tensile strength	≥ 550 MPa	—
Fibres per kg	> 120 million	—
Melting point	160 – 170 °C	—
Density	0.91 g/cm³	—
Length	12 – 18 mm	—
Standards	EN 14889-2 Type 1a; ASTM C1116 Type III	—

Consumption

Use	Dosage
Slabs and floors	600 – 900 g/m³
Mortars and screeds	600 – 900 g/m³

Consumption is theoretical and varies with substrate porosity, profile and application method.

Application Conditions

- Use the approved dosage.
- Mix for at least 5 minutes after adding fibres.

Application Notes

- Add fibres early in mixing.
- Mix at least 5 minutes after addition.
- Cure as normal concrete.

Health & Safety

- Wear gloves, safety goggles and a dust mask when mixing.
- Contains cement; alkaline when wet. Avoid skin and eye contact.
- Avoid inhaling dust.

First Aid & Cleaning

- Eyes: rinse immediately with plenty of clean water for at least 15 minutes and seek medical advice.
- Skin: wash with soap and water; cement is alkaline when wet.
- Inhalation of dust: move to fresh air.
- Ingestion: rinse mouth and seek medical advice.
- Clean equipment with water.

The information in this datasheet is based on laboratory tests and practical experience and is given in good faith. Users should verify product suitability for their specific application. O MIX reserves the right to update this information without prior notice.