Construction Chemicals

SUBMITTAL DOCUMENT

Beadmix

Iron-Free Spherical Glass Beads
Blasting, Filler & Reflective



Finish
Silky-matt

Iron-Free
No contamination

Reusable
Recyclable

Reflective
Road markings

Project	
Main Contractor	
Consultant	
Submittal No. / Rev.	00
Date	Nov 2026

Construction Chemicals

Contents

1. Method Statement 3

2. Technical Data Sheet 8

3. Test Reports 11

4. Approvals & Certificates 12

METHOD STATEMENT

Beadmix — Iron-Free Spherical Glass Beads Blasting, Filler & Reflective

Project Name		**Document No.**	OMX-MS-BEADMIX
Main Contractor		**Revision**	01
Consultant		**Date of Issue**	Nov 2026
Product	Beadmix	**Status**	For Approval

1. Purpose

This method statement defines the procedure, sequence, resources, quality checks and safety measures for the supply and application of Beadmix on site. It ensures that the work is carried out safely, in line with the approved drawings and project specification, and achieves the performance stated in the O MIX Technical Data Sheet.

2. Scope of Work

This method statement covers the handling, use in blasting, recovery and use as drop-on reflective beads of Beadmix glass beads.

- Receipt and storage.
- Selection of grading.
- Use in blasting.
- Use as drop-on beads for road markings.
- Recovery, sieving and disposal.

3. Definitions

Term	Meaning
Glass bead blasting	Cleaning or finishing with spherical glass beads.
Drop-on beads	Beads applied onto wet road paint for reflectivity.
Grading	Particle size range of the beads.

4. Roles & Responsibilities

Role	Responsibility
Project Manager	Overall responsibility for planning, resources, approvals and coordination with the consultant and main contractor.
Site Engineer	Supervises the work daily; confirms substrate readiness, climate conditions, mixing, consumption and sequence; keeps daily records.

Role	Responsibility
QA/QC Inspector	Carries out inspections and tests at each stage, records results, raises inspection requests at hold points and signs the checklist.
HSE Officer	Conducts toolbox talks, checks PPE, ventilation, access and safe storage; stops work if unsafe conditions arise.
Foreman / Applicators	Carry out the work as per this method statement and report any deviation immediately.
Storekeeper	Receives, stores and issues materials in original packaging under the stated storage conditions; controls batch numbers.

5. Materials

Material	Description
Beadmix	Glass beads, 25 kg bags or 1 t big bags

5.1 Key product data

Property	Typical Value
Material	Soda-lime glass, iron-free
Shape	Spherical
Hardness	6 Mohs
Softening point	approx. 730 °C
Specific gravity	approx. 2.5
Bulk density	1.5 – 1.6 g/cm³
SiO_2	70 – 75 %
Na_2O	12 – 15 %

6. Tools & Equipment

- Blast cabinet or blasting unit
- Compressor
- Sieves
- Bead dispenser for road marking
- Thermo-hygrometer and surface thermometer (dew point check)
- Moisture meter
- Measuring buckets and scale
- Masking tape and protective sheeting
- Lighting and extension cables

6.1 Personal protective equipment

- Blasting hood / respirator
- Eye protection

- Gloves
- Ear protection

7. Storage & Handling

- Store dry, in closed bags, protected from moisture. Not hazardous for transport.
- Store on pallets, off the ground, in a dry, covered and ventilated area.
- Keep containers closed until use; use materials on a first-in, first-out basis.
- Store rolls and cartons flat, off the ground, protected from direct sunlight, heat, oil and mechanical damage.
- Handle with care to avoid damage to packaging; do not stack beyond the safe height.

8. Pre-Start Requirements

- Material submittal, this method statement and the inspection plan approved by the consultant.
- Work area handed over clean, free of other trades and with safe access.
- Adequate lighting, power supply and ventilation available.
- Climate conditions checked and recorded before work starts.
- A trial area prepared and approved where required by the project.
- Toolbox talk held with the work team covering this method statement and the safety measures.

9. Surface Preparation

1. Select the grading as per the required finish.
2. Check that blasting equipment and dust extraction are working.
3. Mask areas not to be blasted.
4. Run a trial on a sample part and approve the finish.

10. Preparation of Material

1. Check grading and batch on the bag label.
2. Keep beads dry; load into the blasting unit or dispenser.

11. Use

1. Blasting: adjust pressure and distance; blast evenly.
2. Road marking: apply drop-on beads into the wet paint immediately after application.
3. Inspect the finish or reflectivity.
4. Record grading, pressure and quantity used.

12. Recovery & Inspection

- Recover beads, sieve out fines and reuse.
- Dispose of spent fines as per local regulations.
- Clean the work area.

13. Quality Control & Inspection

Check	Stage	Acceptance Criteria	By
Material	On receipt	Correct grading, dry	Storekeeper
Finish	After blasting	Uniform silky-matt	QA/QC
Reflectivity	Road marking	As per specification	QA/QC

13.1 Inspection and test plan

Activity	Inspection / Test	Frequency	Record
Material receipt	Grading, dryness	Each delivery	Material inspection report
Trial	Finish approved	Each job	Trial record
Use	Pressure, finish / reflectivity	Daily	Daily report

14. Defects & Remedies

Defect	Likely Cause	Remedy
Uneven finish	Wrong pressure or distance	Adjust and re-blast
High breakage	Pressure too high	Reduce pressure
Low reflectivity	Late drop-on	Apply beads into wet paint immediately

15. Health, Safety & Environment

Hazard	Control Measures
Dust from blasting	Enclosed cabinet or respirator; extraction
Noise	Ear protection
Slips on spilled beads	Clean spills immediately
Compressed air	Inspected hoses and fittings

- Use blasting cabinets or approved respiratory protection during blasting.
- Wear eye protection.
- Spilled beads are slippery; clean immediately.
- Eyes: rinse with clean water; do not rub.
- Inhalation of dust: move to fresh air.

15.1 Waste & environment

- Collect empty containers and residues in designated bins.
- Do not discharge material or washings into drains or soil.
- Allow small quantities of leftover mixed material to cure before disposal; dispose of according to local regulations.

16. Cleaning

- Sweep or vacuum spilled beads immediately.

17. Limitations

- Keep beads dry.
- Any deviation from this method statement must be approved by the Site Engineer and the consultant.

Appendix A — Inspection Checklist

Inspection Item	Result	Remarks
Grading verified	☐ Yes ☐ No	
Equipment checked	☐ Yes ☐ No	
Trial approved	☐ Yes ☐ No	
Blasting / drop-on carried out	☐ Yes ☐ No	
Finish inspected	☐ Yes ☐ No	
Beads recovered and sieved	☐ Yes ☐ No	
Area cleaned	☐ Yes ☐ No	

Inspected by	Signature	Date

Construction Chemicals

Technical Data Sheet

Beadmix — Submittal Document

Construction Chemicals

Product Datasheet
Edition: 01 | Date: Nov 2026
Accessories



Beadmix

Iron-Free Spherical Glass Beads
Blasting, Filler & Reflective

Product Description

Beadmix is a range of iron-free, spherical soda-lime glass beads for light blasting and cleaning (silky-matt finish), as a filler and as reflective beads for road markings. The beads are reusable and are available in fine, medium and coarse gradings.

Uses

- Light blasting, peening and cleaning of metals.
- Silky-matt surface finishing.
- Filler in coatings and composites.
- Reflective beads for road marking paints.
- Cleaning of moulds and machine parts.

Advantages

- Silky-matt, uniform finish.
- Iron-free; no contamination.
- Reusable many times.
- Reflective for road markings.
- Rolls-Royce CSS 8 approved; AMS 2431/6, MIL-G-9954, NF L 06-831.

Application

1. **Selection**
   Select the grading for the required finish or use.
2. **Blasting / Mixing**
   Use in blasting equipment, or add to paint / drop-on for road markings.
3. **Recovery**
   Recover, sieve and reuse beads in blasting systems.

Consumption

As per use
blasting, filler or road marking
Road marking drop-on rate as per marking specification.

Packaging

25 kg bags on pallets up to 1 t, or 1 t big bags.

Storage & Shelf Life

Store dry, in closed bags, protected from moisture. Not hazardous for transport.

Technical Data

Typical values at 25 °C

Property	Typical Value	Test Method
Material	Soda-lime glass, iron-free	—
Shape	Spherical	—
Hardness	6 Mohs	—
Softening point	approx. 730 °C	—
Specific gravity	approx. 2.5	—
Bulk density	1.5 – 1.6 g/cm³	—
SiO_2	70 – 75 %	—
Na_2O	12 – 15 %	—
CaO	7 – 12 %	—
Approval	Rolls-Royce CSS 8	—
Specifications	AMS 2431/6, MIL-G-9954, NF L 06-831	—

Consumption

Grade	Size ranges (µm)
Fine	0 – 50 / 40 – 70 / 70 – 110 / 90 – 150
Medium	100 – 200 / 150 – 250 / 200 – 300 / 200 – 400
Coarse	300 – 400 / 400 – 600 / 600 – 800

Consumption is theoretical and varies with substrate porosity, profile and application method.

Application Conditions

- Keep beads dry; moisture causes clumping.
- Use in blasting equipment suitable for glass beads.
- Remove fines and broken beads during recycling.

Application Notes

- Select finer grades for smooth finishes and coarser grades for faster cleaning.
- Adjust blasting pressure to avoid excessive breakage.
- For road markings apply drop-on beads into wet paint.
- Sieve recycled beads regularly.

Health & Safety

- Use blasting cabinets or approved respiratory protection during blasting.
- Wear eye protection.
- Spilled beads are slippery; clean immediately.

First Aid & Cleaning

- Eyes: rinse with clean water; do not rub.
- Inhalation of dust: move to fresh air.
- Skin: wash with water.
- Sweep or vacuum spilled beads immediately.

The information in this datasheet is based on laboratory tests and practical experience and is given in good faith. Users should verify product suitability for their specific application. O MIX reserves the right to update this information without prior notice.

Construction Chemicals

Test Reports

Beadmix — Submittal Document

To be attached: laboratory test reports supporting the values in the Technical Data Sheet.

Construction Chemicals

Approvals & Certificates

Beadmix — Submittal Document

To be attached: approvals and certificates, where available.