Construction Chemicals

Product Datasheet
Edition: 01 | Date: Nov 2026
Accessories



Beadmix

Iron-Free Spherical Glass Beads
Blasting, Filler & Reflective

Product Description

Beadmix is a range of iron-free, spherical soda-lime glass beads for light blasting and cleaning (silky-matt finish), as a filler and as reflective beads for road markings. The beads are reusable and are available in fine, medium and coarse gradings.

Uses

- Light blasting, peening and cleaning of metals.
- Silky-matt surface finishing.
- Filler in coatings and composites.
- Reflective beads for road marking paints.
- Cleaning of moulds and machine parts.

Advantages

- Silky-matt, uniform finish.
- Iron-free; no contamination.
- Reusable many times.
- Reflective for road markings.
- Rolls-Royce CSS 8 approved; AMS 2431/6, MIL-G-9954, NF L 06-831.

Application

1. **Selection**
   Select the grading for the required finish or use.
2. **Blasting / Mixing**
   Use in blasting equipment, or add to paint / drop-on for road markings.
3. **Recovery**
   Recover, sieve and reuse beads in blasting systems.

Consumption

As per use
blasting, filler or road marking
Road marking drop-on rate as per marking specification.

Packaging

25 kg bags on pallets up to 1 t, or 1 t big bags.

Storage & Shelf Life

Store dry, in closed bags, protected from moisture. Not hazardous for transport.

Technical Data

Typical values at 25 °C

Property	Typical Value	Test Method
Material	Soda-lime glass, iron-free	—
Shape	Spherical	—
Hardness	6 Mohs	—
Softening point	approx. 730 °C	—
Specific gravity	approx. 2.5	—
Bulk density	1.5 – 1.6 g/cm³	—
SiO_2	70 – 75 %	—
Na_2O	12 – 15 %	—
CaO	7 – 12 %	—
Approval	Rolls-Royce CSS 8	—
Specifications	AMS 2431/6, MIL-G-9954, NF L 06-831	—

Consumption

Grade	Size ranges (µm)
Fine	0 – 50 / 40 – 70 / 70 – 110 / 90 – 150
Medium	100 – 200 / 150 – 250 / 200 – 300 / 200 – 400
Coarse	300 – 400 / 400 – 600 / 600 – 800

Consumption is theoretical and varies with substrate porosity, profile and application method.

Application Conditions

- Keep beads dry; moisture causes clumping.
- Use in blasting equipment suitable for glass beads.
- Remove fines and broken beads during recycling.

Application Notes

- Select finer grades for smooth finishes and coarser grades for faster cleaning.
- Adjust blasting pressure to avoid excessive breakage.
- For road markings apply drop-on beads into wet paint.
- Sieve recycled beads regularly.

Health & Safety

- Use blasting cabinets or approved respiratory protection during blasting.
- Wear eye protection.
- Spilled beads are slippery; clean immediately.

First Aid & Cleaning

- Eyes: rinse with clean water; do not rub.
- Inhalation of dust: move to fresh air.
- Skin: wash with water.
- Sweep or vacuum spilled beads immediately.

The information in this datasheet is based on laboratory tests and practical experience and is given in good faith. Users should verify product suitability for their specific application. O MIX reserves the right to update this information without prior notice.