Construction Chemicals

Product Datasheet
Edition: 01 | Date: Nov 2026
Bonding Agents



Addmix VAE

Vinyl Acetate–Ethylene (VAE) Polymer Dispersion

Product Description

Addmix VAE is a vinyl acetate–ethylene copolymer dispersion stabilised with polyvinyl alcohol. It is designed for flexible, water-resistant adhesives with rapid setting, good adhesion to plastics and a very low film-forming temperature.

Uses

- Film-to-wood lamination.
- Flooring installation adhesives.
- Paper and packaging adhesives.
- Leather, textile and foam bonding.
- Water-resistant adhesives for building insulation materials.

Advantages

- Excellent elongation, flexibility and water resistance.
- Rapid setting compared with PVAc.
- Good adhesion to plastics.
- Permanently flexible adhesive films.
- Film formation at 0 °C.

Application

1. **Formulation**
   Use as the main binder in water-based adhesive formulations.
2. **Mixing**
   Add fillers, plasticisers and additives under stirring as per the formulation.
3. **Testing**
   Verify viscosity, open time and bond strength on the intended substrates.

Consumption

As per formulation
binder in water-based adhesives
Determine the dosage by laboratory trials.

Packaging

200 kg and 220 kg drums; IBC 1,000 – 1,100 kg; flexi-bags and bulk tankers.

Storage & Shelf Life

9 months in original, unopened packaging. Store at +5 °C to +30 °C; protect from frost and direct sunlight.

Technical Data

Typical values at 25 °C

Property	Typical Value	Test Method
Polymer	Vinyl acetate–ethylene copolymer	—
Protective colloid	Polyvinyl alcohol (PVOH)	—
Appearance	Milky white dispersion	—
Solids content	54 – 56 %	—
Viscosity (25 °C)	1300 – 2000 mPa·s	—
pH	4 – 6	—
Density (20 °C)	approx. 1.07 g/cm³	—
Minimum film-forming temperature	0 °C	—
Glass transition temperature	approx. 0 °C	—
Average particle size	approx. 1 µm	—
Dispersion film	Clear, glossy, slightly tacky	—

Consumption

Application	Use
Lamination adhesives	Main binder
Flooring adhesives	Main binder
Paper and packaging	Main binder
Leather / textile / foam	Main binder

Consumption is theoretical and varies with substrate porosity, profile and application method.

Application Conditions

- Store and use at +5 °C to +30 °C.
- Do not freeze.
- Check compatibility with all formulation components before production.
- Stir before use.

Application Notes

- Determine the formulation and dosage by laboratory trials.
- Add plasticisers and fillers slowly under stirring.
- Adjust viscosity with water where needed.
- Test bond strength and water resistance on the actual substrates.

Health & Safety

- Wear gloves and safety goggles.
- Avoid contact with eyes and prolonged skin contact.
- Spills make floors slippery; absorb with inert material.

First Aid & Cleaning

- Eyes: rinse with clean water for 15 minutes and seek medical advice.
- Skin: wash with soap and water.
- Ingestion: rinse mouth and seek medical advice.
- Clean equipment with water before the dispersion dries.

The information in this datasheet is based on laboratory tests and practical experience and is given in good faith. Users should verify product suitability for their specific application. O MIX reserves the right to update this information without prior notice.