Construction Chemicals

Product Datasheet
Edition: 01 | Date: Nov 2026
Bonding Agents

Bondmix SBR Plus

Hydrolysis-Resistant SBR Latex
Mortar Modifier & Bonding Agent



Product Description

Bondmix SBR Plus is a hydrolysis-resistant styrene-butadiene latex for modifying cement mortars and as a bonding agent. It reduces the water demand and improves workability, adhesion, abrasion resistance and resistance to salts, making it suitable for demanding plasters, floors and repairs.

Uses

- High-abrasion plasters and floor toppings.
- Patching on low-absorbency surfaces.
- Polymer-modified repair mortars.
- Screeds and tile bedding mortars.
- Bonding agent for new mortars on old concrete.

Advantages

- Hydrolysis resistant: suitable for wet conditions.
- Improves adhesion and flexibility.
- Increases abrasion resistance.
- Reduces water demand; better workability.
- Improves resistance to salts.

Application

1. **Surface Preparation**
   Clean, sound substrate; pre-wet to saturated surface dry.
2. **Mixing**
   Add Bondmix SBR Plus to the gauging water of the mortar, or mix with cement to a bonding slurry — as recommended.
3. **Application**
   Apply the bonding coat and place the modified mortar while the coat is still wet.

Consumption

0.2 – 0.4 kg/m²
as bonding agent (diluted)
As mortar modifier: dosage as specified for the mortar.

Packaging

5 kg and 20 kg jerrycans.

Storage & Shelf Life

12 months in original, unopened packaging. Store at +5 °C to +35 °C; protect from frost and direct sunlight.

Technical Data

Typical values at 25 °C

Property	Typical Value	Test Method
Base	Styrene-butadiene latex, hydrolysis resistant	—
Appearance	Milky white liquid	—
Density	1.0 – 1.1 kg/L	—
Solids content	45 – 50 %	—
Flammability	Non-flammable	—
Application temperature	+5 °C to +35 °C	—

Consumption

Use	Consumption
Bonding agent (diluted)	0.2 – 0.4 kg/m²
Mortar modifier	As specified for the mortar

Consumption is theoretical and varies with substrate porosity, profile and application method.

Application Conditions

- Application temperature: +5 °C to +35 °C.
- Substrate sound, clean, pre-wetted to saturated surface dry.
- Do not apply on frozen surfaces or in rain.
- Place the mortar while the bonding coat is still wet.

Application Notes

- Replace part of the gauging water with Bondmix SBR Plus; reduce added water accordingly.
- For bonding coats, dilute with water and mix with cement to a slurry — as recommended.
- Do not over-mix modified mortars to avoid air entrainment.
- Cure modified mortars to avoid rapid drying.

Health & Safety

- Wear gloves and safety goggles.
- Avoid contact with eyes and prolonged skin contact.
- When mixed with cement the mix is alkaline.

First Aid & Cleaning

- Eyes: rinse immediately with plenty of clean water for at least 15 minutes and seek medical advice.
- Skin: wash with soap and water; cement is alkaline when wet.
- Inhalation of dust: move to fresh air.
- Clean tools with water immediately after use.

The information in this datasheet is based on laboratory tests and practical experience and is given in good faith. Users should verify product suitability for their specific application. O MIX reserves the right to update this information without prior notice.