METHOD STATEMENT

Bondmix SBR — SBR Bonding Agent & Mortar Admixture

Project Name		**Document No.**	OMX-MS-BONDMIXSBR
Main Contractor		**Revision**	01
Consultant		**Date of Issue**	Nov 2026
Product	Bondmix SBR	**Status**	For Approval

1. Purpose

This method statement defines the procedure, sequence, resources, quality checks and safety measures for the supply and application of Bondmix SBR on site. It ensures that the work is carried out safely, in line with the approved drawings and project specification, and achieves the performance stated in the O MIX Technical Data Sheet.

2. Scope of Work

This method statement covers surface preparation, mixing and application of Bondmix SBR as a bonding slurry and as a mortar admixture for plasters, screeds and repair mortars.

- Inspection and acceptance of the substrate and the work area.
- Surface preparation and repair of defects.
- Mixing and application of the material as described in this document.
- Curing, protection and handover of the completed area.
- Quality control, inspection and documentation of each stage.

3. Definitions

Term	Meaning
Bonding slurry	Mix of SBR, water and cement brushed onto the substrate to bond the next layer.
Admixture	SBR added to the mixing water of a mortar.
SSD	Saturated surface dry — damp substrate without standing water.
Wet-on-wet	Next layer applied while the slurry is still wet.

4. Roles & Responsibilities

Role	Responsibility
Project Manager	Overall responsibility for planning, resources, approvals and coordination with the consultant and main contractor.
Site Engineer	Supervises the work daily; confirms substrate readiness, climate conditions, mixing, consumption and sequence; keeps daily records.

Role	Responsibility
QA/QC Inspector	Carries out inspections and tests at each stage, records results, raises inspection requests at hold points and signs the checklist.
HSE Officer	Conducts toolbox talks, checks PPE, ventilation, access and safe storage; stops work if unsafe conditions arise.
Foreman / Applicators	Carry out the work as per this method statement and report any deviation immediately.
Storekeeper	Receives, stores and issues materials in original packaging under the stated storage conditions; controls batch numbers.

5. Materials

Material	Description
Bondmix SBR	SBR latex, 5 kg and 20 kg jerrycans
Cement	Ordinary Portland cement
Sand	Clean, graded sand for mortars

5.1 Key product data

Property	Typical Value
Base	Styrene-butadiene (SBR) latex
Appearance	Milky white liquid
Density	1.02 – 1.05 kg/L
Solids content	45 – 50 %
Drying time	1 – 3 hours
Adhesion	≥ 1.5 MPa
Application temperature	+5 °C to +35 °C

6. Tools & Equipment

- Mixer
- Buckets
- Stiff brushes
- Trowels
- Pressure washer
- Measuring jugs
- Thermo-hygrometer and surface thermometer (dew point check)
- Moisture meter
- Measuring buckets and scale
- Masking tape and protective sheeting
- Lighting and extension cables

6.1 Personal protective equipment

- Gloves
- Goggles
- Dust mask
- Safety shoes

7. Storage & Handling

- 12 months in original, unopened packaging. Store at +5 °C to +35 °C; protect from frost and direct sunlight.
- Store on pallets, off the ground, in a dry, covered and ventilated area.
- Keep containers closed until use; use materials on a first-in, first-out basis.
- Keep containers tightly closed and protect from frost and direct sunlight.
- Handle with care to avoid damage to packaging; do not stack beyond the safe height.

8. Pre-Start Requirements

- Material submittal, this method statement and the inspection plan approved by the consultant.
- Work area handed over clean, free of other trades and with safe access.
- Adequate lighting, power supply and ventilation available.
- Climate conditions checked and recorded before work starts.
- A trial area prepared and approved where required by the project.
- Toolbox talk held with the work team covering this method statement and the safety measures.

9. Surface Preparation

1. Remove loose concrete, laitance, oil and contaminants.
2. Roughen smooth surfaces mechanically.
3. Pre-wet the substrate to saturated surface dry; remove standing water.
4. Obtain QA/QC approval of the prepared surface before application.

10. Mixing

1. Check the batch number and expiry date and record them.
2. Shake or stir the container before use.
3. Bonding slurry: mix Bondmix SBR with water and cement to a creamy, lump-free consistency — as recommended.
4. Admixture: replace part of the mixing water with Bondmix SBR at 5 – 10 L per 50 kg cement; mix the mortar as normal.
5. Mix only the quantity that can be used before the slurry dries.

11. Application

1. Brush the bonding slurry well into the damp substrate at 0.15 – 0.25 kg/m².
2. Apply the plaster, screed or repair mortar while the slurry is still wet.
3. Compact and finish the mortar as specified.
4. Record quantities used per area.

12. Curing & Protection

- Protect from rapid drying, sun and wind for at least 24 hours.
- Keep moist where specified.
- Barricade the area until the mortar has set.

13. Quality Control & Inspection

Check	Stage	Acceptance Criteria	By
Substrate	Before application	Sound, clean, SSD	QA/QC
Slurry	During application	Creamy, full coverage, still wet when overlaid	Site Engineer
Dosage	Admixture use	5 – 10 L per 50 kg cement	Site Engineer
Bond	After curing	No hollow sound on tap test	QA/QC

13.1 Inspection and test plan

Activity	Inspection / Test	Frequency	Record
Material receipt	Product, batch, expiry	Each delivery	Material inspection report
Surface preparation	Clean, sound, SSD	Each area	Inspection request (hold point)
Slurry	Consistency, coverage	Each area	Daily report
Mortar	Applied wet-on-wet	Each area	Daily report
Final	Bond (tap test)	Each area	Handover checklist

14. Defects & Remedies

Defect	Likely Cause	Remedy
Hollow sound / debonding	Slurry dried before mortar; dusty substrate	Remove and reapply wet-on-wet on clean substrate
Cracking	Rapid drying	Cure properly; protect from sun and wind
Weak surface	Excess water in mix	Follow dosage; do not over-water

15. Health, Safety & Environment

Hazard	Control Measures
Skin and eye contact	Gloves, goggles; eye-wash available
Cement dust	Dust masks when mixing slurries
Slips	Housekeeping; clean spills
Manual handling	Correct lifting technique

- Wear gloves and safety goggles.
- Avoid contact with eyes and prolonged skin contact.
- When mixed with cement the mix is alkaline.
- Eyes: rinse immediately with plenty of clean water for at least 15 minutes and seek medical advice.
- Skin: wash with soap and water; cement is alkaline when wet.

15.1 Waste & environment

- Collect empty containers and residues in designated bins.
- Do not discharge material or washings into drains or soil.
- Allow small quantities of leftover mixed material to cure before disposal; dispose of according to local regulations.

16. Cleaning

- Clean tools with water immediately after use.

17. Limitations

- Do not apply below +5 °C or on frozen substrates.
- Do not let the bonding slurry dry before applying the next layer.
- Any deviation from this method statement must be approved by the Site Engineer and the consultant.

Appendix A — Inspection Checklist

Inspection Item	Result	Remarks
Substrate prepared and SSD	☐ Yes ☐ No	
Slurry mixed to consistency	☐ Yes ☐ No	
Slurry brushed into surface	☐ Yes ☐ No	
Mortar applied wet-on-wet	☐ Yes ☐ No	
Admixture dosage recorded	☐ Yes ☐ No	
Curing carried out	☐ Yes ☐ No	
Tap test passed	☐ Yes ☐ No	

Inspected by	Signature	Date