Construction Chemicals

Product Datasheet
Edition: 01 | Date: Nov 2026
Bonding Agents

Bondmix SBR

SBR Bonding Agent
& Mortar Admixture



Product Description

Bondmix SBR is a styrene-butadiene (SBR) latex bonding agent. It is used as a bonding slurry with cement or as a partial replacement of mixing water to improve adhesion, water resistance and durability of plasters, screeds and repair mortars.

Uses

- Bonding slurry between old and new cementitious layers.
- Water-resistant plasters and screeds.
- Polymer-modified repair mortars.
- Wet areas and water tanks.
- Admixture for cement mortars.

Advantages

- Improves adhesion: ≥ 1.5 MPa.
- Improves water resistance.
- Increases durability of mortars.
- Easy to use; mixes with water and cement.
- Water-based, non-flammable.

Application

1. **Surface Preparation**
   Clean, sound substrate; pre-wet to saturated surface dry.
2. **Mixing**
   For bonding slurry mix Bondmix SBR with water and cement to a creamy consistency; as admixture replace part of the mixing water.
3. **Application**
   Brush the slurry into the surface and apply the mortar while the slurry is still wet.

Consumption

0.15 – 0.25 kg/m²
as bonding slurry
As admixture: 5 – 10 L per 50 kg cement.

Packaging

5 kg and 20 kg jerrycans.

Storage & Shelf Life

12 months in original, unopened packaging. Store at +5 °C to +35 °C; protect from frost and direct sunlight.

Technical Data

Typical values at 25 °C

Property	Typical Value	Test Method
Base	Styrene-butadiene (SBR) latex	—
Appearance	Milky white liquid	—
Density	1.02 – 1.05 kg/L	—
Solids content	45 – 50 %	—
Drying time	1 – 3 hours	—
Adhesion	≥ 1.5 MPa	—
Application temperature	+5 °C to +35 °C	—

Consumption

Use	Dosage / Consumption
Bonding slurry	0.15 – 0.25 kg/m²
Admixture in mortars and plasters	5 – 10 L per 50 kg cement

Consumption is theoretical and varies with substrate porosity, profile and application method.

Application Conditions

- Application temperature: +5 °C to +35 °C.
- Substrate sound, clean and pre-wetted to saturated surface dry.
- Do not apply on frozen surfaces or in rain.
- Apply the mortar while the bonding slurry is still wet.

Application Notes

- Bonding slurry: mix with water and cement to a creamy consistency — as recommended.
- Admixture: replace part of the mixing water with Bondmix SBR at 5 – 10 L per 50 kg cement.
- Do not allow the slurry to dry before applying the next layer.
- Cure polymer-modified mortars as normal cement mortars, avoiding rapid drying.

Health & Safety

- Wear gloves and safety goggles.
- Avoid contact with eyes and prolonged skin contact.
- When mixed with cement the mix is alkaline.

First Aid & Cleaning

- Eyes: rinse immediately with plenty of clean water for at least 15 minutes and seek medical advice.
- Skin: wash with soap and water; cement is alkaline when wet.
- Inhalation of dust: move to fresh air.
- Clean tools with water immediately after use.

The information in this datasheet is based on laboratory tests and practical experience and is given in good faith. Users should verify product suitability for their specific application. O MIX reserves the right to update this information without prior notice.