Construction Chemicals

**Product Datasheet**
Edition: 01 | Date: Nov 2026
Sport Court Systems

# Acrycourt FC

Thermoplastic Acrylic Finish
for Courts & Decorative Concrete




## Product Description

Acrycourt FC is a water-based thermoplastic acrylic coating for sport courts and decorative concrete. It gives a colourful, UV-resistant finish with slip resistance in wet and dry conditions, on concrete and asphalt.

## Uses

- Tennis, basketball and multi-purpose courts.
- Playgrounds and walkways.
- Decorative concrete and asphalt surfaces.
- Colour coats in court systems.

## Advantages

- UV resistant, colour stable.
- Slip resistant in wet and dry conditions.
- Bond strength ≥ 2.5 MPa.
- Flexible: elongation 80 – 120 %.
- Water-based, VOC < 50 g/L.

## Application

1. **Surface Preparation**
   Clean, dry, sound concrete or asphalt; prime concrete where specified.
2. **Mixing**
   Stir thoroughly; dilute 5 – 10 % with water.
3. **Application**
   Apply 2 – 3 coats crosswise by squeegee or roller.

## Consumption

**0.15 – 0.20 kg/m²**
per coat
System (2 – 3 coats): 0.30 – 0.60 kg/m².

## Packaging

20 kg pails in colours.

## Storage & Shelf Life

12 months in original, unopened packaging. Store at +5 °C to +35 °C; protect from frost and direct sunlight.

## Technical Data

*Typical values at 25 °C*

| Property | Typical Value | Test Method |
|---|---|---|
| **Base** | Thermoplastic water-based acrylic | — |
| **Density** | 1.35 – 1.45 kg/L | — |
| **Solids content** | 55 – 70 % | — |
| **Viscosity** | 18,000 – 25,000 mPa·s | — |
| **Bond strength** | ≥ 2.5 MPa | — |
| **Elongation** | 80 – 120 % | — |
| **Drying time** | 30 – 60 minutes | — |
| **Recoat time** | 4 – 6 hours | — |
| **VOC** | < 50 g/L | — |
| **Dilution** | 5 – 10 % water | — |

## Consumption

| Use | Consumption |
|---|---|
| **Each coat** | 0.15 – 0.20 kg/m² |
| **System (2 – 3 coats)** | 0.30 – 0.60 kg/m² |

*Consumption is theoretical and varies with substrate porosity, profile and application method.*

## Application Conditions

- Air and surface temperature: +10 °C to +35 °C.
- Do not apply when rain or dew is expected before the coat has dried.
- Asphalt at least 14 days old; concrete at least 28 days old.
- Surface clean, dry, sound and free of oil and loose material.

## Application Notes

- Dilute 5 – 10 % with clean water.
- Apply 2 – 3 coats crosswise.
- Use one batch per area to avoid shade differences.
- Avoid application in direct midday sun on hot surfaces.

## Health & Safety

- Wear gloves and safety goggles.
- Avoid contact with eyes and prolonged skin contact.
- Ensure ventilation in enclosed areas.

## First Aid & Cleaning

- Eyes: rinse with clean water for 15 minutes and seek medical advice.
- Skin: wash with soap and water.
- Inhalation: move to fresh air.
- Clean tools with water immediately after use.

*The information in this datasheet is based on laboratory tests and practical experience and is given in good faith. Users should verify product suitability for their specific application. O MIX reserves the right to update this information without prior notice.*