Construction Chemicals

Product Datasheet
Edition: 01 | Date: Nov 2026
Sport Court Systems



Acrycourt RAC

Acrylic Resurfacer
for Sport Courts

Product Description

Acrycourt RAC is a water-based acrylic resurfacer and filler for asphalt and concrete sport courts. Mixed with silica sand and water, it fills pores and minor depressions and gives a uniform, levelled base for the cushion and colour coats.

Uses

- Tennis, basketball and multi-purpose courts.
- Resurfacing new or old asphalt and concrete.
- Filling pores and minor depressions.
- Base layer of the O MIX Hard and Soft Acrylic court systems.

Advantages

- Fills pores and levels the surface.
- Bond strength ≥ 1.5 MPa.
- Mixed with sand on site.
- Water-based, low odour.
- Uniform base for colour coats.

Application

1. **Surface Preparation**
   Clean, dry, sound asphalt or concrete; prime concrete with Bondmix WB.
2. **Mixing**
   Mix 1 part Acrycourt RAC with 1 – 2 parts silica sand and water as recommended.
3. **Application**
   Spread with a rubber squeegee; allow each coat to dry before the next.

Consumption

1.0 – 2.0 kg/m²
total, in 1 – 2 coats
1.5 kg/m² in the O MIX Hard / Soft Acrylic systems.

Packaging

20 kg pails and 200 kg drums.

Storage & Shelf Life

12 months in original, unopened packaging. Store at +5 °C to +35 °C; protect from frost and direct sunlight.

Technical Data

Typical values at 25 °C

Property	Typical Value	Test Method
Base	Water-based acrylic	—
Colour	White	—
Density	1.30 – 1.40 kg/L	—
Solids content	50 – 60 %	—
Bond strength	≥ 1.5 MPa	—
Drying time	1 – 3 hours	—
Recoat time	6 – 12 hours	—
Sand addition	1 : 1 to 1 : 2 (product : sand) as recommended	—

Consumption

Use	Consumption
Resurfacing (1 – 2 coats)	1.0 – 2.0 kg/m²
Hard / Soft Acrylic systems	1.5 kg/m²

Consumption is theoretical and varies with substrate porosity, profile and application method.

Application Conditions

- Air and surface temperature: +10 °C to +35 °C.
- Do not apply when rain or dew is expected before the coat has dried.
- Asphalt at least 14 days old; concrete at least 28 days old.
- Surface clean, dry, sound and free of oil and loose material.

Application Notes

- Mix sand and water as recommended to a squeegee consistency.
- Apply in thin coats; do not fill depressions deeper than the layer thickness in one pass.
- Allow each coat to dry fully before the next.
- Lightly scrape ridges between coats.

Health & Safety

- Wear gloves and safety goggles.
- Avoid contact with eyes and prolonged skin contact.
- Ensure ventilation in enclosed areas.

First Aid & Cleaning

- Eyes: rinse with clean water for 15 minutes and seek medical advice.
- Skin: wash with soap and water.
- Inhalation: move to fresh air.
- Clean tools with water immediately after use.

The information in this datasheet is based on laboratory tests and practical experience and is given in good faith. Users should verify product suitability for their specific application. O MIX reserves the right to update this information without prior notice.