Construction Chemicals

Product Datasheet
Edition: 01 | Date: Nov 2026
Sport Court Systems

Bondmix WB

Water-Based Two-Component
Epoxy Primer & Bonding Coat



Product Description

Bondmix WB is a two-component, water-based epoxy primer for concrete and cementitious substrates, indoors and outdoors. It penetrates and seals the surface, reduces peeling and improves the adhesion of acrylic and polyurethane sport-court systems, micro-cement and waterproofing coatings. It is milky when applied and dries clear.

Uses

- Primer for acrylic and PU sport-court systems.
- Primer and bonding coat for Micromix Deco micro-cement.
- Primer for Roofguard AC waterproofing systems.
- Sealing of porous concrete and screeds.
- Interior and exterior use.

Advantages

- Water-based, low VOC, low odour.
- Penetrates and seals porous substrates.
- Improves adhesion of following layers.
- Reduces peeling and delamination.
- Dries clear.

Application

1. **Surface Preparation**
   Clean, sound, dust-free concrete; damp but without standing water is acceptable.
2. **Mixing**
   Add Part A to Part B (1 : 4 by weight) and mix 2 – 3 min with a slow-speed mixer.
3. **Application**
   Apply by roller or brush at 0.15 – 0.30 kg/m²; next layer after 4 – 6 hours.

Consumption

0.15 – 0.30 kg/m²
per coat, depending on porosity
0.2 kg/m² in O MIX court, roof and micro-cement systems.

Packaging

10 kg sets (Part A 2 kg + Part B 8 kg) and 20 kg sets (Part A 4 kg + Part B 16 kg).

Storage & Shelf Life

12 months in original, unopened packaging. Store dry at +5 °C to +35 °C, away from direct sunlight. Protect from frost.

Technical Data

Typical values at 25 °C

Property	Typical Value	Test Method
Mixing ratio (A : B)	1 : 4 by weight — pre-weighed sets, mix as recommended	—
Appearance	Milky; dries clear	—
Density	1.05 – 1.15 kg/L	—
Solids content	30 – 55 %	—
Viscosity	500 – 1500 mPa·s	—
Pot life	1 – 2 hours	—
Touch dry	1 – 2 hours	—
Recoat interval	4 – 6 hours	—
Full cure	24 hours	—
Coverage	approx. 6 – 8 m²/L	—
Application temperature	+10 °C to +35 °C	—

Consumption

Use	Consumption
Dense concrete	0.15 – 0.20 kg/m²
Porous concrete / screed	0.20 – 0.30 kg/m²
O MIX court, roof and micro-cement systems	0.2 kg/m²

Consumption is theoretical and varies with substrate porosity, profile and application method.

Application Conditions

- Ambient and substrate temperature: +10 °C to +35 °C.
- Relative humidity: max. 85 %.
- Substrate clean, sound; damp is acceptable, no standing water.
- Concrete at least 28 days old (asphalt not to be primed).

Application Notes

- Mix complete sets at 1 : 4 by weight.
- Do not leave puddles; apply a uniform film.
- Apply the next layer after 4 – 6 hours and within 24 hours.
- Clean tools with water before the material cures.

Health & Safety

- Wear gloves and safety goggles.
- Uncured epoxy may cause skin sensitisation; avoid skin and eye contact.
- Ensure ventilation in enclosed areas.

First Aid & Cleaning

- Eyes: rinse immediately with plenty of clean water for at least 15 minutes and seek medical advice.
- Skin: remove contaminated clothing and wash with soap and water; do not use solvents on skin.
- Inhalation: move to fresh air; seek medical advice if symptoms persist.
- Ingestion: do not induce vomiting; seek medical advice immediately.
- Clean tools with water immediately after use.