Construction Chemicals

SUBMITTAL DOCUMENT

# Mixflex EPDM

Coloured EPDM Granules
for Sports & Play Surfaces




| Colour | Elastic | Safe | Thickness |
|---|---|---|---|
| UV stable | > 400 % | Shock absorbing | 10 – 20 mm |

| | |
|---|---|
| **Project** | |
| **Main Contractor** | |
| **Consultant** | |
| **Submittal No. / Rev.** | 00 |
| **Date** | Nov 2026 |

Construction Chemicals

# Contents


1. Method Statement 3

2. Technical Data Sheet 9

3. Test Reports 12

4. Approvals & Certificates 13

METHOD STATEMENT

# Mixflex EPDM — Coloured EPDM Granules for Sports & Play Surfaces

| | | | |
|---|---|---|---|
| **Project Name** | | **Document No.** | OMX-MS-MIXFLEXEPDM |
| **Main Contractor** | | **Revision** | 01 |
| **Consultant** | | **Date of Issue** | Nov 2026 |
| **Product** | Mixflex EPDM | **Status** | For Approval |

## 1. Purpose

This method statement defines the procedure, sequence, resources, quality checks and safety measures for the supply and application of Mixflex EPDM on site. It ensures that the work is carried out safely, in line with the approved drawings and project specification, and achieves the performance stated in the O MIX Technical Data Sheet.

## 2. Scope of Work

This method statement covers preparation, mixing, application, curing and inspection of Mixflex EPDM (coloured epdm granules for sports & play surfaces).

- Inspection and acceptance of the substrate and the work area.
- Surface preparation and repair of defects.
- Mixing and application of the material as described in this document.
- Curing, protection and handover of the completed area.
- Quality control, inspection and documentation of each stage.

## 3. Definitions

| Term | Meaning |
|---|---|
| **Pot life** | Time the mixed material remains workable after adding water. |
| **SSD** | Saturated surface dry — substrate damp but without standing water. |
| **Layer thickness** | Thickness of one application pass. |
| **Curing** | Keeping the applied material protected from rapid drying until it gains strength. |

## 4. Roles & Responsibilities

| Role | Responsibility |
|---|---|
| **Project Manager** | Overall responsibility for planning, resources, approvals and coordination with the consultant and main contractor. |
| **Site Engineer** | Supervises the work daily; confirms substrate readiness, climate conditions, mixing, consumption and sequence; keeps daily records. |

| Role | Responsibility |
|---|---|
| **QA/QC Inspector** | Carries out inspections and tests at each stage, records results, raises inspection requests at hold points and signs the checklist. |
| **HSE Officer** | Conducts toolbox talks, checks PPE, ventilation, access and safe storage; stops work if unsafe conditions arise. |
| **Foreman / Applicators** | Carry out the work as per this method statement and report any deviation immediately. |
| **Storekeeper** | Receives, stores and issues materials in original packaging under the stated storage conditions; controls batch numbers. |

## 5. Materials

| Material | Description |
|---|---|
| **Mixflex EPDM** | 25 kg PE bags, colours on request. |

### 5.1 Key product data

| Property | Typical Value |
|---|---|
| **Granule size** | 0.5 – 3 mm |
| **Density** | approx. 1.6 g/cm³ |
| **Hardness** | Shore A 60 – 70 |
| **Elongation** | > 400 % |
| **Tensile strength** | > 6 MPa |
| **Service temperature** | -30 °C to +80 °C |

## 6. Tools & Equipment

- Pressure washer
- Wire brushes
- Slow-speed mixer
- Brushes
- Rollers
- Airless spray
- Wet-film comb
- Thermo-hygrometer and surface thermometer (dew point check)
- Moisture meter
- Measuring buckets and scale
- Masking tape and protective sheeting
- Lighting and extension cables

### 6.1 Personal protective equipment

- Gloves
- Goggles
- Overalls
- Mask for spray

## 7. Storage & Handling

- Store dry and covered, away from direct sunlight.
- Store on pallets, off the ground, in a dry, covered and ventilated area.
- Keep containers closed until use; use materials on a first-in, first-out basis.
- Keep containers tightly closed and protect from frost and direct sunlight.
- Handle with care to avoid damage to packaging; do not stack beyond the safe height.

## 8. Pre-Start Requirements

- Material submittal, this method statement and the inspection plan approved by the consultant.
- Work area handed over clean, free of other trades and with safe access.
- Adequate lighting, power supply and ventilation available.
- Climate conditions checked and recorded before work starts.
- A trial area prepared and approved where required by the project.
- Toolbox talk held with the work team covering this method statement and the safety measures.

## 9. Surface Preparation

1. Remove dust, dirt, oil, efflorescence and loose material.
2. Repair cracks and defects.
3. Ensure the surface is sound and dry (or as specified).
4. Pre-wet absorbent surfaces to a saturated surface-dry condition; remove standing water.
5. Protect adjacent surfaces with masking tape and sheeting.
6. Obtain QA/QC approval of the prepared surface before starting the next step.

## 10. Mixing

1. Check the batch number and expiry date and record them.
2. Weigh granules and binder (15 – 20 %).
3. Mix 3 – 5 minutes in a forced-action mixer.

## 11. Application

1. Spread the mix between screed rails.
2. Level and compact with a trowel or roller.
3. Work in manageable areas and finish each area in one operation where possible.
4. Check layer thickness and consumption regularly and record the results.

## 12. Curing & Protection

- Cure 24 hours before use.
- Protect from sun, wind and rain; keep moist where required during the first 24 hours.
- Barricade the area and display warning signs.

## 13. Quality Control & Inspection

| Check | Stage | Acceptance Criteria | By |
|---|---|---|---|
| **Substrate** | Before application | Prepared, sound and clean as specified | QA/QC |
| **Climate** | During work | Base dry, primed and clean | Site Engineer |
| **Consumption** | During application | 8 – 10 kg/m² per 1 cm thickness | QA/QC |
| **Finish** | After curing | Uniform, no defects | QA/QC |

### 13.1 Inspection and test plan

| Activity | Inspection / Test | Frequency | Record |
|---|---|---|---|
| **Material receipt** | Product, batch, expiry, packaging condition | Each delivery | Material inspection report |
| **Climate** | Air / substrate temperature, RH, dew point | Start of shift and every 4 hours | Daily climate log |
| **Surface preparation** | Visual, moisture, soundness | Each area | Inspection request (hold point) |
| **Application** | Consumption, thickness, appearance | Each coat / area | Daily progress report |
| **Final inspection** | Visual, continuity, finish | Each completed area | Handover checklist |

## 14. Defects & Remedies

| Defect | Likely Cause | Remedy |
|---|---|---|
| **Shrinkage cracks** | Rapid drying; layer too thick; excess water | Remove, reapply in thinner layers and protect from drying |
| **Poor adhesion / hollow areas** | Dusty or dry substrate | Remove, clean and pre-wet; reapply |
| **Dusting surface** | Excess water or late finishing | Light sanding and apply a fresh thin layer |
| **Uneven finish** | Insufficient trowelling | Sand and apply a finishing layer |

## 15. Health, Safety & Environment

| Hazard | Control Measures |
|---|---|
| **Skin and eye contact** | Gloves, goggles, overalls; eye-wash available |
| **Inhalation of vapours / dust** | Ventilation; masks as required |
| **Slips and trips** | Housekeeping; barricades and signs |
| **Manual handling** | Correct lifting technique; mechanical aids |
| **Electrical tools** | Inspected tools; protected cables |

- Wear gloves and safety goggles.
- Avoid contact with eyes and prolonged skin contact.
- Ensure ventilation in enclosed areas; use a mask for spray application.
- Eyes: rinse with clean water for 15 minutes and seek medical advice.
- Skin: wash with soap and water.

### 15.1 Waste & environment

- Collect empty containers and residues in designated bins.
- Do not discharge material or washings into drains or soil.
- Allow small quantities of leftover mixed material to cure before disposal; dispose of according to local regulations.

## 16. Cleaning

- Clean tools with water immediately after use.

## 17. Limitations

- Base dry, primed and clean.
- Ambient temperature: +10 °C to +35 °C.
- Do not apply in rain or when rain is expected before the material has set.
- Any deviation from this method statement must be approved by the Site Engineer and the consultant.

## Appendix A — Inspection Checklist

| Inspection Item | Result | Remarks |
|---|---|---|
| Substrate prepared and approved | ☐ Yes ☐ No | |
| Batch numbers recorded | ☐ Yes ☐ No | |
| Material mixed as specified | ☐ Yes ☐ No | |
| Applied at specified consumption | ☐ Yes ☐ No | |
| Curing and protection carried out | ☐ Yes ☐ No | |
| Final inspection passed | ☐ Yes ☐ No | |

| Inspected by | Signature | Date |
|---|---|---|
| | | |

Construction Chemicals

# Technical Data Sheet

Mixflex EPDM — Submittal Document

Construction Chemicals

**Product Datasheet**
Edition: 01 | Date: Nov 2026
Sport Court Systems

# Mixflex EPDM

Coloured EPDM Granules
for Sports & Play Surfaces




## Product Description

Mixflex EPDM is UV-stable, coloured EPDM rubber granules for playgrounds, running tracks and multi-purpose courts. Mixed with Mixflex PU Binder, it is spread and compacted to form a seamless, resilient surface.

## Uses

- Children's playgrounds.
- Running tracks.
- Multi-purpose courts.
- Walkways and pool surrounds.

## Advantages

- UV stable colours.
- Elastic: elongation > 400 %.
- Durable, seamless surface.
- Safe, shock-absorbing.
- Custom colours.

## Application

1. **Preparation**
   Prime the base as specified.
2. **Mixing**
   Mix granules with 15 – 20 % Mixflex PU Binder for 3 – 5 minutes.
3. **Laying**
   Spread, level and compact within the working time.

## Consumption

**8 – 10 kg/m²**
per 1 cm thickness

## Packaging

25 kg PE bags, colours on request.

## Storage & Shelf Life

Store dry and covered, away from direct sunlight.

## Technical Data

*Typical values at 25 °C*

| Property | Typical Value | Test Method |
|---|---|---|
| **Granule size** | 0.5 – 3 mm | — |
| **Density** | approx. 1.6 g/cm³ | — |
| **Hardness** | Shore A 60 – 70 | — |
| **Elongation** | > 400 % | — |
| **Tensile strength** | > 6 MPa | — |
| **Service temperature** | -30 °C to +80 °C | — |

## Consumption

| Thickness | Consumption |
|---|---|
| **10 mm** | 8 – 10 kg/m² |
| **15 mm** | 12 – 14 kg/m² |
| **20 mm** | 16 – 18 kg/m² |

*Consumption is theoretical and varies with substrate porosity, profile and application method.*

## Application Conditions

- Base dry, primed and clean.
- Ambient temperature: +10 °C to +35 °C.
- No rain during laying and curing.

## Application Notes

- Use 15 – 20 % Mixflex PU Binder by weight.
- Lay within the binder working time.
- Do not lay in rain or on wet bases.

## Health & Safety

- Wear gloves and safety goggles.
- Avoid contact with eyes and prolonged skin contact.
- Ensure ventilation in enclosed areas; use a mask for spray application.

## First Aid & Cleaning

- Eyes: rinse with clean water for 15 minutes and seek medical advice.
- Skin: wash with soap and water.
- Inhalation: move to fresh air.
- Ingestion: rinse mouth and seek medical advice.
- Clean tools with water immediately after use.

*The information in this datasheet is based on laboratory tests and practical experience and is given in good faith. Users should verify product suitability for their specific application. O MIX reserves the right to update this information without prior notice.*

Construction Chemicals

# Test Reports

Mixflex EPDM — Submittal Document

*To be attached: laboratory test reports supporting the values in the Technical Data Sheet.*

Construction Chemicals

# Approvals & Certificates

Mixflex EPDM — Submittal Document

*To be attached: approvals and certificates, where available.*