Construction Chemicals

Product Datasheet
Edition: 01 | Date: Nov 2026
Sport Court Systems

Mixflex EPDM

Coloured EPDM Granules
for Sports & Play Surfaces



Product Description

Mixflex EPDM is UV-stable, coloured EPDM rubber granules for playgrounds, running tracks and multi-purpose courts. Mixed with Mixflex PU Binder, it is spread and compacted to form a seamless, resilient surface.

Uses

- Children's playgrounds.
- Running tracks.
- Multi-purpose courts.
- Walkways and pool surrounds.

Advantages

- UV stable colours.
- Elastic: elongation > 400 %.
- Durable, seamless surface.
- Safe, shock-absorbing.
- Custom colours.

Application

1. **Preparation**
   Prime the base as specified.
2. **Mixing**
   Mix granules with 15 – 20 % Mixflex PU Binder for 3 – 5 minutes.
3. **Laying**
   Spread, level and compact within the working time.

Consumption

8 – 10 kg/m²
per 1 cm thickness

Packaging

25 kg PE bags, colours on request.

Storage & Shelf Life

Store dry and covered, away from direct sunlight.

Technical Data

Typical values at 25 °C

Property	Typical Value	Test Method
Granule size	0.5 – 3 mm	—
Density	approx. 1.6 g/cm³	—
Hardness	Shore A 60 – 70	—
Elongation	> 400 %	—
Tensile strength	> 6 MPa	—
Service temperature	-30 °C to +80 °C	—

Consumption

Thickness	Consumption
10 mm	8 – 10 kg/m²
15 mm	12 – 14 kg/m²
20 mm	16 – 18 kg/m²

Consumption is theoretical and varies with substrate porosity, profile and application method.

Application Conditions

- Base dry, primed and clean.
- Ambient temperature: +10 °C to +35 °C.
- No rain during laying and curing.

Application Notes

- Use 15 – 20 % Mixflex PU Binder by weight.
- Lay within the binder working time.
- Do not lay in rain or on wet bases.

Health & Safety

- Wear gloves and safety goggles.
- Avoid contact with eyes and prolonged skin contact.
- Ensure ventilation in enclosed areas; use a mask for spray application.

First Aid & Cleaning

- Eyes: rinse with clean water for 15 minutes and seek medical advice.
- Skin: wash with soap and water.
- Inhalation: move to fresh air.
- Ingestion: rinse mouth and seek medical advice.
- Clean tools with water immediately after use.

The information in this datasheet is based on laboratory tests and practical experience and is given in good faith. Users should verify product suitability for their specific application. O MIX reserves the right to update this information without prior notice.