Construction Chemicals

Product Datasheet
Edition: 01 | Date: Nov 2026
Sport Court Systems



Mixflex PU Binder

One-Component Polyurethane Binder for Rubber Granules

Product Description

Mixflex PU Binder is a one-component, solvent-free polyurethane binder for SBR and EPDM rubber granules. It cures with moisture to form elastic, durable sports and play surfaces.

Uses

- Binding EPDM and SBR granules.
- Playgrounds and running tracks.
- Shock pads.
- Multi-purpose courts.

Advantages

- Solvent-free, 100 % solids.
- Elastic, durable bond.
- Working time 30 – 60 min.
- Service -30 °C to +80 °C.
- One component.

Application

1. **Preparation**
   Weigh granules and binder.
2. **Mixing**
   Add 15 – 20 % binder by weight of the mix and mix 3 – 5 minutes.
3. **Laying**
   Lay within 30 – 60 minutes; level and compact.

Consumption

15 – 20 %
of mix weight

Packaging

5 kg and 20 kg metal pails; 200 – 220 kg drums.

Storage & Shelf Life

12 months in original, unopened packaging. Store dry at +5 °C to +35 °C, away from direct sunlight.

Technical Data

Typical values at 25 °C

Property	Typical Value	Test Method
Type	One-component, moisture-curing PU	—
Colour	Clear / amber	—
Solids content	100 %	—
Density	1.02 – 1.10 kg/L	—
Viscosity	3000 – 6000 mPa·s	—
Working time	30 – 60 min	—
Setting	8 – 12 hours	—
Full cure	24 hours	—
Service temperature	-30 °C to +80 °C	—

Consumption

Use	Binder dosage
EPDM wearing layer	15 – 20 %
SBR base / shock pad	15 – 20 %

Consumption is theoretical and varies with substrate porosity, profile and application method.

Application Conditions

- Ambient temperature: +10 °C to +35 °C.
- No rain during laying.
- Base dry and primed.

Application Notes

- Keep containers closed (moisture-curing).
- Lay within the working time.
- Do not lay in rain.

Health & Safety

- Wear chemical-resistant gloves, safety goggles and overalls.
- Uncured resin may cause skin sensitisation; avoid skin and eye contact.
- Contains isocyanates; ensure ventilation.

First Aid & Cleaning

- Eyes: rinse immediately with plenty of clean water for at least 15 minutes and seek medical advice.
- Skin: remove contaminated clothing and wash with soap and water; do not use solvents on skin.
- Inhalation: move to fresh air; seek medical advice if symptoms persist.
- Ingestion: do not induce vomiting; seek medical advice immediately.
- Clean tools with the recommended thinner before the material cures.

The information in this datasheet is based on laboratory tests and practical experience and is given in good faith. Users should verify product suitability for their specific application. O MIX reserves the right to update this information without prior notice.