Construction Chemicals

Product Datasheet
Edition: 01 | Date: Nov 2026
Protective Coating

Mixcoat PU

Two-Component Polyurethane
Waterproofing & Protective Membrane



Product Description

Mixcoat PU is a two-component, elastic polyurethane membrane for waterproofing and protection of roofs, terraces, floors, façades and ceilings. It forms a seamless, UV-resistant film that bridges cracks, protects concrete against carbonation and chloride ingress, and can be reinforced with fibre mesh at joints and details.

Uses

- Waterproofing of roofs, terraces and balconies.
- Protective membrane for floors, façades and ceilings.
- Top coat in the O MIX PU Protective system over epoxy body coats.
- Protection of concrete against carbonation and chlorides.
- Waterproofing of wet areas, with optional fibre-mesh reinforcement.

Advantages

- Seamless, elastic and crack-bridging.
- UV resistant for exposed areas.
- Elongation ≥ 200 %.
- Reduces chloride ingress by 96 %.
- Water cleaning of tools.

Application

1. **Surface Preparation**
   Clean, sound substrate; repair cracks; form coves at corners and prime.
2. **Mixing**
   Add Part B to Part A (1 : 1 by weight) and mix 2 – 3 min with a slow-speed mixer.
3. **Application**
   Apply by squeegee or notched trowel in at least two coats, 1.0 – 1.2 kg/m² per mm.

Consumption

1.0 – 1.2 kg/m²
per 1 mm dry film, in 2 – 3 coats
0.5 kg/m² when used as top coat in the PU Protective system.

Packaging

20 kg sets (Part A 10 kg + Part B 10 kg) and 5 kg sets (2.5 kg + 2.5 kg).

Storage & Shelf Life

12 months in original, unopened packaging. Store dry at +5 °C to +35 °C, protected from frost and direct sunlight.

Technical Data

Typical values at 25 °C

Property	Typical Value	Test Method
Mixing ratio (A : B)	1 : 1 by weight	—
Hardness	Shore A 80	—
Tensile strength	4.2 N/mm²	—
Elongation at break	≥ 200 %	—
Adhesion to concrete	2 N/mm²	—
Water vapour transmission	43 g/m²/day	—
Chloride ion reduction	96 %	—
Recoat interval	16 hours at 25 °C (max. 48 hours)	—
Primer tack-free time	6 – 8 hours	—

Consumption

Application	Coats	Consumption
Waterproofing membrane, 1 mm	2 – 3	1.0 – 1.2 kg/m²
Top coat in PU Protective system	1 – 2	0.5 kg/m²
Reinforced detail (joints, corners)	2 + mesh	as required

Consumption is theoretical and varies with substrate porosity, profile and application method.

Application Conditions

- Ambient and substrate temperature: +10 °C to +35 °C.
- Substrate at least 3 °C above dew point.
- Relative humidity: max. 85 %.
- Substrate clean and sound; damp but without standing water when the wet-surface primer is used.
- Concrete at least 28 days old.

Application Notes

- Prime with O MIX PU or solvent-free epoxy primer; use the wet-surface primer on damp substrates.
- Apply the membrane after the primer is tack-free (6 – 8 hours).
- Apply at least two coats; apply the next coat within 48 hours (16 hours at 25 °C).
- Reinforce joints, corners and cracks with fibre mesh or geotextile embedded in the first coat.
- Broadcast quartz sand into the final wet coat where an anti-slip finish is required.

Health & Safety

- Wear chemical-resistant gloves, safety goggles and overalls.
- Avoid skin and eye contact; uncured material may cause sensitisation.
- Ensure good ventilation in enclosed areas.

First Aid & Cleaning

- Eyes: rinse immediately with plenty of clean water for at least 15 minutes and seek medical advice.
- Skin: remove contaminated clothing and wash with soap and water; do not use solvents on skin.
- Inhalation: move to fresh air; seek medical advice if symptoms persist.
- Ingestion: do not induce vomiting; seek medical advice immediately.
- Clean tools with water immediately after use; cured material can only be removed mechanically.

The information in this datasheet is based on laboratory tests and practical experience and is given in good faith. Users should verify product suitability for their specific application. O MIX reserves the right to update this information without prior notice.