Construction Chemicals

Product Datasheet
Edition: 01 | Date: Nov 2026
Protective Coating



O-Defoamer

Mineral-Oil Based Defoamer
for Water-Based Paints & Plasters

Product Description

O-Defoamer is an APEO-free defoamer based on mineral oil and non-ionic surfactants. It prevents foam formation and destroys entrapped air during production and application of water-based architectural paints, plasters and adhesives, giving smooth, pinhole-free films.

Uses

- Water-based architectural paints: matt, silk and textured.
- Solvent-free emulsion paints.
- Synthetic resin plasters.
- Water-based adhesives.
- Use in both the grind (dispersion) and let-down stages.

Advantages

- Effective at low dosage: 0.1 – 0.5 %.
- APEO free.
- Prevents pinholes and craters.
- Long-lasting defoaming effect.
- Easy to incorporate in water-based systems.

Application

1. **Dosage**
   Use 0.1 – 0.5 % of the total formulation weight, depending on the system.
2. **Grind Stage**
   Add about two thirds of the dosage during pigment dispersion.
3. **Let-Down Stage**
   Add the remaining third during let-down under stirring.

Consumption

0.1 – 0.5 %
of total formulation weight
Optimum dosage to be determined by laboratory trials.

Packaging

135 kg drums and 900 kg IBC totes.

Storage & Shelf Life

15 months in original, unopened packaging. Store at +5 °C to +35 °C; protect from frost and direct sunlight. Stir before use.

Technical Data

Typical values at 25 °C

Property	Typical Value	Test Method
Composition	Mineral oil, non-ionic surfactants	—
Appearance	White emulsion	—
Active content	approx. 47 %	—
Viscosity	< 1500 mPa·s	—
Density	0.94 g/cm³	—
Flash point	> 190 °C	—
APEO	Free	—
Storage temperature	+5 °C to +35 °C	—
Shelf life	15 months	—

Consumption

Formulation	Dosage (% of total weight)
Matt paints	0.1 – 0.4 %
Silk paints	0.2 – 0.4 %
Textured paints / plasters	0.3 – 0.5 %
Solvent-free paints	0.2 – 0.5 %
Adhesives	0.1 – 0.3 %

Consumption is theoretical and varies with substrate porosity, profile and application method.

Application Conditions

- Add under stirring with adequate shear for uniform distribution.
- Split the dosage: about 2/3 in the grind and 1/3 in the let-down.
- Product temperature during use: +5 °C to +35 °C.
- Stir the container before use; the emulsion may separate slightly on storage.

Application Notes

- Determine the optimum dosage in laboratory trials for each formulation.
- Overdosing may cause surface defects such as craters or reduced gloss.
- Check compatibility with the complete formulation before production.
- Do not freeze.

Health & Safety

- Wear gloves and safety goggles.
- Avoid contact with eyes; avoid prolonged skin contact.
- Spills make floors slippery; absorb with inert material.

First Aid & Cleaning

- Eyes: rinse with clean water for 15 minutes and seek medical advice.
- Skin: wash with soap and water.
- Ingestion: rinse mouth and seek medical advice.
- Clean equipment with warm water and detergent.