METHOD STATEMENT

Stone Sealer BS — Water-Based Silane / Siloxane Penetrating Water Repellent

Project Name		**Document No.**	OMX-MS-STONESEALERBS
Main Contractor		**Revision**	01
Consultant		**Date of Issue**	Nov 2026
Product	Stone Sealer BS	**Status**	For Approval

1. Purpose

This method statement defines the procedure, sequence, resources, quality checks and safety measures for the supply and application of Stone Sealer BS on site. It ensures that the work is carried out safely, in line with the approved drawings and project specification, and achieves the performance stated in the O MIX Technical Data Sheet.

2. Scope of Work

This method statement covers surface preparation and application of Stone Sealer BS, a water-based silane/siloxane penetrating water repellent, on natural and artificial stone, concrete, brick, masonry, interlocking pavers and façades.

- Inspection of the substrate and the work area.
- Cleaning and repair of the substrate.
- Trial area and approval.
- Application of the water repellent.
- Protection, inspection and handover of the treated area.

3. Definitions

Term	Meaning
Water repellent	Penetrating treatment that reduces water absorption without forming a surface film.
Flood coat	Application until the surface is saturated, without run-down.
Wet-on-wet	Second coat applied before the first coat has dried.
Coverage	Area treated per litre of material.
Trial area	Small area treated to approve appearance and consumption.

4. Roles & Responsibilities

Role	Responsibility
Project Manager	Overall responsibility for planning, resources, approvals and coordination with the consultant and main contractor.

Role	Responsibility
Site Engineer	Supervises the work daily; confirms substrate readiness, climate conditions, mixing, consumption and sequence; keeps daily records.
QA/QC Inspector	Carries out inspections and tests at each stage, records results, raises inspection requests at hold points and signs the checklist.
HSE Officer	Conducts toolbox talks, checks PPE, ventilation, access and safe storage; stops work if unsafe conditions arise.
Foreman / Applicators	Carry out the work as per this method statement and report any deviation immediately.
Storekeeper	Receives, stores and issues materials in original packaging under the stated storage conditions; controls batch numbers.

5. Materials

Material	Description
Stone Sealer BS	Silane / siloxane water repellent, 20 L jerrycans (1 L, 5 L, 200 L available)
Repair mortar / sealant	For cracks and joints before treatment

5.1 Key product data

Property	Typical Value
Base	Water-based silane / siloxane
Active content	8 – 12 %
Density (25 °C)	0.98 – 1.02 kg/L
pH	7 – 9
Flash point	> 100 °C
Number of coats	1 (2 on porous substrates)
Coverage	3 – 10 m²/L
Drying time	2 – 4 hours

6. Tools & Equipment

- Low-pressure sprayer
- Brushes
- Rollers
- Pressure washer
- Measuring jugs
- Masking materials
- Thermometer and weather forecast
- Moisture meter
- Masking tape and protective sheeting
- Spray mist screens where required

6.1 Personal protective equipment

- Gloves
- Goggles
- Overalls
- Mask for spray mist

7. Storage & Handling

- 12 months in original, unopened packaging. Store at +5 °C to +35 °C; protect from frost and direct sunlight.
- Store on pallets, off the ground, in a dry, covered and ventilated area.
- Keep containers closed until use; use materials on a first-in, first-out basis.
- Keep containers tightly closed and protect from frost and direct sunlight.
- Handle with care to avoid damage to packaging; do not stack beyond the safe height.

8. Pre-Start Requirements

- Material submittal, this method statement and the inspection plan approved by the consultant.
- Work area handed over clean, free of other trades and with safe access.
- Adequate lighting, power supply and ventilation available.
- Climate conditions checked and recorded before work starts.
- A trial area prepared and approved where required by the project.
- Toolbox talk held with the work team covering this method statement and the safety measures.

9. Surface Preparation

1. Inspect the surface; new concrete and mortar must be at least 28 days old.
2. Clean the surface by pressure washing or brushing to remove dirt, efflorescence, moss, oil and loose material.
3. Repair cracks wider than 0.3 mm and defective joints; allow repairs to cure.
4. Allow the surface to dry completely after cleaning (typically 2 – 3 dry days).
5. Mask and protect glass, frames, painted surfaces, plants and adjacent areas.
6. Prepare a trial area and obtain approval of appearance and consumption.
7. Obtain QA/QC approval of the prepared surface before application.

10. Preparation of Material

1. Check the batch number and expiry date and record them.
2. Stir or shake the container before use.
3. Use as supplied; do not dilute.
4. Pour into the sprayer tank or a clean bucket only the quantity needed.

11. Application

1. Apply by low-pressure sprayer, brush or roller until the surface is saturated (flood coat).
2. On vertical surfaces work from bottom to top, avoiding run-down.
3. On porous substrates apply the second coat wet-on-wet.
4. Remove excess material from dense surfaces before it dries to avoid shiny patches.
5. Record the quantity used per area to confirm the coverage.

12. Curing & Protection

- Drying time 2 – 4 hours; full water repellency after 24 – 72 hours.
- Protect from rain for at least 4 hours after application.
- Keep the treated area free of traffic and other trades until dry.
- Remove masking after the treatment has dried.

13. Quality Control & Inspection

Check	Stage	Acceptance Criteria	By
Substrate	Before application	Clean, dry, sound, ≥ 28 days, cracks repaired	QA/QC
Weather	Before and during work	+5 °C to +35 °C, no rain forecast for 4 h	Site Engineer
Trial area	Before full application	Appearance and coverage approved	QA/QC + Consultant
Coverage	During application	3 – 10 m²/L as per trial	QA/QC
Water repellency	After 72 hours	Water beads on the surface, no absorption	QA/QC

13.1 Inspection and test plan

Activity	Inspection / Test	Frequency	Record
Material receipt	Product, batch, expiry, packaging	Each delivery	Material inspection report
Climate	Air / substrate temperature, weather forecast	Start of shift	Daily log
Surface preparation	Clean, dry, repaired	Each area	Inspection request (hold point)
Application	Coverage, saturation, coats	Each area	Daily progress report
Final inspection	Water drop test, appearance	Each completed area	Handover checklist

14. Defects & Remedies

Defect	Likely Cause	Remedy
Shiny or dark patches	Excess material left on dense surface	Wipe excess before drying; clean with water while fresh

Defect	Likely Cause	Remedy
Poor water repellency	Wet substrate; under-application; rain too soon	Allow to dry and re-apply to saturation
White residue	Application in hot sun or on dirty surface	Clean surface; re-apply in suitable conditions
Run-down marks	Over-application on vertical surfaces	Work bottom to top with lighter passes

15. Health, Safety & Environment

Hazard	Control Measures
Eye and skin contact	Gloves, goggles; eye-wash available
Inhalation of spray mist	Low-pressure spray; masks; ventilation
Work at height	Approved scaffolding, harness and access
Slips	Housekeeping; barricades and signs
Manual handling	Correct lifting technique

- Wear gloves and safety goggles.
- Avoid contact with eyes and prolonged contact with skin.
- Use in well-ventilated areas; avoid inhaling spray mist.
- Eyes: rinse with clean water for 15 minutes and seek medical advice.
- Skin: wash with soap and water.

15.1 Waste & environment

- Collect empty containers and residues in designated bins.
- Do not discharge material or washings into drains or soil.
- Allow small quantities of leftover mixed material to cure before disposal; dispose of according to local regulations.

16. Cleaning

- Clean tools and spray equipment with water immediately after use.

17. Limitations

- Do not apply below +5 °C or above +35 °C.
- Do not apply on wet surfaces or when rain is expected within 4 hours.
- Not a waterproofing membrane against hydrostatic pressure.
- Any deviation from this method statement must be approved by the Site Engineer and the consultant.

Appendix A — Inspection Checklist

Inspection Item	Result	Remarks
Substrate age and condition verified	☐ Yes ☐ No	
Surface cleaned and dry	☐ Yes ☐ No	
Cracks and joints repaired	☐ Yes ☐ No	
Adjacent surfaces protected	☐ Yes ☐ No	
Trial area approved	☐ Yes ☐ No	
Material used undiluted	☐ Yes ☐ No	
Surface saturated without run-down	☐ Yes ☐ No	
Second coat on porous areas	☐ Yes ☐ No	
Protected from rain 4 h	☐ Yes ☐ No	
Water drop test passed	☐ Yes ☐ No	

Inspected by	Signature	Date