Construction Chemicals

Product Datasheet
Edition: 01 | Date: Nov 2026
Thermal Insulation



Roofguard Combo Mix

Two-Component Spray
Polyurethane Foam Insulation

Product Description

Roofguard Combo Mix is a two-component spray polyurethane foam for seamless thermal and acoustic insulation. It bonds strongly to concrete, metal and roofs, has a closed-cell structure and is flame-retarded.

Uses

- Roof insulation.
- Industrial buildings.
- Cold stores.
- Tanks and pipes.
- Walls and ceilings.

Advantages

- Thermal conductivity 0.020 – 0.025 W/m·K.
- Seamless, no joints.
- Closed cells ≥ 90 %.
- Strong adhesion to concrete and metal.
- Flame-retarded.

Application

1. **Surface Preparation**
   Clean, dry, sound surface.
2. **Mixing**
   Components A and B are mixed in the spray gun by a proportioning machine (1 : 1).
3. **Application**
   Spray in passes to the specified thickness; protect from UV with a coating.

Consumption

1 kg/m²
for approx. 25 – 30 mm

Packaging

Steel drums: Part A 220 kg + Part B 220 kg.

Storage & Shelf Life

12 months in original, unopened packaging. Store dry at +5 °C to +35 °C, away from direct sunlight.

Technical Data

Typical values at 25 °C

Property	Typical Value	Test Method
Mixing ratio (A : B)	1 : 1 (machine-proportioned)	—
Density	35 – 45 kg/m³	—
Thermal conductivity	0.020 – 0.025 W/m·K	—
Closed cells	≥ 90 %	—
Compressive strength	150 – 200 kPa	—
Water absorption	≤ 2 %	—
Application temperature	+10 °C to +40 °C	—

Consumption

Thickness	Consumption
25 – 30 mm	approx. 1 kg/m²
50 – 60 mm	approx. 2 kg/m²

Consumption is theoretical and varies with substrate porosity, profile and application method.

Application Conditions

- Application temperature: +10 °C to +40 °C.
- Surface dry and clean.
- No wind or rain during spraying.

Application Notes

- Use a heated plural-component spray machine.
- Spray in passes of 10 – 15 mm.
- Protect the foam from UV with a coating (e.g. Roofguard PUR).

Health & Safety

- Wear full-face respirator, gloves and coveralls during spraying.
- Isocyanates may cause sensitisation.
- Keep unprotected persons away from the spray area.

First Aid & Cleaning

- Eyes: rinse immediately with plenty of clean water for at least 15 minutes and seek medical advice.
- Skin: remove contaminated clothing and wash with soap and water; do not use solvents on skin.
- Inhalation: move to fresh air; seek medical advice if symptoms persist.
- Ingestion: do not induce vomiting; seek medical advice immediately.
- Clean tools with the recommended thinner before the material cures.

The information in this datasheet is based on laboratory tests and practical experience and is given in good faith. Users should verify product suitability for their specific application. O MIX reserves the right to update this information without prior notice.