Construction Chemicals

SUBMITTAL DOCUMENT

Acid Lock Pro

Integrated Chemical-Resistant
Epoxy Lining System



Chemical
Novolac top coat

3 Layers
Primer – body – top

Lining
Concrete & steel

Holiday-Free
Tested lining

Project	
Main Contractor	
Consultant	
Submittal No. / Rev.	00
Date	Nov 2026

Construction Chemicals

Contents

1. System Method Statement 3

2. TDS — O-Prime ST 11

3. TDS — O-Guard EP 15

4. TDS — Mixcoat Novolac 18

5. Test Reports 22

6. Approvals & Certificates 23

METHOD STATEMENT

Acid Lock Pro — Integrated Chemical-Resistant Epoxy Lining System

Project Name		**Document No.**	OMX-SMS-01
Main Contractor		**Revision**	01
Consultant		**Date of Issue**	Nov 2026
System	Acid Lock Pro	**Status**	For Approval

1. Purpose

This method statement defines the sequence, resources, inspection and test plan and safety measures for the installation of the Acid Lock Pro system on site. It describes how each layer of the system is prepared, mixed, applied, inspected and protected so that the completed system achieves the performance stated in the O MIX Technical Data Sheets of its components.

2. Scope of Work

Acid Lock Pro is a heavy-duty, integrated epoxy lining system for concrete and steel exposed to aggressive chemicals. A surface-tolerant epoxy primer is followed by a solvent-free epoxy body coat and finished with a high-build novolac epoxy top coat that gives very high resistance to acids, alkalis, solvents and fuels.

- Substrate inspection, testing and acceptance.
- Surface preparation and repair of defects.
- Stage 1: Primer — O-Prime ST.
- Stage 2: Body coat — O-Guard EP.
- Stage 3: Chemical-resistant top coat (2 coats) — Mixcoat Novolac.
- Curing, protection, final testing and handover.

2.1 System build-up

Stage	Product	Function	Consumption
1	O-Prime ST	Primer	0.18 – 0.20 kg/m²
2	O-Guard EP	Body coat	0.25 – 0.30 kg/m²
3	Mixcoat Novolac	Chemical-resistant top coat (2 coats)	0.50 – 0.60 kg/m² (smooth)

2.2 Typical areas of use

- Chemical plants and containment bunds.
- Wastewater and potable water tanks.
- Battery rooms and acid areas.
- Food, dairy and beverage plants.
- Heavy workshops and process areas.

3. Definitions

Term	Meaning
System	All layers of the build-up applied in the stated sequence.
Hold point	Stage at which work stops until QA/QC (and the consultant, where required) approve.
Recoat window	Minimum and maximum time between two layers for proper inter-layer bonding.
Dew point	Temperature at which moisture condenses; the substrate must be at least 3 °C above it.
Mock-up / trial area	Area applied before the main works to approve materials, method and appearance.
Pot life	Time a mixed multi-component material remains workable.
Holiday	Pinhole or discontinuity in a lining, detected with a holiday detector.
WFT / DFT	Wet film thickness during application / dry film thickness after cure.

4. Roles & Responsibilities

Role	Responsibility
Project Manager	Planning, resources, approvals and coordination with the consultant and main contractor.
Site Engineer	Daily supervision; confirms substrate readiness, climate, mixing, consumption and recoat windows; keeps daily records.
QA/QC Inspector	Carries out tests at each hold point, records results and signs the inspection checklist.
HSE Officer	Toolbox talks, PPE, ventilation, safe access and storage; stops unsafe work.
Applicator Foreman	Leads the application team and follows this method statement; reports deviations.
O MIX Technical Representative	Technical support, site visits and advice on product use when requested.

5. Materials

Product	Description	Packaging
O-Prime ST	Surface-Tolerant Epoxy Primer for Steel, Light Metals & Concrete	20 kg sets (Part A 16 kg + Part B 4 kg) and 5 kg sets (Part A 4 kg + Part B 1 kg) in metal pails.
O-Guard EP	Solvent-Free Polyamine Epoxy Lining for Potable Water Tanks	5 kg sets: Part A 4.35 kg in pail + Part B 0.65 kg in jerrycan.
Mixcoat Novolac	Solvent-Free Novolac Epoxy Coating for Chemical-Resistant Floors and Linings	5 kg and 20 kg sets: Part A in pail + Part B in jerrycan.

5.1 Key product data

Product	Mixing ratio	Pot life / working time	Recoat / drying
O-Prime ST	4 : 1 by weight	2 hours	Overcoat within the O-Prime ST recoat window (min. as per TDS)
O-Guard EP	200 : 30 by weight — pre-weighed sets, mix as recommended	40 min	24 hours (max. 48 hours)
Mixcoat Novolac	2 : 1 by volume — pre-weighed sets, mix full units as recommended	30 – 40 min	Min. 16 hours / max. 48 hours

6. Tools & Equipment

- Diamond grinder and/or shot blaster with dust extraction; industrial vacuum
- Slow-speed drill mixer (300 – 500 rpm) with spiral paddle
- Rollers, brushes, squeegees, notched trowels and steel trowels as required by each stage
- Scales and measuring containers for part mixing (where permitted)
- Thermo-hygrometer, surface thermometer and dew-point calculator
- Moisture meter and plastic sheets for moisture testing
- Masking tape, protective sheeting, barriers and warning signs
- Lighting and extension cables with residual current protection
- Wet-film comb gauge
- Pull-off adhesion tester
- Spiked roller and spiked shoes
- Holiday detector (wet sponge or high-voltage spark tester)
- Ultrasonic / magnetic DFT gauge
- Airless spray pump where specified
- Forced ventilation and gas detector for confined spaces

6.1 Personal protective equipment

- Safety shoes, helmet and high-visibility vest
- Chemical-resistant gloves (nitrile) and safety goggles
- Coveralls with long sleeves
- Dust masks (P2) during grinding and powder mixing
- Respirators with organic vapour cartridges for solvent-containing products and confined spaces
- Knee pads for floor work

7. Storage & Handling

- Store all products in original, unopened packaging in a dry, shaded and ventilated store at the temperatures stated in each TDS.
- Keep Part A, Part B (and Part C) of each kit together; do not mix components from different batches.
- Protect liquids from frost and direct sun, and powders from moisture.
- Store solvent-containing products away from heat, sparks and ignition sources.

- Use materials on a first-in, first-out basis and record batch numbers for each area.
- Condition materials to +15 °C to +25 °C for 24 hours before use in hot or cold weather.

8. Pre-Start Requirements

- Approved material submittal, this method statement and the inspection and test plan.
- Approved drawings showing areas, joints, upstands, drains and details.
- Work area handed over clean, free of other trades, with safe access, lighting and power.
- Mock-up / trial area executed and approved for system, colour and finish.
- Toolbox talk held with the team on this method statement and HSE measures.
- Climate monitoring equipment calibrated and available.

9. Substrate Inspection & Acceptance (Hold Point)

Check	Acceptance criteria	Method
Concrete age	≥ 28 days (cement-based substrates)	Site records
Compressive strength	≥ 25 N/mm²	Rebound hammer (ASTM C805) or cores
Surface tensile (pull-off) strength	≥ 1.5 N/mm²	Pull-off test ASTM D7234
Moisture content	< 4 % (no moisture under plastic sheet after 16 h)	Moisture meter; plastic sheet test ASTM D4263
Steel surface cleanliness	Sa 2½ (St 2 minimum where surface-tolerant primer is accepted)	ISO 8501-1
Dust on steel	Rating ≤ 2	ISO 8502-3 tape test
Climate	Substrate ≥ 3 °C above dew point; RH ≤ 85 %	ISO 8502-4 / thermo-hygrometer

10. Surface Preparation

1. Remove oil and grease by solvent cleaning (SSPC-SP 1).
2. Abrasive blast-clean steel to Sa 2½ (or power-tool clean to St 2 where accepted for the surface-tolerant primer).
3. Remove dust; check dust rating and soluble salts where required.
4. Concrete: shot blast or diamond grind to remove laitance and open the pores.
5. Mask and protect adjacent surfaces, drains and fixtures.
6. Record substrate test results and obtain QA/QC approval before priming (hold point).

11. Application Sequence

Apply the system stage by stage in the order below. Each stage must be inspected and approved before the next stage starts, and the next stage must be applied within the recoat window stated.

11.1 Stage 1 — Primer: O-Prime ST

Consumption: 0.18 – 0.20 kg/m². Time before next stage: Overcoat within the O-Prime ST recoat window (min. as per TDS).

1. Check batch numbers and condition the kit to +15 °C to +25 °C.
2. Stir Part A thoroughly to disperse any settled pigment.
3. Add the complete Part B to Part A (4 : 1 by weight).
4. Mix 2 – 3 minutes with a slow-speed mixer until uniform in colour.
5. Add epoxy thinner only where needed for spray application, within the recommended limit.
6. Apply a stripe coat by brush on welds, edges, bolts and corners.
7. Apply the full coat by brush, roller or airless spray at 0.18 – 0.20 kg/m² (100 µm DFT) or to the DFT specified for the system.
8. Measure wet film thickness continuously and adjust application to reach the specified DFT.
9. Apply additional coats where the specified total DFT exceeds the single-coat thickness.

11.2 Stage 2 — Body coat: O-Guard EP

Consumption: 0.25 – 0.30 kg/m². Time before next stage: Min. 24 h, max. 48 h.

1. Check batch numbers and condition the kit to +15 °C to +25 °C.
2. Add Part B to Part A (200 : 30 by weight) and mix 2 – 3 min with a slow-speed mixer.
3. Apply the body coat by roller or airless spray at 0.25 – 0.30 kg/m².
4. Apply the top coat after 24 hours and within 48 hours.
5. Check wet film thickness during application.

11.3 Stage 3 — Chemical-resistant top coat (2 coats): Mixcoat Novolac

Consumption: 0.50 – 0.60 kg/m² (smooth). Time before next stage: Min. 16 h, max. 48 h between coats; full chemical resistance after 7 days.

1. Check batch numbers and condition the kit to +15 °C to +25 °C.
2. Empty the full Part B into the Part A container (2 : 1 by volume).
3. Mix 3 minutes at 300–400 rpm with a helical paddle, scraping sides and bottom.
4. Do not split kits unless weighed on calibrated scales; do not thin.
5. Apply the primer at 0.15 – 0.20 kg/m² and allow to cure.
6. Apply Mixcoat Novolac evenly by short-nap roller, brush or airless spray, working continuously.
7. For anti-slip finish, broadcast quartz sand into the first coat within 15 minutes; remove excess after cure.
8. Apply the second coat within the recoat window (16 – 48 hours); if exceeded, abrade first.

12. Hold Points & Recoat Windows

Stage	Before starting	Waiting time before next stage	Approved by
1. O-Prime ST	Substrate accepted (Section 9)	Overcoat within the O-Prime ST recoat window (min. as per TDS)	QA/QC

Stage	Before starting	Waiting time before next stage	Approved by
2. O-Guard EP	Previous stage inspected and approved	Min. 24 h, max. 48 h	QA/QC
3. Mixcoat Novolac	Previous stage inspected and approved	Min. 16 h, max. 48 h between coats; full chemical resistance after 7 days	QA/QC

13. Curing, Protection & Return to Service

- Protect each layer from rain, dew, dust, water and traffic until it has cured.
- Barricade the area and display warning signs during application and curing.
- Keep ventilation running in enclosed areas until full cure.
- Do not fill or immerse the lining before full cure (7 days at 25 °C).

14. Quality Control & Inspection Test Plan

Activity	Inspection / Test	Frequency	Record
Material receipt	Product, batch, expiry, packaging condition	Each delivery	Material inspection report
Climate	Air / substrate temperature, RH, dew point (ISO 8502-4)	Start of shift and every 4 h	Daily climate log
Substrate	Strength, pull-off (ASTM D7234), moisture (ASTM D4263)	Each area (hold point)	Inspection request
Mixing	Complete kits, ratio, mixing time	Each mix	Daily record
Film thickness	WFT comb gauge (ASTM D4414) during application	Each coat	Daily record
DFT	Steel: SSPC-PA 2; concrete: ultrasonic gauge (SSPC-PA 9)	Each coat	DFT report
Consumption	Material used vs area	Each stage	Daily record
Continuity	Holiday test ASTM D4787 (concrete) / ASTM D5162 (steel)	100 % of lining	Holiday test report
Adhesion	Pull-off test on trial area / as specified (ASTM D7234 or D4541)	As specified	Test report
Final inspection	Appearance, continuity, finish, details	Each area	Handover checklist

15. Defects & Remedies

Defect	Likely cause	Remedy
Poor adhesion / delamination	Weak, dusty or damp substrate; recoat window exceeded	Remove, re-prepare and reapply; abrade and re-prime if window exceeded
Pinholes / bubbles	Outgassing; air trapped in mixing; thick application	Seal porous areas; mix slowly; spiked roller; sand and recoat
Blushing / tacky surface	High humidity or low temperature during cure	Wash, abrade and recoat in suitable conditions

Defect	Likely cause	Remedy
Soft spots	Incorrect ratio or incomplete mixing	Remove and reapply with complete kits
Holidays found	Insufficient thickness; pinholes	Abrade locally, recoat and re-test
Colour / shade variation	Different batches; uneven application	Use one batch per area; apply additional coat

16. Health, Safety & Environment

Hazard	Control measures
Skin / eye contact with resins and cement	Gloves, goggles, coveralls; eye-wash station
Inhalation of dust and vapours	Dust extraction; ventilation; masks / respirators
Fire (solvent vapours)	No smoking or hot work; fire extinguisher at the work area
Slips and trips	Housekeeping; barricades and warning signs
Manual handling	Correct lifting; mechanical aids for drums and pails
Electrical equipment	Inspected tools; protected cables with RCD
Confined spaces (tanks)	Permit to work, gas testing, forced ventilation, standby person

- Read the Safety Data Sheet of each product before use.
- Keep first-aid kit and eye-wash on site; follow the first-aid measures in each TDS.

16.1 Waste & environment

- Collect empty containers and residues in designated bins.
- Allow small quantities of mixed resin to cure before disposal; dispose of according to local regulations.
- Do not discharge materials or washings into drains or soil.

17. Cleaning

- Clean tools of water-based and cementitious products with water immediately after use.
- Clean tools of epoxy and PU products with the recommended thinner before the material cures.
- Cured material can only be removed mechanically.

18. Limitations

- Do not apply outside the temperature and humidity limits stated in the TDS of each product.
- Do not apply on wet surfaces or when rain or dew is expected before the layer has cured.
- Do not mix or substitute products from other systems without written approval from O MIX.
- Any deviation from this method statement must be approved by the Site Engineer and the consultant.

Appendix A — Inspection Checklist

Inspection Item	Result	Remarks
Approved submittal and method statement on site	☐ Yes ☐ No	
Mock-up approved	☐ Yes ☐ No	
Substrate tests passed (strength, pull-off, moisture)	☐ Yes ☐ No	
Surface preparation approved	☐ Yes ☐ No	
Stage 1 — O-Prime ST applied and approved	☐ Yes ☐ No	
Stage 2 — O-Guard EP applied and approved	☐ Yes ☐ No	
Stage 3 — Mixcoat Novolac applied and approved	☐ Yes ☐ No	
Recoat windows respected	☐ Yes ☐ No	
Final tests passed	☐ Yes ☐ No	
Area protected and handed over	☐ Yes ☐ No	

Inspected by	Signature	Date

Appendix B — Daily Application Record

Date	Area / zone	Stage	Batch No.	Qty used	Air / substrate °C	RH %	Sign

Construction Chemicals

O-Prime ST Data Sheet

Acid Lock Pro — Submittal Document

Construction Chemicals

Product Datasheet
Edition: 01 | Date: Nov 2026
Protective Coating

O-Prime ST

Surface-Tolerant Epoxy Primer
for Steel, Light Metals & Concrete



Product Description

O-Prime ST is a two-component, solvent-based, surface-tolerant epoxy primer. It gives reliable adhesion on steel prepared by hand or power tools (St 2) as well as blast-cleaned steel (Sa 2½), and is suitable for concrete, light metals and their alloys. It is the base primer of the O MIX protective coating systems.

Uses

- Primer for structural steel, tanks, pipes and steel structures.
- Maintenance painting where only hand or power-tool cleaning is possible (St 2).
- Primer for light metals and their alloys.
- Primer on concrete before epoxy and polyurethane protective systems.
- Base coat in O MIX Acid Lock, Potable Water Tank and PU Protective systems.

Advantages

- Surface tolerant: St 2 or Sa 2½.
- High solids 85 %, high build.
- Excellent adhesion to steel and concrete.
- Wide DFT range 100 – 1000 µm.
- Compatible with epoxy and PU topcoats.

Application

1. **Surface Preparation**
   Remove rust, mill scale, oil and loose paint to St 2 minimum (Sa 2½ preferred).
2. **Mixing**
   Add Part B to Part A (4 : 1 by weight) and mix 2 – 3 min with a slow-speed mixer.
3. **Application**
   Apply by brush, roller or airless spray at 0.18 – 0.20 kg/m² (100 µm DFT).

Consumption

0.18 – 0.20 kg/m²
at 100 µm DFT — theoretical 8.5 m²/L
Practical consumption depends on surface profile, method and losses.

Packaging

20 kg sets (Part A 16 kg + Part B 4 kg) and 5 kg sets (Part A 4 kg + Part B 1 kg) in metal pails.

Storage & Shelf Life

12 months in original, unopened packaging. Store dry at +5 °C to +35 °C, away from direct sunlight, heat and ignition sources.

Technical Data

Typical values at 25 °C

Property	Typical Value	Test Method
Mixing ratio (A : B)	4 : 1 by weight	—
Finish	Semi-gloss	—
Colours	Grey, red, white	—
Solids content	85 %	—
Recommended DFT	100 – 1000 µm	—
Theoretical coverage	8.5 m²/L at 100 µm DFT	—
Pot life (25 °C)	2 hours	—
VOC	316 g/L	—
Flash point	27 °C	—
Min. substrate temperature	+10 °C	—
Shelf life	12 months	—

Consumption

DFT	Theoretical coverage	Consumption
100 µm	8.5 m²/L	0.18 – 0.20 kg/m²
150 µm	5.7 m²/L	0.27 – 0.30 kg/m²
200 µm	4.25 m²/L	0.36 – 0.40 kg/m²

Consumption is theoretical and varies with substrate porosity, profile and application method.

Application Conditions

- Substrate temperature: min. +10 °C.
- Substrate at least 3 °C above dew point.
- Relative humidity: max. 85 %.
- Steel: St 2 minimum; Sa 2½ for immersion or severe exposure.
- Concrete: at least 28 days old, sound, dry (< 4 % moisture) and free of laitance.

Application Notes

- Mix complete sets only; partial mixing must be weighed exactly at 4 : 1.
- Apply by brush, roller or airless spray; use brush for stripe coats on edges, welds and bolts.
- Overcoat with the specified O MIX epoxy or PU coat within the recoat window stated for the system.
- Thin only with the recommended epoxy thinner where needed for spray.
- Do not apply on wet surfaces or when condensation is expected.

Health & Safety

- Solvent-based: flammable. Keep away from heat, sparks and open flames; no smoking.
- Wear chemical-resistant gloves, safety goggles and overalls; use a respirator with organic vapour cartridges in enclosed spaces.
- Uncured epoxy may cause skin sensitisation; avoid skin and eye contact.
- Ensure good ventilation during application and curing.

First Aid & Cleaning

- Eyes: rinse immediately with plenty of clean water for at least 15 minutes and seek medical advice.
- Skin: remove contaminated clothing and wash with soap and water; do not use solvents on skin.
- Inhalation: move to fresh air; seek medical advice if symptoms persist.
- Ingestion: do not induce vomiting; seek medical advice immediately.
- Clean tools and equipment immediately with epoxy thinner.

The information in this datasheet is based on laboratory tests and practical experience and is given in good faith. Users should verify product suitability for their specific application. O MIX reserves the right to update this information without prior notice.

Construction Chemicals

O-Guard EP Data Sheet

Acid Lock Pro — Submittal Document

Construction Chemicals

Product Datasheet
Edition: 01 | Date: Nov 2026
Protective Coating

O-Guard EP

Solvent-Free Polyamine Epoxy Lining for Potable Water Tanks



Product Description

O-Guard EP is a solvent-free, polyamine-cured epoxy coating for lining potable water tanks and other concrete and steel structures. It is suitable for contact with drinking water and food, resists chemicals and corrosive vapours, and gives a glossy, easy-to-clean surface. An anti-slip finish is optional.

Uses

- Potable water tanks and reservoirs.
- Chemical and wastewater tanks.
- Industrial concrete and steel tanks.
- Car parks and bridge decks.
- Pharmaceutical and textile plants, basements and power stations.

Advantages

- Suitable for potable water contact.
- Solvent-free, 100 % solids.
- Resists chemicals and corrosive vapours.
- Glossy, easy to clean.
- Can be used in lamination systems.

Application

1. **Surface Preparation**
   Concrete ≥ 25 N/mm², pull-off ≥ 1.5 N/mm², ≥ 28 days, moisture < 4 %; prime with O-Prime ST.
2. **Mixing**
   Add Part B to Part A (200 : 30 by weight) and mix 2 – 3 min with a slow-speed mixer.
3. **Application**
   Apply by roller or airless spray at 0.25 – 0.30 kg/m² per coat; second coat within 48 hours.

Consumption

0.25 – 0.30 kg/m²
per coat (approx. 200 µm)
Two coats for tank linings.

Packaging

5 kg sets: Part A 4.35 kg in pail + Part B 0.65 kg in jerrycan.

Storage & Shelf Life

12 months in original, unopened packaging. Store dry at +5 °C to +35 °C, away from direct sunlight.

Technical Data

Typical values at 25 °C

Property	Typical Value	Test Method
Mixing ratio (A : B)	200 : 30 by weight — pre-weighed sets, mix as recommended	—
Specific gravity	1.57	—
Solids content	100 %	—
Flash point	145 °C	—
Pot life	40 min	—
Recoat	24 hours (max. 48 hours)	—
Full cure	7 days	—
Heat resistance	up to 80 °C	—
Colours	On request	—

Consumption

Layer	Product	Consumption
Primer	O-Prime ST	0.18 – 0.25 kg/m²
Body coat	O-Guard EP	0.25 – 0.30 kg/m²
Top coat	O-Guard EP	0.25 – 0.30 kg/m²

Consumption is theoretical and varies with substrate porosity, profile and application method.

Application Conditions

- Ambient and substrate temperature: +10 °C to +35 °C.
- Substrate at least 3 °C above dew point.
- Relative humidity: max. 85 %.
- Concrete ≥ 25 N/mm², pull-off ≥ 1.5 N/mm², ≥ 28 days, moisture < 4 %.

Application Notes

- Mix complete sets.
- Apply the second coat within 48 hours.
- Allow 7 days full cure and wash the tank with clean water before filling with potable water.
- Broadcast fine quartz sand on floors where anti-slip is required.

Health & Safety

- Wear chemical-resistant gloves, safety goggles and overalls.
- Uncured resin may cause skin sensitisation; avoid skin and eye contact.
- Ensure good ventilation in enclosed areas.

First Aid & Cleaning

- Eyes: rinse immediately with plenty of clean water for at least 15 minutes and seek medical advice.
- Skin: remove contaminated clothing and wash with soap and water; do not use solvents on skin.
- Inhalation: move to fresh air; seek medical advice if symptoms persist.
- Ingestion: do not induce vomiting; seek medical advice immediately.
- Clean tools with the recommended thinner before the material cures.

Construction Chemicals

Mixcoat Novolac Data Sheet

Acid Lock Pro — Submittal Document

Construction Chemicals

Product Datasheet
Edition: 01 | Date: Nov 2026
Protective Coating

Mixcoat Novolac

Solvent-Free Novolac Epoxy Coating
for Chemical-Resistant Floors and Linings



Product Description

Mixcoat Novolac is a two-component, solvent-free, low-viscosity novolac epoxy coating for aggressive chemical environments. It gives a durable, chemical-resistant and slip-resistant finish on prepared concrete and steel, and can also be used as a binder in resin mortar and slurry systems.

Uses

- Heavy-duty coating for dairies.
- Food processing and beverage plants.
- Hospitals and pharmaceutical industry.
- Chemical industry and sugar refineries.
- Power stations and battery rooms.
- Heavy engineering workshops.
- Internal protection of concrete tanks containing chemicals.
- Sewage and wastewater treatment plants and liquid containment areas.

Advantages

- Solvent-free — no fire risk, no shrinkage on cure.
- Excellent adhesion to concrete and steel.
- Anti-slip, anti-skid finish option.
- High mechanical strength.
- High resistance to abrasion.
- High chemical resistance.

Application

1. **Surface Preparation**
   Concrete ≥ 28 days old, sound and dry (< 4 % moisture). Remove laitance and old coatings mechanically.
2. **Priming**
   Apply epoxy primer at 0.15 – 0.20 kg/m² to seal hairline cracks and pores. Allow to dry.
3. **Top Coat**
   Mix full A + B kit (2:1 by volume) for 3 min. Apply 2 coats by roller, brush or airless spray.

Consumption

0.50 – 0.60 kg/m² (2 coats, smooth)
Textured 0.8 – 1.0 · Anti-slip 1.6 – 2.0 kg/m²
Full system table on page 2.

Packaging

5 kg and 20 kg sets: Part A in pail + Part B in jerrycan.

Storage & Shelf Life

12 months in original, unopened packaging. Store dry and covered at +10 °C to +30 °C, away from heat, sunlight and frost.

Technical Data

Typical values at 25 °C

Property	Typical Value	Test Method
Mixing ratio (A : B)	2 : 1 by volume — pre-weighed sets, mix full units as recommended	—
Colour	Natural, white, grey; other colours on request	—
Mixed density	1.5 ± 0.1 g/cm³	ASTM D1475
Volume solids	> 98 %	—
Pot life	30 – 40 min	—
Touch dry	6 – 8 hours	—
Recoat interval	Min. 16 hours / max. 48 hours	—
Initial cure	24 hours	—
Full cure	7 days	—
Compressive strength	> 75 N/mm²	ASTM D695
Flexural strength	> 50 N/mm²	ASTM D790
Tensile strength	> 30 N/mm²	ASTM D638
Pull-off adhesion to concrete	> 2.5 N/mm² (concrete failure)	ASTM D4541
Abrasion resistance (CS-17, 1000 g, 1000 cycles)	55 mg loss	ASTM D4060
Hardness	≥ 80 Shore D	ASTM D2240
Dry heat resistance	Up to +120 °C	—

Consumption

System	Coats	Consumption	DFT
Primer (epoxy primer)	1	0.15 – 0.20 kg/m²	—
Smooth finish	2	0.50 – 0.60 kg/m²	0.3 – 0.4 mm
Textured finish	2	0.80 – 1.00 kg/m²	0.5 – 0.6 mm
Anti-slip finish (quartz broadcast)	2	1.60 – 2.00 kg/m²	1.0 – 3.0 mm (incl. quartz)

Consumption is theoretical and varies with substrate porosity, profile and application method.

Application Conditions

- Ambient and substrate: +10 °C to +35 °C.
- Substrate at least 3 °C above dew point.
- Relative humidity: max. 85 %.
- Substrate moisture: < 4 %.
- Full chemical resistance: 7 days at 25 °C (10 days at 15 °C).

Application Notes

- Stir Part A, add all of Part B, mix at 300–400 rpm.
- Pour in a line and spread with a nap-shed resistant roller; work continuously.
- If the recoat window is missed: solvent wipe, abrade, solvent wipe.
- Broadcast aggregate within 15 minutes if anti-slip is required.
- Do not thin. Discard material that starts to gel.

Chemical Resistance

Reagent	Rating	Reagent	Rating
Acetic Acid 20%	3	Isophorone	5
Acetone	3	Iso-propanol	5
Ammonia 40%	5	Jet Fuel	3
Benzene	3	Kerosene	5
N-Butanol	5	Lactic Acid	5
N-Butyl Acetate	5	Linseed Oil	5
Calcium Hydroxide 30%	5	Methanol	5
Castor Oil	5	Methylene Chloride	0
Chlorinated Paraffin	5	Methyl Ethyl Ketone (MEK)	3
Chloroform	3	Methyl Isobutyl Ketone (MIBK)	3
Citric Acid 30%	5	Milk	5
Crude Oil	5	Mineral Oils	5
Cyclohexanone	5	Naphtha	5
Deionised / Distilled Water	5	Nitric Acid 10%	5
Diacetone Alcohol	5	Nitric Acid 30%	3
Diesel Oil	5	Nitric Acid 69%	0
Di-isobutyl Ketone	5	Nonyl Phenol	5
Dioxane	3	Phenol	5
Dipentene	5	Phosphoric Acid 10%	5
Epichlorohydrin	1	Phosphoric Acid 20%	5
Ethyl Acetate	5	Phosphoric Acid 50%	3
Ethyl Benzene	3	Potassium Hydroxide	5
Ethylene Glycol	5	Sea Water	5
Ethylene Glycol Monoethyl Ether	5	Sodium Hydroxide	5
Formaldehyde	5	Styrene	3
Formic Acid	5	Sugar Solution 30%	5
Furfural	3	Sulphuric Acid 10%	5
Glycerol	5	Sulphuric Acid 50%	3
Hydrazine	3	Sulphuric Acid 98%	0
Hydrochloric Acid 35%	3	Toluene	5
Hydrogen Peroxide	5	Toluene Diisocyanate	5
Hydrogen Sulphide	3	White Spirit	5
Iso-butanol	5	Xylene	5
Iso-butyl Acetate	5		

Rating after 7 days cure at 25 °C: 5 = excellent (long-term) 3 = medium term (1 month) 1 = short term (24 h) 0 = not resistant

Health & Safety

- Wear nitrile gloves, goggles and overalls; use an organic-vapour mask when spraying.
- Uncured epoxy may cause skin sensitisation.
- Ensure good ventilation in confined spaces.

First Aid & Cleaning

- Eyes: rinse with water for 15 minutes and seek medical advice.
- Skin: wash with soap and water.
- Clean tools with epoxy thinner before the material cures; cured material can only be removed mechanically.

Construction Chemicals

Test Reports

Acid Lock Pro — Submittal Document

To be attached: laboratory test reports supporting the values in the Technical Data Sheets.

Construction Chemicals

Approvals & Certificates

Acid Lock Pro — Submittal Document

To be attached: approvals and certificates, where available.