Construction Chemicals

SUBMITTAL DOCUMENT

# O MIX MicroArt HD-Walls

Micro-Cement
System for Walls & Columns




**Decorative**
Walls & columns

**Thin**
Fine finish

**Protected**
PU top coat

**Seamless**
No joints

| | |
|---|---|
| **Project** | |
| **Main Contractor** | |
| **Consultant** | |
| **Submittal No. / Rev.** | 00 |
| **Date** | Nov 2026 |

Construction Chemicals

# Contents


1. System Method Statement 3

2. TDS — Bondmix WB 11

3. TDS — Micromix Deco 2 14

4. TDS — Decora PU 17

5. Test Reports 20

6. Approvals & Certificates 21

METHOD STATEMENT

# O MIX MicroArt HD-Walls — Micro-Cement System for Walls & Columns

| | | | |
|---|---|---|---|
| **Project Name** | | **Document No.** | OMX-SMS-16 |
| **Main Contractor** | | **Revision** | 01 |
| **Consultant** | | **Date of Issue** | Nov 2026 |
| **System** | O MIX MicroArt HD-Walls | **Status** | For Approval |

## 1. Purpose

This method statement defines the sequence, resources, inspection and test plan and safety measures for the installation of the O MIX MicroArt HD-Walls system on site. It describes how each layer of the system is prepared, mixed, applied, inspected and protected so that the completed system achieves the performance stated in the O MIX Technical Data Sheets of its components.

## 2. Scope of Work

O MIX MicroArt HD-Walls is a thin decorative micro-cement system for interior walls and columns: a water-based bonding primer, fine micro-cement finishing layers, an intermediate water-based epoxy sealer and a clear matt PU top coat.

- Substrate inspection, testing and acceptance.
- Surface preparation and repair of defects.
- Stage 1: Primer / bonding coat — Bondmix WB.
- Stage 2: Finish layers — Micromix Deco 2.
- Stage 3: Intermediate sealer — Bondmix WB.
- Stage 4: Clear matt top coat — Decora PU.
- Curing, protection, final testing and handover.

### 2.1 System build-up

| Stage | Product | Function | Consumption |
|---|---|---|---|
| 1 | Bondmix WB | Primer / bonding coat | 0.2 kg/m² |
| 2 | Micromix Deco 2 | Finish layers | approx. 1 kg/m² |
| 3 | Bondmix WB | Intermediate sealer | 0.2 kg/m² |
| 4 | Decora PU | Clear matt top coat | 0.25 kg/m² |

### 2.2 Typical areas of use

- Interior walls.
- Columns.
- Feature walls in commercial and residential interiors.

## 3. Definitions

| Term | Meaning |
|---|---|
| **System** | All layers of the build-up applied in the stated sequence. |
| **Hold point** | Stage at which work stops until QA/QC (and the consultant, where required) approve. |
| **Recoat window** | Minimum and maximum time between two layers for proper inter-layer bonding. |
| **Dew point** | Temperature at which moisture condenses; the substrate must be at least 3 °C above it. |
| **Mock-up / trial area** | Area applied before the main works to approve materials, method and appearance. |
| **Pot life** | Time a mixed multi-component material remains workable. |

## 4. Roles & Responsibilities

| Role | Responsibility |
|---|---|
| **Project Manager** | Planning, resources, approvals and coordination with the consultant and main contractor. |
| **Site Engineer** | Daily supervision; confirms substrate readiness, climate, mixing, consumption and recoat windows; keeps daily records. |
| **QA/QC Inspector** | Carries out tests at each hold point, records results and signs the inspection checklist. |
| **HSE Officer** | Toolbox talks, PPE, ventilation, safe access and storage; stops unsafe work. |
| **Applicator Foreman** | Leads the application team and follows this method statement; reports deviations. |
| **O MIX Technical Representative** | Technical support, site visits and advice on product use when requested. |

## 5. Materials

| Product | Description | Packaging |
|---|---|---|
| **Bondmix WB** | Water-Based Two-Component Epoxy Primer & Bonding Coat | 10 kg sets (Part A 2 kg + Part B 8 kg) and 20 kg sets (Part A 4 kg + Part B 16 kg). |
| **Micromix Deco 2** | Micro-Cement Fine Finish Decorative Top Layer | 25 kg bags. |
| **Decora PU** | Clear Matt Polyurethane Top Coat for Decorative Concrete | 5 L and 20 L sets (Part A + Part B) in metal containers. |

### 5.1 Key product data

| Product | Mixing ratio | Pot life / working time | Recoat / drying |
|---|---|---|---|
| **Bondmix WB** | 1 : 4 by weight — pre-weighed sets, mix as recommended | 1 – 2 hours | 4 – 6 hours |
| **Micromix Deco 2** | Water / powder 0.30 – 0.33 | 15 – 20 minutes | approx. 2 hours |
| **Decora PU** | 5 : 1 by weight | 2 hours | 4 hours to 10 days |

## 6. Tools & Equipment

- Diamond grinder and/or shot blaster with dust extraction; industrial vacuum
- Slow-speed drill mixer (300 – 500 rpm) with spiral paddle
- Rollers, brushes, squeegees, notched trowels and steel trowels as required by each stage
- Scales and measuring containers for part mixing (where permitted)
- Thermo-hygrometer, surface thermometer and dew-point calculator
- Moisture meter and plastic sheets for moisture testing
- Masking tape, protective sheeting, barriers and warning signs
- Lighting and extension cables with residual current protection
- Stainless-steel and flexible trowels
- Orbital sander with 120 – 220 grit discs

### 6.1 Personal protective equipment

- Safety shoes, helmet and high-visibility vest
- Chemical-resistant gloves (nitrile) and safety goggles
- Coveralls with long sleeves
- Dust masks (P2) during grinding and powder mixing
- Respirators with organic vapour cartridges for solvent-containing products and confined spaces
- Knee pads for floor work

## 7. Storage & Handling

- Store all products in original, unopened packaging in a dry, shaded and ventilated store at the temperatures stated in each TDS.
- Keep Part A, Part B (and Part C) of each kit together; do not mix components from different batches.
- Protect liquids from frost and direct sun, and powders from moisture.
- Store solvent-containing products away from heat, sparks and ignition sources.
- Use materials on a first-in, first-out basis and record batch numbers for each area.
- Condition materials to +15 °C to +25 °C for 24 hours before use in hot or cold weather.

## 8. Pre-Start Requirements

- Approved material submittal, this method statement and the inspection and test plan.
- Approved drawings showing areas, joints, upstands, drains and details.
- Work area handed over clean, free of other trades, with safe access, lighting and power.
- Mock-up / trial area executed and approved for system, colour and finish.
- Toolbox talk held with the team on this method statement and HSE measures.
- Climate monitoring equipment calibrated and available.

## 9. Substrate Inspection & Acceptance (Hold Point)

| Check | Acceptance criteria | Method |
|---|---|---|
| **Concrete age** | ≥ 28 days (cement-based substrates) | Site records |
| **Compressive strength** | ≥ 25 N/mm² | Rebound hammer (ASTM C805) or cores |
| **Surface tensile (pull-off) strength** | ≥ 1.5 N/mm² | Pull-off test ASTM D7234 |
| **Moisture content** | < 4 % (no moisture under plastic sheet after 16 h) | Moisture meter; plastic sheet test ASTM D4263 |
| **Surface profile** | CSP 2 – 3 (primers / thin coats), CSP 3 – 5 (self-levelling / thick layers) | ICRI 310.2R comparator chips |
| **Flatness** | As per project specification | 3 m straight edge |
| **Climate** | Substrate ≥ 3 °C above dew point; RH ≤ 85 % | ISO 8502-4 / thermo-hygrometer |

## 10. Surface Preparation

1. Remove laitance, curing compounds, oil, paint and loose material by shot blasting or diamond grinding to the required profile.
2. Open cracks to a V-groove and remove dust; repair holes, voids and spalls.
3. Grind high spots and remove sharp edges; form 45° coves at wall / floor junctions where required.
4. Vacuum all dust with an industrial vacuum immediately before priming.
5. Mask and protect adjacent surfaces, drains and fixtures.
6. Record substrate test results and obtain QA/QC approval before priming (hold point).

## 11. Application Sequence

Apply the system stage by stage in the order below. Each stage must be inspected and approved before the next stage starts, and the next stage must be applied within the recoat window stated.

### 11.1 Stage 1 — Primer / bonding coat: Bondmix WB

Consumption: 0.2 kg/m². Time before next stage: 4 – 6 h.

1. Check batch numbers and condition the kit to +15 °C to +25 °C.
2. Pour the complete Part A into Part B (1 : 4 by weight).
3. Mix 2 – 3 minutes with a slow-speed mixer until uniform.
4. Mix complete sets only.
5. Apply by roller or brush at 0.15 – 0.30 kg/m² without puddles.
6. Apply a second coat on very porous substrates.
7. Apply the next system layer after 4 – 6 hours and within 24 hours.

### 11.2 Stage 2 — Finish layers: Micromix Deco 2

Consumption: approx. 1 kg/m². Time before next stage: 24 h between layers, sanding.

1. Pour the measured clean water into the bucket.
2. Add the powder gradually while mixing at low speed.
3. Mix 3 minutes to a smooth, lump-free paste; rest 2 minutes and remix briefly.
4. Apply the first finishing layer at 0.5 – 1 mm with a stainless-steel trowel.
5. After drying, sand lightly and remove dust.
6. Apply the second finishing layer after 24 hours and burnish as required.
7. Sand lightly and apply Decora PU top coat.

### 11.3 Stage 3 — Intermediate sealer: Bondmix WB

Consumption: 0.2 kg/m². Time before next stage: 4 – 6 h.

1. Check batch numbers and condition the kit to +15 °C to +25 °C.
2. Pour the complete Part A into Part B (1 : 4 by weight).
3. Mix 2 – 3 minutes with a slow-speed mixer until uniform.
4. Mix complete sets only.
5. Apply by roller or brush at 0.15 – 0.30 kg/m² without puddles.
6. Apply a second coat on very porous substrates.
7. Apply the next system layer after 4 – 6 hours and within 24 hours.

### 11.4 Stage 4 — Clear matt top coat: Decora PU

Consumption: 0.25 kg/m². Time before next stage: 12 – 24 h between coats.

1. Check batch numbers and condition the kit to +15 °C to +25 °C.
2. Stir Part A.
3. Add Part B to Part A at 5 : 1 by weight.
4. Mix 2 – 3 minutes with a slow-speed mixer.
5. Thin up to 20 % only where required.
6. Apply the first coat by roller or spray in a thin, even layer.
7. Avoid puddles and lap marks; keep a wet edge.
8. Apply the second coat after 12 – 24 hours (minimum 4 hours, maximum 10 days).
9. Apply further coats as specified.

## 12. Hold Points & Recoat Windows

| Stage | Before starting | Waiting time before next stage | Approved by |
|---|---|---|---|
| **1. Bondmix WB** | Substrate accepted (Section 9) | 4 – 6 h | QA/QC |
| **2. Micromix Deco 2** | Previous stage inspected and approved | 24 h between layers, sanding | QA/QC |

| Stage | Before starting | Waiting time before next stage | Approved by |
|---|---|---|---|
| **3. Bondmix WB** | Previous stage inspected and approved | 4 – 6 h | QA/QC |
| **4. Decora PU** | Previous stage inspected and approved | 12 – 24 h between coats | QA/QC |

## 13. Curing, Protection & Return to Service

- Protect each layer from rain, dew, dust, water and traffic until it has cured.
- Barricade the area and display warning signs during application and curing.
- Keep ventilation running in enclosed areas until full cure.
- Avoid water and heavy traffic for 7 days after the top coat; maintain with neutral cleaners only.

## 14. Quality Control & Inspection Test Plan

| Activity | Inspection / Test | Frequency | Record |
|---|---|---|---|
| **Material receipt** | Product, batch, expiry, packaging condition | Each delivery | Material inspection report |
| **Climate** | Air / substrate temperature, RH, dew point (ISO 8502-4) | Start of shift and every 4 h | Daily climate log |
| **Substrate** | Strength, pull-off (ASTM D7234), moisture (ASTM D4263) | Each area (hold point) | Inspection request |
| **Mixing** | Complete kits, ratio, mixing time | Each mix | Daily record |
| **Consumption** | Material used vs area | Each stage | Daily record |
| **Final inspection** | Appearance, continuity, finish, details | Each area | Handover checklist |

## 15. Defects & Remedies

| Defect | Likely cause | Remedy |
|---|---|---|
| **Poor adhesion / delamination** | Weak, dusty or damp substrate; recoat window exceeded | Remove, re-prepare and reapply; abrade and re-prime if window exceeded |
| **Pinholes / bubbles** | Outgassing; air trapped in mixing; thick application | Seal porous areas; mix slowly; spiked roller; sand and recoat |
| **Blushing / tacky surface** | High humidity or low temperature during cure | Wash, abrade and recoat in suitable conditions |
| **Soft spots** | Incorrect ratio or incomplete mixing | Remove and reapply with complete kits |
| **Cracking of cementitious layers** | Rapid drying; layer too thick | Protect from sun and wind; apply thinner layers |
| **Colour / shade variation** | Different batches; uneven application | Use one batch per area; apply additional coat |

## 16. Health, Safety & Environment

| Hazard | Control measures |
|---|---|
| **Skin / eye contact with resins and cement** | Gloves, goggles, coveralls; eye-wash station |
| **Inhalation of dust and vapours** | Dust extraction; ventilation; masks / respirators |
| **Fire (solvent vapours)** | No smoking or hot work; fire extinguisher at the work area |
| **Slips and trips** | Housekeeping; barricades and warning signs |
| **Manual handling** | Correct lifting; mechanical aids for drums and pails |
| **Electrical equipment** | Inspected tools; protected cables with RCD |

- Read the Safety Data Sheet of each product before use.
- Keep first-aid kit and eye-wash on site; follow the first-aid measures in each TDS.

### 16.1 Waste & environment

- Collect empty containers and residues in designated bins.
- Allow small quantities of mixed resin to cure before disposal; dispose of according to local regulations.
- Do not discharge materials or washings into drains or soil.

## 17. Cleaning

- Clean tools of water-based and cementitious products with water immediately after use.
- Clean tools of epoxy and PU products with the recommended thinner before the material cures.
- Cured material can only be removed mechanically.

## 18. Limitations

- Do not apply outside the temperature and humidity limits stated in the TDS of each product.
- Do not apply on wet surfaces or when rain or dew is expected before the layer has cured.
- Do not mix or substitute products from other systems without written approval from O MIX.
- Any deviation from this method statement must be approved by the Site Engineer and the consultant.

## 19. Maintenance

- Clean with neutral pH cleaners; avoid abrasive pads and acids.
- Re-apply Decora PU in high-traffic areas as needed.
- Use felt pads under furniture legs.

## Appendix A — Inspection Checklist

| Inspection Item | Result | Remarks |
|---|---|---|
| Approved submittal and method statement on site | ☐ Yes ☐ No | |
| Mock-up approved | ☐ Yes ☐ No | |
| Substrate tests passed (strength, pull-off, moisture) | ☐ Yes ☐ No | |
| Surface preparation approved | ☐ Yes ☐ No | |
| Stage 1 — Bondmix WB applied and approved | ☐ Yes ☐ No | |
| Stage 2 — Micromix Deco 2 applied and approved | ☐ Yes ☐ No | |
| Stage 3 — Bondmix WB applied and approved | ☐ Yes ☐ No | |
| Stage 4 — Decora PU applied and approved | ☐ Yes ☐ No | |
| Recoat windows respected | ☐ Yes ☐ No | |
| Final tests passed | ☐ Yes ☐ No | |
| Area protected and handed over | ☐ Yes ☐ No | |

| Inspected by | Signature | Date |
|---|---|---|
| | | |

## Appendix B — Daily Application Record

| Date | Area / zone | Stage | Batch No. | Qty used | Air / substrate °C | RH % | Sign |
|---|---|---|---|---|---|---|---|
| | | | | | | | |
| | | | | | | | |
| | | | | | | | |
| | | | | | | | |
| | | | | | | | |
| | | | | | | | |
| | | | | | | | |
| | | | | | | | |

Construction Chemicals

# Bondmix WB Data Sheet

O MIX MicroArt HD-Walls — Submittal Document

Construction Chemicals

**Product Datasheet**
Edition: 01 | Date: Nov 2026
Sport Court Systems

# Bondmix WB

Water-Based Two-Component
Epoxy Primer & Bonding Coat




## Product Description

Bondmix WB is a two-component, water-based epoxy primer for concrete and cementitious substrates, indoors and outdoors. It penetrates and seals the surface, reduces peeling and improves the adhesion of acrylic and polyurethane sport-court systems, micro-cement and waterproofing coatings. It is milky when applied and dries clear.

## Uses

- Primer for acrylic and PU sport-court systems.
- Primer and bonding coat for Micromix Deco micro-cement.
- Primer for Roofguard AC waterproofing systems.
- Sealing of porous concrete and screeds.
- Interior and exterior use.

## Advantages

- Water-based, low VOC, low odour.
- Penetrates and seals porous substrates.
- Improves adhesion of following layers.
- Reduces peeling and delamination.
- Dries clear.

## Application

1. **Surface Preparation**
   Clean, sound, dust-free concrete; damp but without standing water is acceptable.
2. **Mixing**
   Add Part A to Part B (1 : 4 by weight) and mix 2 – 3 min with a slow-speed mixer.
3. **Application**
   Apply by roller or brush at 0.15 – 0.30 kg/m²; next layer after 4 – 6 hours.

## Consumption

**0.15 – 0.30 kg/m²**
per coat, depending on porosity
0.2 kg/m² in O MIX court, roof and micro-cement systems.

## Packaging

10 kg sets (Part A 2 kg + Part B 8 kg) and 20 kg sets (Part A 4 kg + Part B 16 kg).

## Storage & Shelf Life

12 months in original, unopened packaging. Store dry at +5 °C to +35 °C, away from direct sunlight. Protect from frost.

## Technical Data

*Typical values at 25 °C*

| Property | Typical Value | Test Method |
|---|---|---|
| **Mixing ratio (A : B)** | 1 : 4 by weight — pre-weighed sets, mix as recommended | — |
| **Appearance** | Milky; dries clear | — |
| **Density** | 1.05 – 1.15 kg/L | — |
| **Solids content** | 30 – 55 % | — |
| **Viscosity** | 500 – 1500 mPa·s | — |
| **Pot life** | 1 – 2 hours | — |
| **Touch dry** | 1 – 2 hours | — |
| **Recoat interval** | 4 – 6 hours | — |
| **Full cure** | 24 hours | — |
| **Coverage** | approx. 6 – 8 m²/L | — |
| **Application temperature** | +10 °C to +35 °C | — |

## Consumption

| Use | Consumption |
|---|---|
| **Dense concrete** | 0.15 – 0.20 kg/m² |
| **Porous concrete / screed** | 0.20 – 0.30 kg/m² |
| **O MIX court, roof and micro-cement systems** | 0.2 kg/m² |

*Consumption is theoretical and varies with substrate porosity, profile and application method.*

## Application Conditions

- Ambient and substrate temperature: +10 °C to +35 °C.
- Relative humidity: max. 85 %.
- Substrate clean, sound; damp is acceptable, no standing water.
- Concrete at least 28 days old (asphalt not to be primed).

## Application Notes

- Mix complete sets at 1 : 4 by weight.
- Do not leave puddles; apply a uniform film.
- Apply the next layer after 4 – 6 hours and within 24 hours.
- Clean tools with water before the material cures.

## Health & Safety

- Wear gloves and safety goggles.
- Uncured epoxy may cause skin sensitisation; avoid skin and eye contact.
- Ensure ventilation in enclosed areas.

## First Aid & Cleaning

- Eyes: rinse immediately with plenty of clean water for at least 15 minutes and seek medical advice.
- Skin: remove contaminated clothing and wash with soap and water; do not use solvents on skin.
- Inhalation: move to fresh air; seek medical advice if symptoms persist.
- Ingestion: do not induce vomiting; seek medical advice immediately.
- Clean tools with water immediately after use.

Construction Chemicals

# Micromix Deco 2 Data Sheet

O MIX MicroArt HD-Walls — Submittal Document

Construction Chemicals

**Product Datasheet**
Edition: 01 | Date: Nov 2026
**Concrete Admixture**




# Micromix Deco 2

Micro-Cement Fine Finish
Decorative Top Layer

## Product Description

Micromix Deco 2 is a very fine cementitious micro-cement finishing layer. Applied in layers of 0.5 – 1 mm over Micromix Deco 1, it gives a smooth, decorative, seamless finish that is protected with Decora PU.

## Uses

- Decorative floors and walls.
- Bathrooms, kitchens and wet areas.
- Showrooms, offices and residential interiors.
- Columns, stairs and furniture.

## Advantages

- Smooth, decorative seamless finish.
- Compressive strength ≥ 45 MPa.
- Flexural strength ≥ 8 MPa.
- Thin layers: 0.5 – 1 mm.
- Grey or white base for colouring.

## Application

1. **Surface Preparation**
   Apply over cured, sanded Micromix Deco 1 base.
2. **Mixing**
   Mix powder with water at a water/powder ratio of 0.30 – 0.33.
3. **Application**
   Apply 0.5 – 1 mm per layer with a steel trowel; sand lightly between layers; seal with Decora PU.

## Consumption

**1.7 – 1.8 kg/m² per mm**
in 2 thin layers
Approx. 1 kg/m² in the Micromix Deco systems.

## Packaging

25 kg bags.

## Storage & Shelf Life

12 months in original, unopened bags. Store dry, off the ground, protected from moisture.

## Technical Data

*Typical values at 25 °C*

| Property | Typical Value | Test Method |
|---|---|---|
| **Form** | Fine cementitious powder | — |
| **Colour** | Grey / white | — |
| **Water / powder ratio** | 0.30 – 0.33 | — |
| **Layer thickness** | 0.5 – 1 mm | — |
| **Working time** | 15 – 20 minutes | — |
| **Drying time** | approx. 2 hours | — |
| **Next layer** | after 24 hours | — |
| **Flexural strength** | ≥ 8 MPa | — |
| **Compressive strength** | ≥ 45 MPa | — |
| **Density** | approx. 1.7 kg/L | — |

## Consumption

| Layer | Consumption |
|---|---|
| **Per mm of thickness** | 1.7 – 1.8 kg/m² |
| **Finish layers in Micromix Deco systems** | approx. 1 kg/m² |

*Consumption is theoretical and varies with substrate porosity, profile and application method.*

## Application Conditions

- Ambient and substrate temperature: +10 °C to +35 °C.
- Substrate sound, clean, dry and stable.
- Protect from direct sun, wind and rapid drying.
- Do not apply on substrates with rising damp.

## Application Notes

- Water / powder ratio 0.30 – 0.33 (7.5 – 8.3 L per 25 kg bag).
- Apply thin layers with a stainless-steel trowel.
- Sand lightly between layers (180 – 220 grit).
- Seal with Decora PU after drying.

## Health & Safety

- Wear gloves, safety goggles and a dust mask when mixing.
- Contains cement; alkaline when wet. Avoid skin and eye contact.
- Use dust extraction when sanding.

## First Aid & Cleaning

- Eyes: rinse immediately with plenty of clean water for at least 15 minutes and seek medical advice.
- Skin: wash with soap and water; cement is alkaline when wet.
- Inhalation of dust: move to fresh air.
- Ingestion: rinse mouth and seek medical advice.
- Clean tools with water immediately after use.

*The information in this datasheet is based on laboratory tests and practical experience and is given in good faith. Users should verify product suitability for their specific application. O MIX reserves the right to update this information without prior notice.*

Construction Chemicals

# Decora PU Data Sheet

O MIX MicroArt HD-Walls — Submittal Document

Construction Chemicals

**Product Datasheet**
Edition: 01 | Date: Nov 2026
Decorative Paints

# Decora PU

Clear Matt Polyurethane
Top Coat for Decorative Concrete




## Product Description

Decora PU is a two-component, clear, matt acrylic polyurethane top coat for decorative concrete and cementitious finishes. It does not yellow, protects against fungi and bacteria and resists dilute acids and alkalis. It is the protective top coat of the O MIX micro-cement systems.

## Uses

- Concrete and plastered surfaces.
- Polished and decorative concrete.
- Micro-cement floors and walls (Micromix Deco systems).
- Glow-stone and cementitious quartz floors.
- Interior and exterior decorative surfaces.

## Advantages

- Non-yellowing, UV stable.
- Protects against fungi and bacteria.
- Resists dilute acids and alkalis.
- Clear matt finish keeps the natural look.
- Recoat after 4 hours.

## Application

1. **Surface Preparation**
   Clean, dry, sound surface free of dust and grease.
2. **Mixing**
   Add Part B to Part A (5 : 1 by weight) and mix thoroughly; thin up to 20 % if required.
3. **Application**
   Apply by roller or spray in thin coats, 12 – 24 hours between coats.

## Consumption

**approx. 7 m²/L**
at 50 µm DFT per coat
0.25 kg/m² as top coat in micro-cement systems.

## Packaging

5 L and 20 L sets (Part A + Part B) in metal containers.

## Storage & Shelf Life

12 months in original, unopened packaging. Store dry at +5 °C to +35 °C, away from heat, sparks and direct sunlight.

## Technical Data

*Typical values at 25 °C*

| Property | Typical Value | Test Method |
|---|---|---|
| **Mixing ratio (A : B)** | 5 : 1 by weight | — |
| **Finish** | Clear matt | — |
| **Solids content** | 35 % | — |
| **Recommended DFT** | 25 – 75 µm | — |
| **Theoretical coverage** | approx. 7 m²/L at 50 µm | — |
| **Surface dry** | 30 minutes | — |
| **Recoat interval** | 4 hours to 10 days | — |
| **Pot life** | 2 hours | — |
| **VOC** | 576 g/L | — |
| **Thinning** | up to 20 % | — |
| **Min. application temperature** | +8 °C | — |

## Consumption

| Use | Consumption |
|---|---|
| **Top coat, 50 µm DFT** | approx. 7 m²/L per coat |
| **Micro-cement systems** | 0.25 kg/m² (total) |

*Consumption is theoretical and varies with substrate porosity, profile and application method.*

## Application Conditions

- Minimum substrate and air temperature: +8 °C.
- Substrate dry and at least 3 °C above dew point.
- Relative humidity: max. 85 %.
- Cementitious substrates fully cured and dry.

## Application Notes

- Mix complete sets at 5 : 1 by weight.
- Thin up to 20 % with the recommended thinner for spray or first coat on porous surfaces.
- Apply in thin, even coats; avoid puddles.
- Allow 12 – 24 hours between coats (minimum 4 hours, maximum 10 days).
- Test on a sample area for appearance before full application.

## Health & Safety

- Solvent-based: flammable. Keep away from heat, sparks and open flames; no smoking.
- Wear chemical-resistant gloves, safety goggles and a respirator with organic vapour cartridges in enclosed spaces.
- Contains isocyanates; may cause sensitisation.
- Ensure good ventilation during application and drying.

## First Aid & Cleaning

- Eyes: rinse immediately with plenty of clean water for at least 15 minutes and seek medical advice.
- Skin: remove contaminated clothing and wash with soap and water; do not use solvents on skin.
- Inhalation: move to fresh air; seek medical advice if symptoms persist.
- Ingestion: do not induce vomiting; seek medical advice immediately.
- Clean tools immediately with PU thinner.

Construction Chemicals

# Test Reports

O MIX MicroArt HD-Walls — Submittal Document

*To be attached: laboratory test reports supporting the values in the Technical Data Sheets.*

Construction Chemicals

# Approvals & Certificates

O MIX MicroArt HD-Walls — Submittal Document

*To be attached: approvals and certificates, where available.*