Construction Chemicals

SUBMITTAL DOCUMENT

O MIX MicroArt

Micro-Cement
Decorative Finish System



Decorative
Seamless finish

4 Layers
Primer – base – finish – seal

Protected
PU top coat

Renovation
Over tiles

Project	
Main Contractor	
Consultant	
Submittal No. / Rev.	00
Date	Nov 2026

Construction Chemicals

Contents

1. System Method Statement 3

2. TDS — Bondmix WB 11

3. TDS — Micromix Deco 1 14

4. TDS — Micromix Deco 2 17

5. TDS — Decora PU 20

6. Test Reports 23

7. Approvals & Certificates 24

METHOD STATEMENT

O MIX MicroArt — Micro-Cement Decorative Finish System

Project Name		**Document No.**	OMX-SMS-15
Main Contractor		**Revision**	01
Consultant		**Date of Issue**	Nov 2026
System	O MIX MicroArt	**Status**	For Approval

1. Purpose

This method statement defines the sequence, resources, inspection and test plan and safety measures for the installation of the O MIX MicroArt system on site. It describes how each layer of the system is prepared, mixed, applied, inspected and protected so that the completed system achieves the performance stated in the O MIX Technical Data Sheets of its components.

2. Scope of Work

O MIX MicroArt is a seamless decorative micro-cement system for floors, walls, columns and stairs in residential, commercial and showroom interiors. It consists of a water-based bonding primer, a micro-cement base coat, a fine micro-cement finish and a clear matt PU top coat.

- Substrate inspection, testing and acceptance.
- Surface preparation and repair of defects.
- Stage 1: Primer / bonding coat — Bondmix WB.
- Stage 2: Base coat — Micromix Deco 1.
- Stage 3: Fine finish coat — Micromix Deco 2.
- Stage 4: Clear matt top coat — Decora PU.
- Curing, protection, final testing and handover.

2.1 System build-up

Stage	Product	Function	Consumption
1	Bondmix WB	Primer / bonding coat	0.2 kg/m²
2	Micromix Deco 1	Base coat	approx. 1 kg/m²
3	Micromix Deco 2	Fine finish coat	approx. 1 kg/m²
4	Decora PU	Clear matt top coat	0.25 kg/m²

2.2 Typical areas of use

- Walls, floors and columns.
- Showrooms and commercial interiors.
- Residential interiors.

- Renovation over tiles and terrazzo.

3. Definitions

Term	Meaning
System	All layers of the build-up applied in the stated sequence.
Hold point	Stage at which work stops until QA/QC (and the consultant, where required) approve.
Recoat window	Minimum and maximum time between two layers for proper inter-layer bonding.
Dew point	Temperature at which moisture condenses; the substrate must be at least 3 °C above it.
Mock-up / trial area	Area applied before the main works to approve materials, method and appearance.
Pot life	Time a mixed multi-component material remains workable.

4. Roles & Responsibilities

Role	Responsibility
Project Manager	Planning, resources, approvals and coordination with the consultant and main contractor.
Site Engineer	Daily supervision; confirms substrate readiness, climate, mixing, consumption and recoat windows; keeps daily records.
QA/QC Inspector	Carries out tests at each hold point, records results and signs the inspection checklist.
HSE Officer	Toolbox talks, PPE, ventilation, safe access and storage; stops unsafe work.
Applicator Foreman	Leads the application team and follows this method statement; reports deviations.
O MIX Technical Representative	Technical support, site visits and advice on product use when requested.

5. Materials

Product	Description	Packaging
Bondmix WB	Water-Based Two-Component Epoxy Primer & Bonding Coat	10 kg sets (Part A 2 kg + Part B 8 kg) and 20 kg sets (Part A 4 kg + Part B 16 kg).
Micromix Deco 1	Micro-Cement Base Coat for Floors & Walls	25 kg bags.
Micromix Deco 2	Micro-Cement Fine Finish Decorative Top Layer	25 kg bags.
Decora PU	Clear Matt Polyurethane Top Coat for Decorative Concrete	5 L and 20 L sets (Part A + Part B) in metal containers.

5.1 Key product data

Product	Mixing ratio	Pot life / working time	Recoat / drying
Bondmix WB	1 : 4 by weight — pre-weighed sets, mix as recommended	1 – 2 hours	4 – 6 hours

Product	Mixing ratio	Pot life / working time	Recoat / drying
Micromix Deco 1	Water / powder 0.28 – 0.32	20 – 30 minutes	approx. 3 hours
Micromix Deco 2	Water / powder 0.30 – 0.33	15 – 20 minutes	approx. 2 hours
Decora PU	5 : 1 by weight	2 hours	4 hours to 10 days

6. Tools & Equipment

- Diamond grinder and/or shot blaster with dust extraction; industrial vacuum
- Slow-speed drill mixer (300 – 500 rpm) with spiral paddle
- Rollers, brushes, squeegees, notched trowels and steel trowels as required by each stage
- Scales and measuring containers for part mixing (where permitted)
- Thermo-hygrometer, surface thermometer and dew-point calculator
- Moisture meter and plastic sheets for moisture testing
- Masking tape, protective sheeting, barriers and warning signs
- Lighting and extension cables with residual current protection
- Stainless-steel and flexible trowels
- Orbital sander with 120 – 220 grit discs

6.1 Personal protective equipment

- Safety shoes, helmet and high-visibility vest
- Chemical-resistant gloves (nitrile) and safety goggles
- Coveralls with long sleeves
- Dust masks (P2) during grinding and powder mixing
- Respirators with organic vapour cartridges for solvent-containing products and confined spaces
- Knee pads for floor work

7. Storage & Handling

- Store all products in original, unopened packaging in a dry, shaded and ventilated store at the temperatures stated in each TDS.
- Keep Part A, Part B (and Part C) of each kit together; do not mix components from different batches.
- Protect liquids from frost and direct sun, and powders from moisture.
- Store solvent-containing products away from heat, sparks and ignition sources.
- Use materials on a first-in, first-out basis and record batch numbers for each area.
- Condition materials to +15 °C to +25 °C for 24 hours before use in hot or cold weather.

8. Pre-Start Requirements

- Approved material submittal, this method statement and the inspection and test plan.
- Approved drawings showing areas, joints, upstands, drains and details.
- Work area handed over clean, free of other trades, with safe access, lighting and power.

- Mock-up / trial area executed and approved for system, colour and finish.
- Toolbox talk held with the team on this method statement and HSE measures.
- Climate monitoring equipment calibrated and available.

9. Substrate Inspection & Acceptance (Hold Point)

Check	Acceptance criteria	Method
Concrete age	≥ 28 days (cement-based substrates)	Site records
Compressive strength	≥ 25 N/mm²	Rebound hammer (ASTM C805) or cores
Surface tensile (pull-off) strength	≥ 1.5 N/mm²	Pull-off test ASTM D7234
Moisture content	< 4 % (no moisture under plastic sheet after 16 h)	Moisture meter; plastic sheet test ASTM D4263
Surface profile	CSP 2 – 3 (primers / thin coats), CSP 3 – 5 (self-levelling / thick layers)	ICRI 310.2R comparator chips
Flatness	As per project specification	3 m straight edge
Climate	Substrate ≥ 3 °C above dew point; RH ≤ 85 %	ISO 8502-4 / thermo-hygrometer

10. Surface Preparation

1. Remove laitance, curing compounds, oil, paint and loose material by shot blasting or diamond grinding to the required profile.
2. Open cracks to a V-groove and remove dust; repair holes, voids and spalls.
3. Grind high spots and remove sharp edges; form 45° coves at wall / floor junctions where required.
4. Vacuum all dust with an industrial vacuum immediately before priming.
5. Mask and protect adjacent surfaces, drains and fixtures.
6. Record substrate test results and obtain QA/QC approval before priming (hold point).

11. Application Sequence

Apply the system stage by stage in the order below. Each stage must be inspected and approved before the next stage starts, and the next stage must be applied within the recoat window stated.

11.1 Stage 1 — Primer / bonding coat: Bondmix WB

Consumption: 0.2 kg/m². Time before next stage: 4 – 6 h.

1. Check batch numbers and condition the kit to +15 °C to +25 °C.
2. Pour the complete Part A into Part B (1 : 4 by weight).
3. Mix 2 – 3 minutes with a slow-speed mixer until uniform.
4. Mix complete sets only.
5. Apply by roller or brush at 0.15 – 0.30 kg/m² without puddles.
6. Apply a second coat on very porous substrates.

7. Apply the next system layer after 4 – 6 hours and within 24 hours.

11.2 Stage 2 — Base coat: Micromix Deco 1

Consumption: approx. 1 kg/m². Time before next stage: 24 h, light sanding.

1. Pour the measured clean water into the bucket.
2. Add the powder gradually while mixing at low speed.
3. Mix 3 minutes to a smooth, lump-free paste; rest 2 minutes and remix briefly.
4. Apply the first layer with a steel trowel at 1 – 2 mm, embedding reinforcement where specified.
5. After 24 hours, lightly sand and remove dust.
6. Apply the second base layer if specified.
7. Proceed with Micromix Deco 2 finishing layers.

11.3 Stage 3 — Fine finish coat: Micromix Deco 2

Consumption: approx. 1 kg/m². Time before next stage: 24 h between layers, sanding.

1. Pour the measured clean water into the bucket.
2. Add the powder gradually while mixing at low speed.
3. Mix 3 minutes to a smooth, lump-free paste; rest 2 minutes and remix briefly.
4. Apply the first finishing layer at 0.5 – 1 mm with a stainless-steel trowel.
5. After drying, sand lightly and remove dust.
6. Apply the second finishing layer after 24 hours and burnish as required.
7. Sand lightly and apply Decora PU top coat.

11.4 Stage 4 — Clear matt top coat: Decora PU

Consumption: 0.25 kg/m². Time before next stage: 12 – 24 h between coats.

1. Check batch numbers and condition the kit to +15 °C to +25 °C.
2. Stir Part A.
3. Add Part B to Part A at 5 : 1 by weight.
4. Mix 2 – 3 minutes with a slow-speed mixer.
5. Thin up to 20 % only where required.
6. Apply the first coat by roller or spray in a thin, even layer.
7. Avoid puddles and lap marks; keep a wet edge.
8. Apply the second coat after 12 – 24 hours (minimum 4 hours, maximum 10 days).
9. Apply further coats as specified.

12. Hold Points & Recoat Windows

Stage	Before starting	Waiting time before next stage	Approved by
1. Bondmix WB	Substrate accepted (Section 9)	4 – 6 h	QA/QC

Stage	Before starting	Waiting time before next stage	Approved by
2. Micromix Deco 1	Previous stage inspected and approved	24 h, light sanding	QA/QC
3. Micromix Deco 2	Previous stage inspected and approved	24 h between layers, sanding	QA/QC
4. Decora PU	Previous stage inspected and approved	12 – 24 h between coats	QA/QC

13. Curing, Protection & Return to Service

- Protect each layer from rain, dew, dust, water and traffic until it has cured.
- Barricade the area and display warning signs during application and curing.
- Keep ventilation running in enclosed areas until full cure.
- Avoid water and heavy traffic for 7 days after the top coat; maintain with neutral cleaners only.

14. Quality Control & Inspection Test Plan

Activity	Inspection / Test	Frequency	Record
Material receipt	Product, batch, expiry, packaging condition	Each delivery	Material inspection report
Climate	Air / substrate temperature, RH, dew point (ISO 8502-4)	Start of shift and every 4 h	Daily climate log
Substrate	Strength, pull-off (ASTM D7234), moisture (ASTM D4263)	Each area (hold point)	Inspection request
Mixing	Complete kits, ratio, mixing time	Each mix	Daily record
Consumption	Material used vs area	Each stage	Daily record
Final inspection	Appearance, continuity, finish, details	Each area	Handover checklist

15. Defects & Remedies

Defect	Likely cause	Remedy
Poor adhesion / delamination	Weak, dusty or damp substrate; recoat window exceeded	Remove, re-prepare and reapply; abrade and re-prime if window exceeded
Pinholes / bubbles	Outgassing; air trapped in mixing; thick application	Seal porous areas; mix slowly; spiked roller; sand and recoat
Blushing / tacky surface	High humidity or low temperature during cure	Wash, abrade and recoat in suitable conditions
Soft spots	Incorrect ratio or incomplete mixing	Remove and reapply with complete kits
Cracking of cementitious layers	Rapid drying; layer too thick	Protect from sun and wind; apply thinner layers
Colour / shade variation	Different batches; uneven application	Use one batch per area; apply additional coat

16. Health, Safety & Environment

Hazard	Control measures
Skin / eye contact with resins and cement	Gloves, goggles, coveralls; eye-wash station
Inhalation of dust and vapours	Dust extraction; ventilation; masks / respirators
Fire (solvent vapours)	No smoking or hot work; fire extinguisher at the work area
Slips and trips	Housekeeping; barricades and warning signs
Manual handling	Correct lifting; mechanical aids for drums and pails
Electrical equipment	Inspected tools; protected cables with RCD

- Read the Safety Data Sheet of each product before use.
- Keep first-aid kit and eye-wash on site; follow the first-aid measures in each TDS.

16.1 Waste & environment

- Collect empty containers and residues in designated bins.
- Allow small quantities of mixed resin to cure before disposal; dispose of according to local regulations.
- Do not discharge materials or washings into drains or soil.

17. Cleaning

- Clean tools of water-based and cementitious products with water immediately after use.
- Clean tools of epoxy and PU products with the recommended thinner before the material cures.
- Cured material can only be removed mechanically.

18. Limitations

- Do not apply outside the temperature and humidity limits stated in the TDS of each product.
- Do not apply on wet surfaces or when rain or dew is expected before the layer has cured.
- Do not mix or substitute products from other systems without written approval from O MIX.
- Any deviation from this method statement must be approved by the Site Engineer and the consultant.

19. Maintenance

- Clean with neutral pH cleaners; avoid abrasive pads and acids.
- Re-apply Decora PU in high-traffic areas as needed.
- Use felt pads under furniture legs.

Appendix A — Inspection Checklist

Inspection Item	Result	Remarks
Approved submittal and method statement on site	☐ Yes ☐ No	
Mock-up approved	☐ Yes ☐ No	
Substrate tests passed (strength, pull-off, moisture)	☐ Yes ☐ No	
Surface preparation approved	☐ Yes ☐ No	
Stage 1 — Bondmix WB applied and approved	☐ Yes ☐ No	
Stage 2 — Micromix Deco 1 applied and approved	☐ Yes ☐ No	
Stage 3 — Micromix Deco 2 applied and approved	☐ Yes ☐ No	
Stage 4 — Decora PU applied and approved	☐ Yes ☐ No	
Recoat windows respected	☐ Yes ☐ No	
Final tests passed	☐ Yes ☐ No	
Area protected and handed over	☐ Yes ☐ No	

Inspected by	Signature	Date

Appendix B — Daily Application Record

Date	Area / zone	Stage	Batch No.	Qty used	Air / substrate °C	RH %	Sign

Construction Chemicals

Bondmix WB Data Sheet

O MIX MicroArt — Submittal Document

Construction Chemicals

Product Datasheet
Edition: 01 | Date: Nov 2026
Sport Court Systems

Bondmix WB

Water-Based Two-Component
Epoxy Primer & Bonding Coat



Product Description

Bondmix WB is a two-component, water-based epoxy primer for concrete and cementitious substrates, indoors and outdoors. It penetrates and seals the surface, reduces peeling and improves the adhesion of acrylic and polyurethane sport-court systems, micro-cement and waterproofing coatings. It is milky when applied and dries clear.

Uses

- Primer for acrylic and PU sport-court systems.
- Primer and bonding coat for Micromix Deco micro-cement.
- Primer for Roofguard AC waterproofing systems.
- Sealing of porous concrete and screeds.
- Interior and exterior use.

Advantages

- Water-based, low VOC, low odour.
- Penetrates and seals porous substrates.
- Improves adhesion of following layers.
- Reduces peeling and delamination.
- Dries clear.

Application

1. **Surface Preparation**
   Clean, sound, dust-free concrete; damp but without standing water is acceptable.
2. **Mixing**
   Add Part A to Part B (1 : 4 by weight) and mix 2 – 3 min with a slow-speed mixer.
3. **Application**
   Apply by roller or brush at 0.15 – 0.30 kg/m²; next layer after 4 – 6 hours.

Consumption

0.15 – 0.30 kg/m²
per coat, depending on porosity
0.2 kg/m² in O MIX court, roof and micro-cement systems.

Packaging

10 kg sets (Part A 2 kg + Part B 8 kg) and 20 kg sets (Part A 4 kg + Part B 16 kg).

Storage & Shelf Life

12 months in original, unopened packaging. Store dry at +5 °C to +35 °C, away from direct sunlight. Protect from frost.

Technical Data

Typical values at 25 °C

Property	Typical Value	Test Method
Mixing ratio (A : B)	1 : 4 by weight — pre-weighed sets, mix as recommended	—
Appearance	Milky; dries clear	—
Density	1.05 – 1.15 kg/L	—
Solids content	30 – 55 %	—
Viscosity	500 – 1500 mPa·s	—
Pot life	1 – 2 hours	—
Touch dry	1 – 2 hours	—
Recoat interval	4 – 6 hours	—
Full cure	24 hours	—
Coverage	approx. 6 – 8 m²/L	—
Application temperature	+10 °C to +35 °C	—

Consumption

Use	Consumption
Dense concrete	0.15 – 0.20 kg/m²
Porous concrete / screed	0.20 – 0.30 kg/m²
O MIX court, roof and micro-cement systems	0.2 kg/m²

Consumption is theoretical and varies with substrate porosity, profile and application method.

Application Conditions

- Ambient and substrate temperature: +10 °C to +35 °C.
- Relative humidity: max. 85 %.
- Substrate clean, sound; damp is acceptable, no standing water.
- Concrete at least 28 days old (asphalt not to be primed).

Application Notes

- Mix complete sets at 1 : 4 by weight.
- Do not leave puddles; apply a uniform film.
- Apply the next layer after 4 – 6 hours and within 24 hours.
- Clean tools with water before the material cures.

Health & Safety

- Wear gloves and safety goggles.
- Uncured epoxy may cause skin sensitisation; avoid skin and eye contact.
- Ensure ventilation in enclosed areas.

First Aid & Cleaning

- Eyes: rinse immediately with plenty of clean water for at least 15 minutes and seek medical advice.
- Skin: remove contaminated clothing and wash with soap and water; do not use solvents on skin.
- Inhalation: move to fresh air; seek medical advice if symptoms persist.
- Ingestion: do not induce vomiting; seek medical advice immediately.
- Clean tools with water immediately after use.

Construction Chemicals

Micromix Deco 1 Data Sheet

O MIX MicroArt — Submittal Document

Construction Chemicals

Product Datasheet
Edition: 01 | Date: Nov 2026
Concrete Admixture



Micromix Deco 1

Micro-Cement Base Coat
for Floors & Walls

Product Description

Micromix Deco 1 is a cementitious micro-cement base coat for floors, walls and stairs. Applied in thin layers of 1 – 2 mm over concrete, screed, ceramic or terrazzo, it forms a strong, seamless base for Micromix Deco 2 finishing layers.

Uses

- Floors, walls and stairs.
- Bathrooms and kitchens.
- Showrooms and commercial interiors.
- Renovation over concrete, screed, ceramic tiles or terrazzo.

Advantages

- Seamless base coat, 1 – 2 mm per layer.
- Compressive strength ≥ 35 MPa.
- Adhesion ≥ 1.5 MPa.
- Applies over existing tiles and terrazzo.
- Base of the Micromix Deco system.

Application

1. **Surface Preparation**
   Sound, clean, stable substrate; prime with Bondmix WB.
2. **Mixing**
   Mix powder with water at a water/powder ratio of 0.28 – 0.32.
3. **Application**
   Apply 1 – 2 mm per layer with a steel trowel; next layer after 24 hours.

Consumption

1.6 – 1.8 kg/m² per mm
in 1 – 2 layers
Approx. 1 kg/m² per layer in the Micromix Deco systems.

Packaging

25 kg bags.

Storage & Shelf Life

12 months in original, unopened bags. Store dry, off the ground, protected from moisture.

Technical Data

Typical values at 25 °C

Property	Typical Value	Test Method
Form	Cementitious powder	—
Water / powder ratio	0.28 – 0.32	—
Layer thickness	1 – 2 mm	—
Working time	20 – 30 minutes	—
Drying time	approx. 3 hours	—
Next layer	after 24 hours	—
Adhesion	≥ 1.5 MPa	—
Flexural strength	≥ 7 MPa	—
Compressive strength	≥ 35 MPa	—
Density	approx. 1.8 kg/L	—
Application temperature	+10 °C to +35 °C	—

Consumption

Layer	Consumption
Per mm of thickness	1.6 – 1.8 kg/m²
Base layer in Micromix Deco systems	approx. 1 kg/m²

Consumption is theoretical and varies with substrate porosity, profile and application method.

Application Conditions

- Ambient and substrate temperature: +10 °C to +35 °C.
- Substrate sound, clean, dry and stable.
- Protect from direct sun, wind and rapid drying.
- Do not apply on substrates with rising damp.

Application Notes

- Water / powder ratio 0.28 – 0.32 (7.0 – 8.0 L per 25 kg bag).
- Embed Fiberlock reinforcement in the first layer on floors where specified.
- Lightly sand between layers.
- Finish with Micromix Deco 2 and protect with Decora PU.

Health & Safety

- Wear gloves, safety goggles and a dust mask when mixing.
- Contains cement; alkaline when wet. Avoid skin and eye contact.
- Use dust extraction when sanding.

First Aid & Cleaning

- Eyes: rinse immediately with plenty of clean water for at least 15 minutes and seek medical advice.
- Skin: wash with soap and water; cement is alkaline when wet.
- Inhalation of dust: move to fresh air.
- Ingestion: rinse mouth and seek medical advice.
- Clean tools with water immediately after use.

The information in this datasheet is based on laboratory tests and practical experience and is given in good faith. Users should verify product suitability for their specific application. O MIX reserves the right to update this information without prior notice.

Construction Chemicals

Micromix Deco 2 Data Sheet

O MIX MicroArt — Submittal Document

Construction Chemicals

Product Datasheet
Edition: 01 | Date: Nov 2026
Concrete Admixture



Micromix Deco 2

Micro-Cement Fine Finish
Decorative Top Layer

Product Description

Micromix Deco 2 is a very fine cementitious micro-cement finishing layer. Applied in layers of 0.5 – 1 mm over Micromix Deco 1, it gives a smooth, decorative, seamless finish that is protected with Decora PU.

Uses

- Decorative floors and walls.
- Bathrooms, kitchens and wet areas.
- Showrooms, offices and residential interiors.
- Columns, stairs and furniture.

Advantages

- Smooth, decorative seamless finish.
- Compressive strength ≥ 45 MPa.
- Flexural strength ≥ 8 MPa.
- Thin layers: 0.5 – 1 mm.
- Grey or white base for colouring.

Application

1. **Surface Preparation**
   Apply over cured, sanded Micromix Deco 1 base.
2. **Mixing**
   Mix powder with water at a water/powder ratio of 0.30 – 0.33.
3. **Application**
   Apply 0.5 – 1 mm per layer with a steel trowel; sand lightly between layers; seal with Decora PU.

Consumption

1.7 – 1.8 kg/m² per mm
in 2 thin layers
Approx. 1 kg/m² in the Micromix Deco systems.

Packaging

25 kg bags.

Storage & Shelf Life

12 months in original, unopened bags. Store dry, off the ground, protected from moisture.

Technical Data

Typical values at 25 °C

Property	Typical Value	Test Method
Form	Fine cementitious powder	—
Colour	Grey / white	—
Water / powder ratio	0.30 – 0.33	—
Layer thickness	0.5 – 1 mm	—
Working time	15 – 20 minutes	—
Drying time	approx. 2 hours	—
Next layer	after 24 hours	—
Flexural strength	≥ 8 MPa	—
Compressive strength	≥ 45 MPa	—
Density	approx. 1.7 kg/L	—

Consumption

Layer	Consumption
Per mm of thickness	1.7 – 1.8 kg/m²
Finish layers in Micromix Deco systems	approx. 1 kg/m²

Consumption is theoretical and varies with substrate porosity, profile and application method.

Application Conditions

- Ambient and substrate temperature: +10 °C to +35 °C.
- Substrate sound, clean, dry and stable.
- Protect from direct sun, wind and rapid drying.
- Do not apply on substrates with rising damp.

Application Notes

- Water / powder ratio 0.30 – 0.33 (7.5 – 8.3 L per 25 kg bag).
- Apply thin layers with a stainless-steel trowel.
- Sand lightly between layers (180 – 220 grit).
- Seal with Decora PU after drying.

Health & Safety

- Wear gloves, safety goggles and a dust mask when mixing.
- Contains cement; alkaline when wet. Avoid skin and eye contact.
- Use dust extraction when sanding.

First Aid & Cleaning

- Eyes: rinse immediately with plenty of clean water for at least 15 minutes and seek medical advice.
- Skin: wash with soap and water; cement is alkaline when wet.
- Inhalation of dust: move to fresh air.
- Ingestion: rinse mouth and seek medical advice.
- Clean tools with water immediately after use.

The information in this datasheet is based on laboratory tests and practical experience and is given in good faith. Users should verify product suitability for their specific application. O MIX reserves the right to update this information without prior notice.

Construction Chemicals

Decora PU Data Sheet

O MIX MicroArt — Submittal Document

Construction Chemicals

Product Datasheet
Edition: 01 | Date: Nov 2026
Decorative Paints

Decora PU

Clear Matt Polyurethane
Top Coat for Decorative Concrete



Product Description

Decora PU is a two-component, clear, matt acrylic polyurethane top coat for decorative concrete and cementitious finishes. It does not yellow, protects against fungi and bacteria and resists dilute acids and alkalis. It is the protective top coat of the O MIX micro-cement systems.

Uses

- Concrete and plastered surfaces.
- Polished and decorative concrete.
- Micro-cement floors and walls (Micromix Deco systems).
- Glow-stone and cementitious quartz floors.
- Interior and exterior decorative surfaces.

Advantages

- Non-yellowing, UV stable.
- Protects against fungi and bacteria.
- Resists dilute acids and alkalis.
- Clear matt finish keeps the natural look.
- Recoat after 4 hours.

Application

1. **Surface Preparation**
   Clean, dry, sound surface free of dust and grease.
2. **Mixing**
   Add Part B to Part A (5 : 1 by weight) and mix thoroughly; thin up to 20 % if required.
3. **Application**
   Apply by roller or spray in thin coats, 12 – 24 hours between coats.

Consumption

approx. 7 m²/L
at 50 µm DFT per coat
0.25 kg/m² as top coat in micro-cement systems.

Packaging

5 L and 20 L sets (Part A + Part B) in metal containers.

Storage & Shelf Life

12 months in original, unopened packaging. Store dry at +5 °C to +35 °C, away from heat, sparks and direct sunlight.

Technical Data

Typical values at 25 °C

Property	Typical Value	Test Method
Mixing ratio (A : B)	5 : 1 by weight	—
Finish	Clear matt	—
Solids content	35 %	—
Recommended DFT	25 – 75 µm	—
Theoretical coverage	approx. 7 m²/L at 50 µm	—
Surface dry	30 minutes	—
Recoat interval	4 hours to 10 days	—
Pot life	2 hours	—
VOC	576 g/L	—
Thinning	up to 20 %	—
Min. application temperature	+8 °C	—

Consumption

Use	Consumption
Top coat, 50 µm DFT	approx. 7 m²/L per coat
Micro-cement systems	0.25 kg/m² (total)

Consumption is theoretical and varies with substrate porosity, profile and application method.

Application Conditions

- Minimum substrate and air temperature: +8 °C.
- Substrate dry and at least 3 °C above dew point.
- Relative humidity: max. 85 %.
- Cementitious substrates fully cured and dry.

Application Notes

- Mix complete sets at 5 : 1 by weight.
- Thin up to 20 % with the recommended thinner for spray or first coat on porous surfaces.
- Apply in thin, even coats; avoid puddles.
- Allow 12 – 24 hours between coats (minimum 4 hours, maximum 10 days).
- Test on a sample area for appearance before full application.

Health & Safety

- Solvent-based: flammable. Keep away from heat, sparks and open flames; no smoking.
- Wear chemical-resistant gloves, safety goggles and a respirator with organic vapour cartridges in enclosed spaces.
- Contains isocyanates; may cause sensitisation.
- Ensure good ventilation during application and drying.

First Aid & Cleaning

- Eyes: rinse immediately with plenty of clean water for at least 15 minutes and seek medical advice.
- Skin: remove contaminated clothing and wash with soap and water; do not use solvents on skin.
- Inhalation: move to fresh air; seek medical advice if symptoms persist.
- Ingestion: do not induce vomiting; seek medical advice immediately.
- Clean tools immediately with PU thinner.

Construction Chemicals

Test Reports

O MIX MicroArt — Submittal Document

To be attached: laboratory test reports supporting the values in the Technical Data Sheets.

Construction Chemicals

Approvals & Certificates

O MIX MicroArt — Submittal Document

To be attached: approvals and certificates, where available.