Construction Chemicals

SUBMITTAL DOCUMENT

O MIX Soft Acrylic

Cushioned Acrylic
Sport Court System



Cushioned
Resilient layers

Comfort
Reduced fatigue

Colour Stable
UV resistant

Water-Based
Low odour

Project	
Main Contractor	
Consultant	
Submittal No. / Rev.	00
Date	Nov 2026

Construction Chemicals

Contents

1. System Method Statement 3

2. TDS — Bondmix WB 11

3. TDS — Acrycourt RAC 14

4. TDS — Acrycourt CU 17

5. TDS — Acrycourt PAC 20

6. Test Reports 23

7. Approvals & Certificates 24

METHOD STATEMENT

O MIX Soft Acrylic — Cushioned Acrylic Sport Court System

Project Name		**Document No.**	OMX-SMS-14
Main Contractor		**Revision**	01
Consultant		**Date of Issue**	Nov 2026
System	O MIX Soft Acrylic	**Status**	For Approval

1. Purpose

This method statement defines the sequence, resources, inspection and test plan and safety measures for the installation of the O MIX Soft Acrylic system on site. It describes how each layer of the system is prepared, mixed, applied, inspected and protected so that the completed system achieves the performance stated in the O MIX Technical Data Sheets of its components.

2. Scope of Work

O MIX Soft Acrylic is a cushioned acrylic court system. Over the primer and resurfacer, coarse and fine rubberised acrylic cushion layers add resilience and comfort, and coloured acrylic top coats complete the playing surface.

- Substrate inspection, testing and acceptance.
- Surface preparation and repair of defects.
- Stage 1: Primer (concrete only) — Bondmix WB.
- Stage 2: Resurfacer — Acrycourt RAC.
- Stage 3: Cushion layers — coarse — Acrycourt CU.
- Stage 4: Cushion layers — fine — Acrycourt CU.
- Stage 5: Colour top coat (2 coats) — Acrycourt PAC.
- Curing, protection, final testing and handover.

2.1 System build-up

Stage	Product	Function	Consumption
1	Bondmix WB	Primer (concrete only)	0.2 kg/m²
2	Acrycourt RAC	Resurfacer	1.5 kg/m²
3	Acrycourt CU	Cushion layers — coarse	3 kg/m² (in several coats)
4	Acrycourt CU	Cushion layers — fine	3 kg/m² (in several coats)
5	Acrycourt PAC	Colour top coat (2 coats)	0.5 kg/m²

2.2 Typical areas of use

- Tennis courts.

- Basketball courts.
- Multi-purpose and school courts.

3. Definitions

Term	Meaning
System	All layers of the build-up applied in the stated sequence.
Hold point	Stage at which work stops until QA/QC (and the consultant, where required) approve.
Recoat window	Minimum and maximum time between two layers for proper inter-layer bonding.
Dew point	Temperature at which moisture condenses; the substrate must be at least 3 °C above it.
Mock-up / trial area	Area applied before the main works to approve materials, method and appearance.
Pot life	Time a mixed multi-component material remains workable.

4. Roles & Responsibilities

Role	Responsibility
Project Manager	Planning, resources, approvals and coordination with the consultant and main contractor.
Site Engineer	Daily supervision; confirms substrate readiness, climate, mixing, consumption and recoat windows; keeps daily records.
QA/QC Inspector	Carries out tests at each hold point, records results and signs the inspection checklist.
HSE Officer	Toolbox talks, PPE, ventilation, safe access and storage; stops unsafe work.
Applicator Foreman	Leads the application team and follows this method statement; reports deviations.
O MIX Technical Representative	Technical support, site visits and advice on product use when requested.

5. Materials

Product	Description	Packaging
Bondmix WB	Water-Based Two-Component Epoxy Primer & Bonding Coat	10 kg sets (Part A 2 kg + Part B 8 kg) and 20 kg sets (Part A 4 kg + Part B 16 kg).
Acrycourt RAC	Acrylic Resurfacer for Sport Courts	20 kg pails and 200 kg drums.
Acrycourt CU	Rubberised Acrylic Cushion Layer for Sport Courts	20 kg pails and 200 kg drums.
Acrycourt PAC	Coloured Acrylic Top Coat for Sport Courts	20 kg pails and 200 kg drums.

5.1 Key product data

Product	Mixing ratio	Pot life / working time	Recoat / drying
Bondmix WB	1 : 4 by weight — pre-weighed sets, mix as recommended	1 – 2 hours	4 – 6 hours

Product	Mixing ratio	Pot life / working time	Recoat / drying
Acrycourt RAC	Ready to use	—	6 – 12 hours
Acrycourt CU	Ready to use	—	6 – 12 hours
Acrycourt PAC	Ready to use	—	4 – 6 hours

6. Tools & Equipment

- Diamond grinder and/or shot blaster with dust extraction; industrial vacuum
- Slow-speed drill mixer (300 – 500 rpm) with spiral paddle
- Rollers, brushes, squeegees, notched trowels and steel trowels as required by each stage
- Scales and measuring containers for part mixing (where permitted)
- Thermo-hygrometer, surface thermometer and dew-point calculator
- Moisture meter and plastic sheets for moisture testing
- Masking tape, protective sheeting, barriers and warning signs
- Lighting and extension cables with residual current protection
- Rubber squeegees and soft brooms
- Line-marking tape and equipment
- 3 m straight edge

6.1 Personal protective equipment

- Safety shoes, helmet and high-visibility vest
- Chemical-resistant gloves (nitrile) and safety goggles
- Coveralls with long sleeves
- Dust masks (P2) during grinding and powder mixing
- Respirators with organic vapour cartridges for solvent-containing products and confined spaces
- Knee pads for floor work

7. Storage & Handling

- Store all products in original, unopened packaging in a dry, shaded and ventilated store at the temperatures stated in each TDS.
- Keep Part A, Part B (and Part C) of each kit together; do not mix components from different batches.
- Protect liquids from frost and direct sun, and powders from moisture.
- Store solvent-containing products away from heat, sparks and ignition sources.
- Use materials on a first-in, first-out basis and record batch numbers for each area.
- Condition materials to +15 °C to +25 °C for 24 hours before use in hot or cold weather.

8. Pre-Start Requirements

- Approved material submittal, this method statement and the inspection and test plan.
- Approved drawings showing areas, joints, upstands, drains and details.

- Work area handed over clean, free of other trades, with safe access, lighting and power.
- Mock-up / trial area executed and approved for system, colour and finish.
- Toolbox talk held with the team on this method statement and HSE measures.
- Climate monitoring equipment calibrated and available.

9. Substrate Inspection & Acceptance (Hold Point)

Check	Acceptance criteria	Method
Asphalt / concrete age	Asphalt ≥ 14 days; concrete ≥ 28 days	Site records
Planarity and falls	Falls typically 0.8 – 1 % in one plane; no ponding after drainage	Flood test and 3 m straight edge
Climate	Substrate ≥ 3 °C above dew point; RH ≤ 85 %	ISO 8502-4 / thermo-hygrometer

10. Surface Preparation

1. Clean the asphalt or concrete by pressure washing and blowing; remove oil, dirt and vegetation.
2. Repair cracks and depressions; correct ponding areas with Acrycourt RAC patch mix.
3. Prime concrete surfaces with Bondmix WB; asphalt is not primed.
4. Mask and protect adjacent surfaces, drains and fixtures.
5. Record substrate test results and obtain QA/QC approval before priming (hold point).

11. Application Sequence

Apply the system stage by stage in the order below. Each stage must be inspected and approved before the next stage starts, and the next stage must be applied within the recoat window stated.

11.1 Stage 1 — Primer (concrete only): Bondmix WB

Consumption: 0.2 kg/m². Time before next stage: 4 – 6 h.

1. Check batch numbers and condition the kit to +15 °C to +25 °C.
2. Pour the complete Part A into Part B (1 : 4 by weight).
3. Mix 2 – 3 minutes with a slow-speed mixer until uniform.
4. Mix complete sets only.
5. Apply by roller or brush at 0.15 – 0.30 kg/m² without puddles.
6. Apply a second coat on very porous substrates.
7. Apply the next system layer after 4 – 6 hours and within 24 hours.

11.2 Stage 2 — Resurfacer: Acrycourt RAC

Consumption: 1.5 kg/m². Time before next stage: 6 – 12 h.

1. Stir Acrycourt RAC in its container.
2. Add silica sand at 1 : 1 to 1 : 2 (product : sand) and water as recommended.

3. Mix to a uniform squeegee consistency.
4. Pour the mix in lines and spread with a rubber squeegee in one direction.
5. Apply 1 – 2 coats to a total of 1.0 – 2.0 kg/m².
6. Scrape ridges lightly between coats.

11.3 Stage 3 — Cushion layers — coarse: Acrycourt CU

Consumption: 3 kg/m² (in several coats). Time before next stage: 6 – 12 h between coats.

1. Stir Acrycourt CU thoroughly until uniform.
2. Apply as supplied.
3. Spread with a rubber squeegee in straight passes.
4. Apply coarse coats first, then fine coats, as specified.
5. Apply each coat at 1.5 – 3.0 kg/m².

11.4 Stage 4 — Cushion layers — fine: Acrycourt CU

Consumption: 3 kg/m² (in several coats). Time before next stage: 6 – 12 h; full cure 24 – 48 h.

1. Stir Acrycourt CU thoroughly until uniform.
2. Apply as supplied.
3. Spread with a rubber squeegee in straight passes.
4. Apply coarse coats first, then fine coats, as specified.
5. Apply each coat at 1.5 – 3.0 kg/m².

11.5 Stage 5 — Colour top coat (2 coats): Acrycourt PAC

Consumption: 0.5 kg/m². Time before next stage: 4 – 6 h between coats; line marking after drying.

1. Stir Acrycourt PAC thoroughly.
2. Add silica sand where a textured finish is specified, as recommended.
3. Mix until uniform.
4. Apply the first coat by squeegee or roller in one direction.
5. Apply the second coat at 90° after 4 – 6 hours.
6. Apply each coat at 0.3 – 0.5 kg/m².
7. Mark lines after the final coat has dried.

12. Hold Points & Recoat Windows

Stage	Before starting	Waiting time before next stage	Approved by
1. Bondmix WB	Substrate accepted (Section 9)	4 – 6 h	QA/QC
2. Acrycourt RAC	Previous stage inspected and approved	6 – 12 h	QA/QC
3. Acrycourt CU	Previous stage inspected and approved	6 – 12 h between coats	QA/QC

Stage	Before starting	Waiting time before next stage	Approved by
4. Acrycourt CU	Previous stage inspected and approved	6 – 12 h; full cure 24 – 48 h	QA/QC
5. Acrycourt PAC	Previous stage inspected and approved	4 – 6 h between coats; line marking after drying	QA/QC

13. Curing, Protection & Return to Service

- Protect each layer from rain, dew, dust, water and traffic until it has cured.
- Barricade the area and display warning signs during application and curing.
- Keep ventilation running in enclosed areas until full cure.
- Allow the final colour coat to dry before line marking; open the court to play after full cure.

14. Quality Control & Inspection Test Plan

Activity	Inspection / Test	Frequency	Record
Material receipt	Product, batch, expiry, packaging condition	Each delivery	Material inspection report
Climate	Air / substrate temperature, RH, dew point (ISO 8502-4)	Start of shift and every 4 h	Daily climate log
Substrate	Strength, pull-off (ASTM D7234), moisture (ASTM D4263)	Each area (hold point)	Inspection request
Mixing	Complete kits, ratio, mixing time	Each mix	Daily record
Consumption	Material used vs area	Each stage	Daily record
Planarity	Flood test / straight edge	Each court	Inspection report
Line marking	Dimensions and straightness	Each court	Inspection report
Final inspection	Appearance, continuity, finish, details	Each area	Handover checklist

15. Defects & Remedies

Defect	Likely cause	Remedy
Poor adhesion / delamination	Weak, dusty or damp substrate; recoat window exceeded	Remove, re-prepare and reapply; abrade and re-prime if window exceeded
Pinholes / bubbles	Outgassing; air trapped in mixing; thick application	Seal porous areas; mix slowly; spiked roller; sand and recoat
Blushing / tacky surface	High humidity or low temperature during cure	Wash, abrade and recoat in suitable conditions
Soft spots	Incorrect ratio or incomplete mixing	Remove and reapply with complete kits
Colour / shade variation	Different batches; uneven application	Use one batch per area; apply additional coat

16. Health, Safety & Environment

Hazard	Control measures
Skin / eye contact with resins and cement	Gloves, goggles, coveralls; eye-wash station
Inhalation of dust and vapours	Dust extraction; ventilation; masks / respirators
Fire (solvent vapours)	No smoking or hot work; fire extinguisher at the work area
Slips and trips	Housekeeping; barricades and warning signs
Manual handling	Correct lifting; mechanical aids for drums and pails
Electrical equipment	Inspected tools; protected cables with RCD

- Read the Safety Data Sheet of each product before use.
- Keep first-aid kit and eye-wash on site; follow the first-aid measures in each TDS.

16.1 Waste & environment

- Collect empty containers and residues in designated bins.
- Allow small quantities of mixed resin to cure before disposal; dispose of according to local regulations.
- Do not discharge materials or washings into drains or soil.

17. Cleaning

- Clean tools of water-based and cementitious products with water immediately after use.
- Clean tools of epoxy and PU products with the recommended thinner before the material cures.
- Cured material can only be removed mechanically.

18. Limitations

- Do not apply outside the temperature and humidity limits stated in the TDS of each product.
- Do not apply on wet surfaces or when rain or dew is expected before the layer has cured.
- Do not mix or substitute products from other systems without written approval from O MIX.
- Any deviation from this method statement must be approved by the Site Engineer and the consultant.

19. Maintenance

- Clean the court regularly with soft brooms and water.
- Remove leaves and debris to prevent staining.
- Re-coat colour layers every few years depending on use.

Appendix A — Inspection Checklist

Inspection Item	Result	Remarks
Approved submittal and method statement on site	☐ Yes ☐ No	
Mock-up approved	☐ Yes ☐ No	
Substrate tests passed (strength, pull-off, moisture)	☐ Yes ☐ No	
Surface preparation approved	☐ Yes ☐ No	
Stage 1 — Bondmix WB applied and approved	☐ Yes ☐ No	
Stage 2 — Acrycourt RAC applied and approved	☐ Yes ☐ No	
Stage 3 — Acrycourt CU applied and approved	☐ Yes ☐ No	
Stage 4 — Acrycourt CU applied and approved	☐ Yes ☐ No	
Stage 5 — Acrycourt PAC applied and approved	☐ Yes ☐ No	
Recoat windows respected	☐ Yes ☐ No	
Final tests passed	☐ Yes ☐ No	
Area protected and handed over	☐ Yes ☐ No	

Inspected by	Signature	Date

Appendix B — Daily Application Record

Date	Area / zone	Stage	Batch No.	Qty used	Air / substrate °C	RH %	Sign

Construction Chemicals

Bondmix WB Data Sheet

O MIX Soft Acrylic — Submittal Document

Construction Chemicals

Product Datasheet
Edition: 01 | Date: Nov 2026
Sport Court Systems

Bondmix WB

Water-Based Two-Component
Epoxy Primer & Bonding Coat



Product Description

Bondmix WB is a two-component, water-based epoxy primer for concrete and cementitious substrates, indoors and outdoors. It penetrates and seals the surface, reduces peeling and improves the adhesion of acrylic and polyurethane sport-court systems, micro-cement and waterproofing coatings. It is milky when applied and dries clear.

Uses

- Primer for acrylic and PU sport-court systems.
- Primer and bonding coat for Micromix Deco micro-cement.
- Primer for Roofguard AC waterproofing systems.
- Sealing of porous concrete and screeds.
- Interior and exterior use.

Advantages

- Water-based, low VOC, low odour.
- Penetrates and seals porous substrates.
- Improves adhesion of following layers.
- Reduces peeling and delamination.
- Dries clear.

Application

1. **Surface Preparation**
   Clean, sound, dust-free concrete; damp but without standing water is acceptable.
2. **Mixing**
   Add Part A to Part B (1 : 4 by weight) and mix 2 – 3 min with a slow-speed mixer.
3. **Application**
   Apply by roller or brush at 0.15 – 0.30 kg/m²; next layer after 4 – 6 hours.

Consumption

0.15 – 0.30 kg/m²
per coat, depending on porosity
0.2 kg/m² in O MIX court, roof and micro-cement systems.

Packaging

10 kg sets (Part A 2 kg + Part B 8 kg) and 20 kg sets (Part A 4 kg + Part B 16 kg).

Storage & Shelf Life

12 months in original, unopened packaging. Store dry at +5 °C to +35 °C, away from direct sunlight. Protect from frost.

Technical Data

Typical values at 25 °C

Property	Typical Value	Test Method
Mixing ratio (A : B)	1 : 4 by weight — pre-weighed sets, mix as recommended	—
Appearance	Milky; dries clear	—
Density	1.05 – 1.15 kg/L	—
Solids content	30 – 55 %	—
Viscosity	500 – 1500 mPa·s	—
Pot life	1 – 2 hours	—
Touch dry	1 – 2 hours	—
Recoat interval	4 – 6 hours	—
Full cure	24 hours	—
Coverage	approx. 6 – 8 m²/L	—
Application temperature	+10 °C to +35 °C	—

Consumption

Use	Consumption
Dense concrete	0.15 – 0.20 kg/m²
Porous concrete / screed	0.20 – 0.30 kg/m²
O MIX court, roof and micro-cement systems	0.2 kg/m²

Consumption is theoretical and varies with substrate porosity, profile and application method.

Application Conditions

- Ambient and substrate temperature: +10 °C to +35 °C.
- Relative humidity: max. 85 %.
- Substrate clean, sound; damp is acceptable, no standing water.
- Concrete at least 28 days old (asphalt not to be primed).

Application Notes

- Mix complete sets at 1 : 4 by weight.
- Do not leave puddles; apply a uniform film.
- Apply the next layer after 4 – 6 hours and within 24 hours.
- Clean tools with water before the material cures.

Health & Safety

- Wear gloves and safety goggles.
- Uncured epoxy may cause skin sensitisation; avoid skin and eye contact.
- Ensure ventilation in enclosed areas.

First Aid & Cleaning

- Eyes: rinse immediately with plenty of clean water for at least 15 minutes and seek medical advice.
- Skin: remove contaminated clothing and wash with soap and water; do not use solvents on skin.
- Inhalation: move to fresh air; seek medical advice if symptoms persist.
- Ingestion: do not induce vomiting; seek medical advice immediately.
- Clean tools with water immediately after use.

Construction Chemicals

Acrycourt RAC Data Sheet

O MIX Soft Acrylic — Submittal Document

Construction Chemicals

Product Datasheet
Edition: 01 | Date: Nov 2026
Sport Court Systems



Acrycourt RAC

Acrylic Resurfacer
for Sport Courts

Product Description

Acrycourt RAC is a water-based acrylic resurfacer and filler for asphalt and concrete sport courts. Mixed with silica sand and water, it fills pores and minor depressions and gives a uniform, levelled base for the cushion and colour coats.

Uses

- Tennis, basketball and multi-purpose courts.
- Resurfacing new or old asphalt and concrete.
- Filling pores and minor depressions.
- Base layer of the O MIX Hard and Soft Acrylic court systems.

Advantages

- Fills pores and levels the surface.
- Bond strength ≥ 1.5 MPa.
- Mixed with sand on site.
- Water-based, low odour.
- Uniform base for colour coats.

Application

1. **Surface Preparation**
   Clean, dry, sound asphalt or concrete; prime concrete with Bondmix WB.
2. **Mixing**
   Mix 1 part Acrycourt RAC with 1 – 2 parts silica sand and water as recommended.
3. **Application**
   Spread with a rubber squeegee; allow each coat to dry before the next.

Consumption

1.0 – 2.0 kg/m²
total, in 1 – 2 coats
1.5 kg/m² in the O MIX Hard / Soft Acrylic systems.

Packaging

20 kg pails and 200 kg drums.

Storage & Shelf Life

12 months in original, unopened packaging. Store at +5 °C to +35 °C; protect from frost and direct sunlight.

Technical Data

Typical values at 25 °C

Property	Typical Value	Test Method
Base	Water-based acrylic	—
Colour	White	—
Density	1.30 – 1.40 kg/L	—
Solids content	50 – 60 %	—
Bond strength	≥ 1.5 MPa	—
Drying time	1 – 3 hours	—
Recoat time	6 – 12 hours	—
Sand addition	1 : 1 to 1 : 2 (product : sand) as recommended	—

Consumption

Use	Consumption
Resurfacing (1 – 2 coats)	1.0 – 2.0 kg/m²
Hard / Soft Acrylic systems	1.5 kg/m²

Consumption is theoretical and varies with substrate porosity, profile and application method.

Application Conditions

- Air and surface temperature: +10 °C to +35 °C.
- Do not apply when rain or dew is expected before the coat has dried.
- Asphalt at least 14 days old; concrete at least 28 days old.
- Surface clean, dry, sound and free of oil and loose material.

Application Notes

- Mix sand and water as recommended to a squeegee consistency.
- Apply in thin coats; do not fill depressions deeper than the layer thickness in one pass.
- Allow each coat to dry fully before the next.
- Lightly scrape ridges between coats.

Health & Safety

- Wear gloves and safety goggles.
- Avoid contact with eyes and prolonged skin contact.
- Ensure ventilation in enclosed areas.

First Aid & Cleaning

- Eyes: rinse with clean water for 15 minutes and seek medical advice.
- Skin: wash with soap and water.
- Inhalation: move to fresh air.
- Clean tools with water immediately after use.

The information in this datasheet is based on laboratory tests and practical experience and is given in good faith. Users should verify product suitability for their specific application. O MIX reserves the right to update this information without prior notice.

Construction Chemicals

Acrycourt CU Data Sheet

O MIX Soft Acrylic — Submittal Document

Construction Chemicals

Product Datasheet
Edition: 01 | Date: Nov 2026
Sport Court Systems

Acrycourt CU

Rubberised Acrylic Cushion Layer for Sport Courts



Product Description

Acrycourt CU is a water-based acrylic cushion coating containing rubber granules. Applied in several coats over the resurfacer, it builds a resilient layer that improves player comfort and reduces fatigue on tennis, basketball and multi-purpose courts.

Uses

- Tennis courts.
- Basketball courts.
- Multi-purpose and school courts.
- Cushion layers of the O MIX Soft Acrylic system.

Advantages

- Resilient cushioning layer.
- Improves player comfort.
- Durable and flexible.
- Water-based, low odour.
- Suitable for outdoor courts.

Application

1. **Surface Preparation**
   Apply over a cured, clean Acrycourt RAC resurfaced base.
2. **Mixing**
   Stir thoroughly before use; apply as supplied.
3. **Application**
   Spread with a rubber squeegee in several coats, allowing each coat to dry.

Consumption

1.5 – 3.0 kg/m²
per coat
Soft Acrylic system: 3 kg/m² coarse + 3 kg/m² fine.

Packaging

20 kg pails and 200 kg drums.

Storage & Shelf Life

12 months in original, unopened packaging. Store at +5 °C to +35 °C; protect from frost and direct sunlight.

Technical Data

Typical values at 25 °C

Property	Typical Value	Test Method
Base	Acrylic with rubber granules	—
Density	1.20 – 1.35 kg/L	—
Solids content	50 – 65 %	—
Viscosity	20,000 – 35,000 mPa·s	—
Drying time	2 – 4 hours	—
Recoat time	6 – 12 hours	—
Full cure	24 – 48 hours	—

Consumption

Use	Consumption
Each cushion coat	1.5 – 3.0 kg/m²
Soft Acrylic — coarse layers	3 kg/m²
Soft Acrylic — fine layers	3 kg/m²

Consumption is theoretical and varies with substrate porosity, profile and application method.

Application Conditions

- Air and surface temperature: +10 °C to +35 °C.
- Do not apply when rain or dew is expected before the coat has dried.
- Asphalt at least 14 days old; concrete at least 28 days old.
- Surface clean, dry, sound and free of oil and loose material.

Application Notes

- Apply over a cured resurfaced base.
- Apply several thin coats rather than one thick coat.
- Allow each coat to dry fully before the next.
- Finish with Acrycourt PAC colour coats.

Health & Safety

- Wear gloves and safety goggles.
- Avoid contact with eyes and prolonged skin contact.
- Ensure ventilation in enclosed areas.

First Aid & Cleaning

- Eyes: rinse with clean water for 15 minutes and seek medical advice.
- Skin: wash with soap and water.
- Inhalation: move to fresh air.
- Clean tools with water immediately after use.

The information in this datasheet is based on laboratory tests and practical experience and is given in good faith. Users should verify product suitability for their specific application. O MIX reserves the right to update this information without prior notice.

Construction Chemicals

Acrycourt PAC Data Sheet

O MIX Soft Acrylic — Submittal Document

Construction Chemicals

Product Datasheet
Edition: 01 | Date: Nov 2026
Sport Court Systems



Acrycourt PAC

Coloured Acrylic Top Coat
for Sport Courts

Product Description

Acrycourt PAC is a water-based, coloured acrylic top coat for sport courts. It provides a colour-stable, UV-resistant and flexible playing surface over the O MIX resurfacer and cushion layers.

Uses

- Tennis and basketball courts.
- Multi-purpose courts and playgrounds.
- Final colour coats of the O MIX Hard and Soft Acrylic systems.

Advantages

- Colour stable and UV resistant.
- Flexible and durable.
- Uniform playing surface.
- Water-based, low odour.
- Wide colour range.

Application

1. **Surface Preparation**
   Apply over a clean, dry, cured resurfacer or cushion layer.
2. **Mixing**
   Stir thoroughly; add silica sand where a textured finish is specified.
3. **Application**
   Apply 2 coats by rubber squeegee or roller, the second at 90° to the first.

Consumption

0.3 – 0.5 kg/m²
per coat (2 coats)
0.5 kg/m² in the O MIX Hard / Soft Acrylic systems.

Packaging

20 kg pails and 200 kg drums.

Storage & Shelf Life

12 months in original, unopened packaging. Store at +5 °C to +35 °C; protect from frost and direct sunlight.

Technical Data

Typical values at 25 °C

Property	Typical Value	Test Method
Base	Pigmented water-based acrylic	—
Density	1.25 – 1.35 kg/L	—
Solids content	50 – 60 %	—
Drying time	1 – 2 hours	—
Recoat time	4 – 6 hours	—
Colours	Range of court colours	—

Consumption

Use	Consumption
Colour coat (each of 2 coats)	0.3 – 0.5 kg/m²
Hard / Soft Acrylic systems	0.5 kg/m²

Consumption is theoretical and varies with substrate porosity, profile and application method.

Application Conditions

- Air and surface temperature: +10 °C to +35 °C.
- Do not apply when rain or dew is expected before the coat has dried.
- Asphalt at least 14 days old; concrete at least 28 days old.
- Surface clean, dry, sound and free of oil and loose material.

Application Notes

- Apply 2 coats crosswise for a uniform colour.
- Use one batch per court to avoid shade differences.
- Apply line marking after the final coat has dried.
- Avoid application in direct midday sun on hot surfaces.

Health & Safety

- Wear gloves and safety goggles.
- Avoid contact with eyes and prolonged skin contact.
- Ensure ventilation in enclosed areas.

First Aid & Cleaning

- Eyes: rinse with clean water for 15 minutes and seek medical advice.
- Skin: wash with soap and water.
- Inhalation: move to fresh air.
- Clean tools with water immediately after use.

The information in this datasheet is based on laboratory tests and practical experience and is given in good faith. Users should verify product suitability for their specific application. O MIX reserves the right to update this information without prior notice.

Construction Chemicals

Test Reports

O MIX Soft Acrylic — Submittal Document

To be attached: laboratory test reports supporting the values in the Technical Data Sheets.

Construction Chemicals

Approvals & Certificates

O MIX Soft Acrylic — Submittal Document

To be attached: approvals and certificates, where available.