Construction Chemicals

Product Datasheet
Edition: 01 | Date: Nov 2026
Waterproofing

Leakinject AC

Flexible Acrylic Gel
Injection Resin



Product Description

Leakinject AC is an ultra-low-viscosity acrylic injection resin that forms a highly flexible gel (300 % elongation). It penetrates very fine cracks and is used for sealing leaking cracks, joints, curtain injection and soil stabilisation. Reaction time is adjustable.

Uses

- Leaking cracks.
- Construction and expansion joints.
- Curtain injection behind walls.
- Soil stabilisation.
- Basements and tunnels.

Advantages

- Ultra-low viscosity: 5 – 8 cps.
- Highly flexible gel: 300 % elongation.
- Adjustable reaction time.
- Seals active leaks.
- Curtain and crack injection.

Application

1. **Preparation**
   Install packers; check pump and run a cup test.
2. **Mixing**
   Mix 1: Resin + accelerator; Mix 2: Polymer + NPS initiator — as recommended.
3. **Injection**
   Inject with a two-component pump at 1 : 1, from the lowest and widest point at low pressure.

Consumption

0.3 – 1.5 kg
per linear metre
Curtain injection as per design.

Packaging

Resin 20 kg (jerrycan), accelerator 2.5 kg, NPS initiator 1 kg, polymer 20 kg.

Storage & Shelf Life

12 months in original, unopened packaging. Store dry at +5 °C to +35 °C, away from direct sunlight.

Technical Data

Typical values at 25 °C

Property	Typical Value	Test Method
Viscosity	5 – 8 cps	—
Elongation (gel)	300 %	—
Mix 1	20 kg resin + 6 % accelerator	—
Mix 2	20 kg polymer + 2 % NPS	—
Pump ratio	1 : 1 (two-component pump)	—
Min. temperature	+2 °C	—

Consumption

Use	Consumption
Crack injection	0.3 – 1.5 kg/m
Curtain injection	As per design

Consumption is theoretical and varies with substrate porosity, profile and application method.

Application Conditions

- Minimum temperature: +2 °C.
- Water may be present.

Application Notes

- Always run a cup test to check gel time before injecting.
- Start from the lowest and widest point.
- Use low pressure.
- Clean the pump with water immediately after use.

Health & Safety

- Wear chemical-resistant gloves and goggles.
- Avoid skin and eye contact; acrylic monomers are irritant.
- Ensure ventilation in enclosed areas.

First Aid & Cleaning

- Eyes: rinse immediately with plenty of clean water for at least 15 minutes and seek medical advice.
- Skin: remove contaminated clothing and wash with soap and water; do not use solvents on skin.
- Inhalation: move to fresh air; seek medical advice if symptoms persist.
- Ingestion: do not induce vomiting; seek medical advice immediately.
- Clean pumps with water immediately after use.

The information in this datasheet is based on laboratory tests and practical experience and is given in good faith. Users should verify product suitability for their specific application. O MIX reserves the right to update this information without prior notice.