Construction Chemicals

Product Datasheet
Edition: 01 | Date: Nov 2026
Waterproofing



Mixseal RB

Rubberised Bitumen Emulsion
Primer & Waterproofing Coating

Product Description

Mixseal RB is a cold-applied, rubber-modified bitumen emulsion used as a primer and as a flexible waterproofing and damp-proofing coating. Its very high elasticity (> 800 % elongation) allows it to follow substrate movements. It must be protected from UV.

Uses

- Primer before bituminous membranes.
- Waterproofing of roofs and terraces.
- Damp-proofing of foundations and basements.
- Retaining walls (soil side).
- Primer before bituminous membranes on dry or slightly damp surfaces.

Advantages

- Very high elongation: > 800 %.
- Seamless waterproof film.
- Primer and waterproofing coat.
- Cold applied, water-based.
- Applies on dry or slightly damp surfaces.

Application

1. **Surface Preparation**
   Clean, sound surface; dry or slightly damp; repair cracks and form coves.
2. **Preparation**
   Stir before use; use as supplied.
3. **Application**
   Apply by brush, roller or spray in 2 coats crosswise; allow each coat to dry.

Consumption

0.5 – 0.75 kg/m²
per coat as waterproofing
As primer: 0.25 – 0.35 kg/m².

Packaging

20 kg pails and 200 kg drums.

Storage & Shelf Life

12 months in original, unopened packaging.
Store at +5 °C to +35 °C; protect from frost.

Technical Data

Typical values at 25 °C

Property	Typical Value	Test Method
Colour	Dark brown / black	—
Density	1.00 – 1.05 kg/L	—
Solids content	45 – 55 %	—
Viscosity	2000 – 6000 mPa·s	—
Touch dry	2 – 4 hours	—
Full cure	24 hours	—
Elongation	> 800 %	—
Application temperature	+5 °C to +45 °C	—
Service temperature	-10 °C to +80 °C	—

Consumption

Use	Consumption
Primer	0.25 – 0.35 kg/m²
Waterproofing coat	0.5 – 0.75 kg/m² per coat

Consumption is theoretical and varies with substrate porosity, profile and application method.

Application Conditions

- Application temperature: +5 °C to +40 °C.
- Do not apply in rain or on frozen surfaces.
- Protect from UV exposure with a protection layer or backfill.
- Substrate dry or slightly damp, no standing water.

Application Notes

- Use as supplied.
- Apply 2 coats crosswise.
- Protect from UV with a protection layer.
- Allow each coat to dry before the next.

Health & Safety

- Wear gloves and safety goggles.
- Avoid skin and eye contact.
- Ensure ventilation in enclosed areas.

First Aid & Cleaning

- Eyes: rinse with clean water for 15 minutes and seek medical advice.
- Skin: wash with soap and water.
- Inhalation: move to fresh air.
- Clean tools with water while fresh; dried material with a suitable solvent.

The information in this datasheet is based on laboratory tests and practical experience and is given in good faith. Users should verify product suitability for their specific application. O MIX reserves the right to update this information without prior notice.