METHOD STATEMENT

Mixseal WB — Water-Based Bitumen Emulsion Cold-Applied Primer & Coating

Project Name		**Document No.**	OMX-MS-MIXSEALWB
Main Contractor		**Revision**	01
Consultant		**Date of Issue**	Nov 2026
Product	Mixseal WB	**Status**	For Approval

1. Purpose

This method statement defines the procedure, sequence, resources, quality checks and safety measures for the supply and application of Mixseal WB on site. It ensures that the work is carried out safely, in line with the approved drawings and project specification, and achieves the performance stated in the O MIX Technical Data Sheet.

2. Scope of Work

This method statement covers surface preparation and application of Mixseal WB as primer and as waterproofing / damp-proofing coating on roofs, foundations, basements and retaining walls.

- Inspection and acceptance of the substrate and the work area.
- Surface preparation and repair of defects.
- Mixing and application of the material as described in this document.
- Curing, protection and handover of the completed area.
- Quality control, inspection and documentation of each stage.

3. Definitions

Term	Meaning
Bitumen emulsion	Bitumen dispersed in water; cures by water evaporation.
Damp-proofing	Protection against soil moisture without hydrostatic pressure.
Protection layer	Board, screed or geotextile protecting the coating.

4. Roles & Responsibilities

Role	Responsibility
Project Manager	Overall responsibility for planning, resources, approvals and coordination with the consultant and main contractor.
Site Engineer	Supervises the work daily; confirms substrate readiness, climate conditions, mixing, consumption and sequence; keeps daily records.

Role	Responsibility
QA/QC Inspector	Carries out inspections and tests at each stage, records results, raises inspection requests at hold points and signs the checklist.
HSE Officer	Conducts toolbox talks, checks PPE, ventilation, access and safe storage; stops work if unsafe conditions arise.
Foreman / Applicators	Carry out the work as per this method statement and report any deviation immediately.
Storekeeper	Receives, stores and issues materials in original packaging under the stated storage conditions; controls batch numbers.

5. Materials

Material	Description
Mixseal WB	Bitumen emulsion, 20 kg pails and 200 kg drums
Reinforcement	Fibreglass mesh or Geomat at corners and joints
Protection	Protection board, screed or Geomat

5.1 Key product data

Property	Typical Value
Colour	Brown (dries black)
Density	1.0 kg/L
Solids content	35 – 55 %
Viscosity	18 – 24 s (DIN 4 cup)
Touch dry	1 – 3 hours
Full cure	24 hours
Application temperature	+5 °C to +40 °C
Service temperature	-10 °C to +80 °C

6. Tools & Equipment

- Wire brushes
- Brushes
- Rollers
- Spray pump
- Buckets
- Thermo-hygrometer and surface thermometer (dew point check)
- Moisture meter
- Measuring buckets and scale
- Masking tape and protective sheeting
- Lighting and extension cables

6.1 Personal protective equipment

- Gloves
- Goggles
- Overalls

7. Storage & Handling

- 12 months in original, unopened packaging. Store at +5 °C to +35 °C; protect from frost.
- Store on pallets, off the ground, in a dry, covered and ventilated area.
- Keep containers closed until use; use materials on a first-in, first-out basis.
- Keep containers tightly closed and protect from frost and direct sunlight.
- Handle with care to avoid damage to packaging; do not stack beyond the safe height.

8. Pre-Start Requirements

- Material submittal, this method statement and the inspection plan approved by the consultant.
- Work area handed over clean, free of other trades and with safe access.
- Adequate lighting, power supply and ventilation available.
- Climate conditions checked and recorded before work starts.
- A trial area prepared and approved where required by the project.
- Toolbox talk held with the work team covering this method statement and the safety measures.

9. Surface Preparation

1. Remove dust, laitance, oil and loose material.
2. Repair cracks and holes; form coves at corners.
3. Remove standing water; slightly damp surface is acceptable.
4. Obtain QA/QC approval of the prepared surface before application.

10. Preparation of Material

1. Check the batch number and expiry date and record them.
2. Stir thoroughly before use.
3. Dilute the first coat 10 – 20 % with water on porous surfaces.

11. Application

1. Apply the primer coat at 0.25 – 0.35 kg/m² and allow to dry.
2. Embed reinforcement at corners and joints in the first waterproofing coat.
3. Apply 2 waterproofing coats crosswise at 0.5 – 0.75 kg/m² each, after the previous coat is dry.
4. Record consumption per area.

12. Curing & Protection

- Touch dry in a few hours; full cure within 24 hours.
- Protect from rain until dry.
- Install protection layer or backfill carefully after curing; protect from UV.

13. Quality Control & Inspection

Check	Stage	Acceptance Criteria	By
Substrate	Before application	Clean, sound, no standing water	QA/QC
Primer	Before coating	Uniform, dry	QA/QC
Consumption	Each coat	0.5 – 0.75 kg/m²	QA/QC
Continuity	Final	No pinholes or thin areas	QA/QC

13.1 Inspection and test plan

Activity	Inspection / Test	Frequency	Record
Material receipt	Product, batch, expiry	Each delivery	Material inspection report
Surface preparation	Clean, sound, coves	Each area	Inspection request (hold point)
Application	Coats, consumption	Each coat	Daily report
Final	Continuity, thickness	Each area	Handover checklist

14. Defects & Remedies

Defect	Likely Cause	Remedy
Blistering	Application on wet surface or in hot sun	Cut, dry and patch
Thin areas	Under-application	Apply additional coat
Wash-off	Rain before drying	Clean and reapply

15. Health, Safety & Environment

Hazard	Control Measures
Skin and eye contact	Gloves, goggles
Work in excavations	Shoring and safe access
Slips	Housekeeping
Manual handling of drums	Mechanical aids

- Wear gloves and safety goggles.
- Avoid skin and eye contact.

- Ensure ventilation in enclosed areas.
- Eyes: rinse with clean water for 15 minutes and seek medical advice.
- Skin: wash with soap and water.

15.1 Waste & environment

- Collect empty containers and residues in designated bins.
- Do not discharge material or washings into drains or soil.
- Allow small quantities of leftover mixed material to cure before disposal; dispose of according to local regulations.

16. Cleaning

- Clean tools with water while fresh; dried material with a suitable solvent.

17. Limitations

- Not UV resistant; must be covered.
- Do not apply below +5 °C or in rain.
- Any deviation from this method statement must be approved by the Site Engineer and the consultant.

Appendix A — Inspection Checklist

Inspection Item	Result	Remarks
Surface prepared	☐ Yes ☐ No	
Coves formed	☐ Yes ☐ No	
Primer applied	☐ Yes ☐ No	
Reinforcement at details	☐ Yes ☐ No	
Two coats applied crosswise	☐ Yes ☐ No	
Consumption recorded	☐ Yes ☐ No	
Protection installed	☐ Yes ☐ No	

Inspected by	Signature	Date