Construction Chemicals

SUBMITTAL DOCUMENT

# Mixseal WB

Water-Based Bitumen Emulsion
Cold-Applied Primer & Coating




**Waterproof**
Roofs & foundations

**Dual Use**
Primer & coating

**Cold Applied**
Water-based

**Protection**
Damp-proofing

| | |
|---|---|
| **Project** | |
| **Main Contractor** | |
| **Consultant** | |
| **Submittal No. / Rev.** | 00 |
| **Date** | Nov 2026 |

Construction Chemicals

# Contents


1. Method Statement 3

2. Technical Data Sheet 8

3. Test Reports 11

4. Approvals & Certificates 12

METHOD STATEMENT

# Mixseal WB — Water-Based Bitumen Emulsion Cold-Applied Primer & Coating

| | | | |
|---|---|---|---|
| **Project Name** | | **Document No.** | OMX-MS-MIXSEALWB |
| **Main Contractor** | | **Revision** | 01 |
| **Consultant** | | **Date of Issue** | Nov 2026 |
| **Product** | Mixseal WB | **Status** | For Approval |

## 1. Purpose

This method statement defines the procedure, sequence, resources, quality checks and safety measures for the supply and application of Mixseal WB on site. It ensures that the work is carried out safely, in line with the approved drawings and project specification, and achieves the performance stated in the O MIX Technical Data Sheet.

## 2. Scope of Work

This method statement covers surface preparation and application of Mixseal WB as primer and as waterproofing / damp-proofing coating on roofs, foundations, basements and retaining walls.

- Inspection and acceptance of the substrate and the work area.
- Surface preparation and repair of defects.
- Mixing and application of the material as described in this document.
- Curing, protection and handover of the completed area.
- Quality control, inspection and documentation of each stage.

## 3. Definitions

| Term | Meaning |
|---|---|
| **Bitumen emulsion** | Bitumen dispersed in water; cures by water evaporation. |
| **Damp-proofing** | Protection against soil moisture without hydrostatic pressure. |
| **Protection layer** | Board, screed or geotextile protecting the coating. |

## 4. Roles & Responsibilities

| Role | Responsibility |
|---|---|
| **Project Manager** | Overall responsibility for planning, resources, approvals and coordination with the consultant and main contractor. |
| **Site Engineer** | Supervises the work daily; confirms substrate readiness, climate conditions, mixing, consumption and sequence; keeps daily records. |

| Role | Responsibility |
|---|---|
| **QA/QC Inspector** | Carries out inspections and tests at each stage, records results, raises inspection requests at hold points and signs the checklist. |
| **HSE Officer** | Conducts toolbox talks, checks PPE, ventilation, access and safe storage; stops work if unsafe conditions arise. |
| **Foreman / Applicators** | Carry out the work as per this method statement and report any deviation immediately. |
| **Storekeeper** | Receives, stores and issues materials in original packaging under the stated storage conditions; controls batch numbers. |

## 5. Materials

| Material | Description |
|---|---|
| **Mixseal WB** | Bitumen emulsion, 20 kg pails and 200 kg drums |
| **Reinforcement** | Fibreglass mesh or Geomat at corners and joints |
| **Protection** | Protection board, screed or Geomat |

### 5.1 Key product data

| Property | Typical Value |
|---|---|
| **Colour** | Brown (dries black) |
| **Density** | 1.0 kg/L |
| **Solids content** | 35 – 55 % |
| **Viscosity** | 18 – 24 s (DIN 4 cup) |
| **Touch dry** | 1 – 3 hours |
| **Full cure** | 24 hours |
| **Application temperature** | +5 °C to +40 °C |
| **Service temperature** | -10 °C to +80 °C |

## 6. Tools & Equipment

- Wire brushes
- Brushes
- Rollers
- Spray pump
- Buckets
- Thermo-hygrometer and surface thermometer (dew point check)
- Moisture meter
- Measuring buckets and scale
- Masking tape and protective sheeting
- Lighting and extension cables

### 6.1 Personal protective equipment

- Gloves
- Goggles
- Overalls

## 7. Storage & Handling

- 12 months in original, unopened packaging. Store at +5 °C to +35 °C; protect from frost.
- Store on pallets, off the ground, in a dry, covered and ventilated area.
- Keep containers closed until use; use materials on a first-in, first-out basis.
- Keep containers tightly closed and protect from frost and direct sunlight.
- Handle with care to avoid damage to packaging; do not stack beyond the safe height.

## 8. Pre-Start Requirements

- Material submittal, this method statement and the inspection plan approved by the consultant.
- Work area handed over clean, free of other trades and with safe access.
- Adequate lighting, power supply and ventilation available.
- Climate conditions checked and recorded before work starts.
- A trial area prepared and approved where required by the project.
- Toolbox talk held with the work team covering this method statement and the safety measures.

## 9. Surface Preparation

1. Remove dust, laitance, oil and loose material.
2. Repair cracks and holes; form coves at corners.
3. Remove standing water; slightly damp surface is acceptable.
4. Obtain QA/QC approval of the prepared surface before application.

## 10. Preparation of Material

1. Check the batch number and expiry date and record them.
2. Stir thoroughly before use.
3. Dilute the first coat 10 – 20 % with water on porous surfaces.

## 11. Application

1. Apply the primer coat at 0.25 – 0.35 kg/m² and allow to dry.
2. Embed reinforcement at corners and joints in the first waterproofing coat.
3. Apply 2 waterproofing coats crosswise at 0.5 – 0.75 kg/m² each, after the previous coat is dry.
4. Record consumption per area.

## 12. Curing & Protection

- Touch dry in a few hours; full cure within 24 hours.
- Protect from rain until dry.
- Install protection layer or backfill carefully after curing; protect from UV.

## 13. Quality Control & Inspection

| Check | Stage | Acceptance Criteria | By |
|---|---|---|---|
| **Substrate** | Before application | Clean, sound, no standing water | QA/QC |
| **Primer** | Before coating | Uniform, dry | QA/QC |
| **Consumption** | Each coat | 0.5 – 0.75 kg/m² | QA/QC |
| **Continuity** | Final | No pinholes or thin areas | QA/QC |

### 13.1 Inspection and test plan

| Activity | Inspection / Test | Frequency | Record |
|---|---|---|---|
| **Material receipt** | Product, batch, expiry | Each delivery | Material inspection report |
| **Surface preparation** | Clean, sound, coves | Each area | Inspection request (hold point) |
| **Application** | Coats, consumption | Each coat | Daily report |
| **Final** | Continuity, thickness | Each area | Handover checklist |

## 14. Defects & Remedies

| Defect | Likely Cause | Remedy |
|---|---|---|
| **Blistering** | Application on wet surface or in hot sun | Cut, dry and patch |
| **Thin areas** | Under-application | Apply additional coat |
| **Wash-off** | Rain before drying | Clean and reapply |

## 15. Health, Safety & Environment

| Hazard | Control Measures |
|---|---|
| **Skin and eye contact** | Gloves, goggles |
| **Work in excavations** | Shoring and safe access |
| **Slips** | Housekeeping |
| **Manual handling of drums** | Mechanical aids |

- Wear gloves and safety goggles.
- Avoid skin and eye contact.

- Ensure ventilation in enclosed areas.
- Eyes: rinse with clean water for 15 minutes and seek medical advice.
- Skin: wash with soap and water.

### 15.1 Waste & environment

- Collect empty containers and residues in designated bins.
- Do not discharge material or washings into drains or soil.
- Allow small quantities of leftover mixed material to cure before disposal; dispose of according to local regulations.

## 16. Cleaning

- Clean tools with water while fresh; dried material with a suitable solvent.

## 17. Limitations

- Not UV resistant; must be covered.
- Do not apply below +5 °C or in rain.
- Any deviation from this method statement must be approved by the Site Engineer and the consultant.

## Appendix A — Inspection Checklist

| Inspection Item | Result | Remarks |
|---|---|---|
| **Surface prepared** | ☐ Yes ☐ No | |
| **Coves formed** | ☐ Yes ☐ No | |
| **Primer applied** | ☐ Yes ☐ No | |
| **Reinforcement at details** | ☐ Yes ☐ No | |
| **Two coats applied crosswise** | ☐ Yes ☐ No | |
| **Consumption recorded** | ☐ Yes ☐ No | |
| **Protection installed** | ☐ Yes ☐ No | |

| Inspected by | Signature | Date |
|---|---|---|
| | | |

Construction Chemicals

# Technical Data Sheet

Mixseal WB — Submittal Document

Construction Chemicals

**Product Datasheet**
Edition: 01 | Date: Nov 2026
**Waterproofing**




# Mixseal WB

Water-Based Bitumen Emulsion
Cold-Applied Primer & Coating

## Product Description

Mixseal WB is a cold-applied, water-based bitumen emulsion used as a primer before membranes and as a waterproofing and damp-proofing coating for roofs, terraces and basements. It is brown when applied and dries black.

## Uses

- Primer before bituminous membranes.
- Waterproofing of roofs and terraces.
- Damp-proofing of foundations and basements.
- Retaining walls (soil side).
- Damp-proof coating for basements.

## Advantages

- Waterproof and damp-proof.
- Primer and coating.
- Water-based, cold applied.
- Can be diluted for porous surfaces.
- Service -10 °C to +80 °C.

## Application

1. **Surface Preparation**
   Clean, sound surface; dry or slightly damp; repair cracks and form coves.
2. **Preparation**
   Stir before use; dilute the first coat 10 – 20 % with water on porous surfaces.
3. **Application**
   Apply by brush, roller or spray in 2 coats crosswise; allow each coat to dry.

## Consumption

**0.5 – 0.75 kg/m²**
per coat as waterproofing
As primer: 0.25 – 0.35 kg/m².

## Packaging

20 kg pails and 200 kg drums.

## Storage & Shelf Life

12 months in original, unopened packaging.
Store at +5 °C to +35 °C; protect from frost.

## Technical Data

*Typical values at 25 °C*

| Property | Typical Value | Test Method |
|---|---|---|
| **Colour** | Brown (dries black) | — |
| **Density** | 1.0 kg/L | — |
| **Solids content** | 35 – 55 % | — |
| **Viscosity** | 18 – 24 s (DIN 4 cup) | — |
| **Touch dry** | 1 – 3 hours | — |
| **Full cure** | 24 hours | — |
| **Application temperature** | +5 °C to +40 °C | — |
| **Service temperature** | -10 °C to +80 °C | — |

## Consumption

| Use | Consumption |
|---|---|
| **Primer** | 0.25 – 0.35 kg/m² |
| **Waterproofing coat** | 0.5 – 0.75 kg/m² per coat |

*Consumption is theoretical and varies with substrate porosity, profile and application method.*

## Application Conditions

- Application temperature: +5 °C to +40 °C.
- Do not apply in rain or on frozen surfaces.
- Protect from UV exposure with a protection layer or backfill.
- Substrate dry or slightly damp, no standing water.

## Application Notes

- First coat on porous surfaces may be diluted 10 – 20 % with water.
- Apply 2 coats crosswise.
- Protect from UV with a protection layer.
- Allow each coat to dry before the next.

## Health & Safety

- Wear gloves and safety goggles.
- Avoid skin and eye contact.
- Ensure ventilation in enclosed areas.

## First Aid & Cleaning

- Eyes: rinse with clean water for 15 minutes and seek medical advice.
- Skin: wash with soap and water.
- Inhalation: move to fresh air.
- Clean tools with water while fresh; dried material with a suitable solvent.

*The information in this datasheet is based on laboratory tests and practical experience and is given in good faith. Users should verify product suitability for their specific application. O MIX reserves the right to update this information without prior notice.*

Construction Chemicals

# Test Reports

Mixseal WB — Submittal Document

*To be attached: laboratory test reports supporting the values in the Technical Data Sheet.*

Construction Chemicals

# Approvals & Certificates

Mixseal WB — Submittal Document

*To be attached: approvals and certificates, where available.*