Construction Chemicals

Product Datasheet
Edition: 01 | Date: Nov 2026
Waterproofing

Roofguard AC

Two-Component Flexible Acrylic Cementitious Waterproofing Coating



Product Description

Roofguard AC is a two-component, flexible, water-based acrylic waterproofing coating supplied as a liquid component (Part A) and a powder component (Part B). It bridges hairline cracks, resists weathering, UV and mould, and does not peel. It is used on roofs, terraces, wet areas and water tanks, and can be reinforced with fibreglass mesh or geotextile.

Uses

- Waterproofing of concrete and metal roofs and terraces.
- Water tanks and swimming pools.
- Bathrooms, kitchens and wet areas.
- Walls, cold rooms and steam pipes.
- Over timber, tiles and foam boards.
- Main layer in the O MIX Roof LAM ST and LAM HD systems.

Advantages

- Flexible: bridges cracks up to 1 mm.
- Weather and UV resistant (QUV 2000 h).
- Excellent adhesion: 2.3 MPa.
- Elongation 150 %.
- Water-based, easy to apply.

Application

1. **Surface Preparation**
   Clean, sound substrate; repair cracks; prime with Bondmix WB (wet-surface primer on damp substrates).
2. **Mixing**
   Add Part B powder gradually to Part A liquid and mix 2 – 3 min with a slow-speed mixer to a lump-free consistency.
3. **Application**
   Apply two or more coats crosswise at 90° by brush or roller; embed mesh or geotextile in the first coat where required.

Consumption

0.25 kg/m² per coat
0.5 – 0.6 kg/m² with fibreglass mesh; 0.8 – 1.0 kg/m² with geotextile
Apply at least two coats.

Packaging

20 kg sets (Part A liquid 5 kg + Part B powder 15 kg) and 5 kg sets (1.25 kg + 3.75 kg).

Storage & Shelf Life

12 months in original, unopened packaging. Store at +5 °C to +35 °C; protect the liquid from frost and the powder from moisture.

Technical Data

Typical values at 25 °C

Property	Typical Value	Test Method
Mixing ratio (A : B)	1 : 3 by weight (liquid : powder) — pre-weighed sets, mix as recommended	—
Specific gravity	1.55	—
Solids content	60 % by volume	—
Tensile strength	1.25 MPa	—
Elongation at break	150 %	—
Adhesion to concrete	2.3 MPa	—
Crack bridging	up to 1 mm	—
Accelerated weathering	QUV 2000 h	—
Pot life	≥ 45 min	—
Touch dry	4 hours	—
Recoat interval	after touch dry (min. 4 hours), max. 24 hours	—
Cure	80 % in 7 days; full cure 28 days	—
Shelf life	12 months	—

Consumption

System	Coats	Consumption
Standard coating	2 or more	0.25 kg/m² per coat
Reinforced with fibreglass mesh	2 + mesh	0.5 – 0.6 kg/m²
Reinforced with geotextile (Roof LAM HD)	2 + geotextile	0.8 – 1.0 kg/m²

Consumption is theoretical and varies with substrate porosity, profile and application method.

Application Conditions

- Ambient and substrate temperature: +10 °C to +30 °C.
- Substrate clean, sound and free of standing water.
- Do not apply in rain or when rain is expected within 24 hours.
- Avoid application in direct strong sun or wind; dampen hot substrates.
- Concrete at least 28 days old.

Application Notes

- Prime with Bondmix WB; use a wet-surface primer on damp substrates.
- Apply coats crosswise at 90° to each other.
- Embed fibreglass mesh or Geomat geotextile in the first wet coat at corners, joints and cracks, or over the full area for reinforced systems.
- Reinforce moving joints with O-Flex PVC.
- Broadcast quartz sand on the last coat where a protection screed or tiles will follow; otherwise use a PE sheet or geotextile separation layer.

Health & Safety

- Wear gloves, safety goggles and a dust mask when handling the powder.
- The powder contains cement and is alkaline when wet; avoid skin and eye contact.
- Ensure good ventilation in enclosed areas.

First Aid & Cleaning

- Eyes: rinse immediately with plenty of clean water for at least 15 minutes and seek medical advice.
- Skin: wash with soap and water.
- Inhalation of dust: move to fresh air.
- Clean tools with water immediately after use; cured material can only be removed mechanically.

The information in this datasheet is based on laboratory tests and practical experience and is given in good faith. Users should verify product suitability for their specific application. O MIX reserves the right to update this information without prior notice.