Construction Chemicals

**Product Datasheet**
Edition: 01 | Date: Nov 2026
**Waterproofing**




# Roofguard PU

Solvent-Free Two-Component Polyurethane Waterproofing Membrane

## Product Description

Roofguard PU is a two-component, solvent-free, cold-applied polyurethane waterproofing membrane. It forms a seamless, elastic film with 350 % elongation for roofs, terraces, wet areas, pools, tunnels and car parks, and can be reinforced with fibre mesh.

## Uses

- Roofs, terraces and balconies.
- Bathrooms, kitchens and wet areas.
- Swimming pools and planters.
- Tunnels, basements and car parks.
- Top coat in the O MIX LAM HD Pro system.

## Advantages

- Elongation 350 %.
- Solvent-free, 99.99 % solids.
- Seamless, waterproof membrane.
- Abrasion resistant.
- Cold applied.

## Application

1. **Surface Preparation**
   Clean, sound substrate; repair cracks, form coves; prime with O-Prime SF (O-Prime WS on damp surfaces).
2. **Mixing**
   Add Part B to Part A (1 : 1 by weight) and mix 2 – 3 min.
3. **Application**
   Apply by squeegee or notched trowel in 2 coats; second coat within 48 hours.

## Consumption

**0.2 – 0.3 kg/m²**
at 250 µm (2 coats)
Reinforced system up to 1.5 kg/m² (3 coats); 0.5 kg/m² in LAM HD Pro.

## Packaging

20 kg sets (10 kg A + 10 kg B) and 5 kg sets (2.5 kg + 2.5 kg).

## Storage & Shelf Life

12 months in original, unopened packaging. Store dry at +5 °C to +35 °C, away from direct sunlight. Protect from moisture.

## Technical Data

*Typical values at 25 °C*

| Property | Typical Value | Test Method |
|---|---|---|
| **Mixing ratio (A : B)** | 1 : 1 by weight — pre-weighed sets, mix as recommended | — |
| **Colour** | Grey, beige or on request | — |
| **Solids content** | 99.99 % | — |
| **Specific gravity** | 1.34 | — |
| **Pot life** | 40 min | — |
| **Drying time** | 16 – 48 hours | — |
| **Full cure** | 7 days | — |
| **Hardness** | Shore A 50 | — |
| **Tensile strength** | 6 – 7 N/mm² | — |
| **Elongation** | 350 % | — |
| **Adhesion** | 1.3 N/mm² | — |
| **Water absorption** | 0.95 % | — |
| **Abrasion** | 67.3 mg loss | — |
| **DFT (reference)** | 406 µm | — |

## Consumption

| System | Coats | Consumption |
|---|---|---|
| **Standard coating, 250 µm** | 2 | 0.2 – 0.3 kg/m² |
| **LAM HD Pro top coat** | 1 – 2 | 0.5 kg/m² |
| **Reinforced membrane** | 3 + mesh | up to 1.5 kg/m² |

*Consumption is theoretical and varies with substrate porosity, profile and application method.*

## Application Conditions

- Ambient and substrate temperature: +10 °C to +35 °C.
- Substrate at least 3 °C above dew point.
- Relative humidity: max. 85 %.
- Substrate clean and sound; concrete at least 28 days old.

## Application Notes

- Prime with O-Prime SF; use O-Prime WS on damp substrates.
- Apply 2 coats; second coat within 48 hours.
- Reinforce joints and cracks with mesh embedded in the first coat; use O-Flex PVC at moving joints.
- Broadcast quartz sand on the last coat for an anti-slip finish.

## Health & Safety

- Wear chemical-resistant gloves, safety goggles and overalls.
- Uncured epoxy may cause skin sensitisation; avoid skin and eye contact.
- Ensure good ventilation in enclosed areas.

## First Aid & Cleaning

- Eyes: rinse immediately with plenty of clean water for at least 15 minutes and seek medical advice.
- Skin: remove contaminated clothing and wash with soap and water; do not use solvents on skin.
- Inhalation: move to fresh air; seek medical advice if symptoms persist.
- Ingestion: do not induce vomiting; seek medical advice immediately.
- Clean tools with PU thinner before the material cures.

*The information in this datasheet is based on laboratory tests and practical experience and is given in good faith. Users should verify product suitability for their specific application. O MIX reserves the right to update this information without prior notice.*