Construction Chemicals

Product Datasheet
Edition: 01 | Date: Nov 2026
Waterproofing



Roofguard PUR

Water-Based Acrylic-PU
Elastic UV-Resistant Waterproofing

Product Description

Roofguard PUR is a water-based, elastic acrylic-polyurethane emulsion for waterproofing and protecting flat and pitched roofs, terraces, balconies, façades and ceilings. It is UV resistant, reflects sunlight and acts as a barrier against carbonation and chlorides. For pedestrian traffic only.

Uses

- Flat and pitched roofs.
- Terraces and balconies.
- Façades and ceilings.
- Anti-carbonation protection of concrete.

Advantages

- UV resistant and solar reflective.
- Elongation ≥ 200 %.
- Chloride reduction 96 %.
- Water-based, VOC 23 g/L.
- Up to 1 mm in one system.

Application

1. **Surface Preparation**
   Clean, sound substrate; form 45° coves; reinforce joints with O-Flex PVC.
2. **Mixing**
   Stir well before use.
3. **Application**
   Apply 2 coats for waterproofing (1 for anti-carbonation); extra coats at corners and joints.

Consumption

0.5 kg/m²
at 500 µm (2 coats)
One coat for anti-carbonation protection.

Packaging

5 kg and 20 kg pails.

Storage & Shelf Life

12 months in original, unopened packaging. Store dry at +5 °C to +35 °C, away from direct sunlight.

Technical Data

Typical values at 25 °C

Property	Typical Value	Test Method
Finish / colours	Semi-gloss; white, grey	—
Solids content	55 %	—
DFT	100 – 1000 µm	—
Surface dry	1 – 2 hours	—
Recoat	from 6 hours (no maximum)	—
VOC	23 g/L	—
Hardness	Shore A 80	—
Tensile strength	4.2 N/mm²	—
Elongation	≥ 200 %	—
Adhesion	2 N/mm²	—
Water vapour transmission	43 g/m²/day	—
Chloride ion reduction	96 %	—

Consumption

Use	Coats	Consumption
Waterproofing	2	0.5 kg/m²
Anti-carbonation	1	approx. 0.25 kg/m²

Consumption is theoretical and varies with substrate porosity, profile and application method.

Application Conditions

- Ambient and substrate temperature: +10 °C to +35 °C.
- Substrate at least 3 °C above dew point.
- Relative humidity: max. 85 %.

Application Notes

- Apply 2 extra coats at corners and joints.
- Form 45° coves.
- Reinforce joints with O-Flex PVC.
- For pedestrian traffic only.

Health & Safety

- Wear gloves and safety goggles.
- Avoid contact with eyes and prolonged skin contact.
- Ensure ventilation in enclosed areas; use a mask for spray application.

First Aid & Cleaning

- Eyes: rinse with clean water for 15 minutes and seek medical advice.
- Skin: wash with soap and water.
- Inhalation: move to fresh air.
- Ingestion: rinse mouth and seek medical advice.
- Clean tools with water immediately after use.

The information in this datasheet is based on laboratory tests and practical experience and is given in good faith. Users should verify product suitability for their specific application. O MIX reserves the right to update this information without prior notice.