Construction Chemicals

Product Datasheet
Edition: 01 | Date: Nov 2026
Protective Coating

Mixcoat Novolac

Solvent-Free Novolac Epoxy Coating
for Chemical-Resistant Floors and Linings



Product Description

Mixcoat Novolac is a two-component, solvent-free, low-viscosity novolac epoxy coating for aggressive chemical environments. It gives a durable, chemical-resistant and slip-resistant finish on prepared concrete and steel, and can also be used as a binder in resin mortar and slurry systems.

Uses

- Heavy-duty coating for dairies.
- Food processing and beverage plants.
- Hospitals and pharmaceutical industry.
- Chemical industry and sugar refineries.
- Power stations and battery rooms.
- Heavy engineering workshops.
- Internal protection of concrete tanks containing chemicals.
- Sewage and wastewater treatment plants and liquid containment areas.

Advantages

- Solvent-free — no fire risk, no shrinkage on cure.
- Excellent adhesion to concrete and steel.
- Anti-slip, anti-skid finish option.
- High mechanical strength.
- High resistance to abrasion.
- High chemical resistance.

Application

1. **Surface Preparation**
   Concrete ≥ 28 days old, sound and dry (< 4 % moisture). Remove laitance and old coatings mechanically.
2. **Priming**
   Apply epoxy primer at 0.15 – 0.20 kg/m² to seal hairline cracks and pores. Allow to dry.
3. **Top Coat**
   Mix full A + B kit (2:1 by volume) for 3 min. Apply 2 coats by roller, brush or airless spray.

Consumption

0.50 – 0.60 kg/m² (2 coats, smooth)
Textured 0.8 – 1.0 · Anti-slip 1.6 – 2.0 kg/m²
Full system table on page 2.

Packaging

5 kg and 20 kg sets: Part A in pail + Part B in jerrycan.

Storage & Shelf Life

12 months in original, unopened packaging. Store dry and covered at +10 °C to +30 °C, away from heat, sunlight and frost.

Technical Data

Typical values at 25 °C

Property	Typical Value	Test Method
Mixing ratio (A : B)	2 : 1 by volume — pre-weighed sets, mix full units as recommended	—
Colour	Natural, white, grey; other colours on request	—
Mixed density	1.5 ± 0.1 g/cm³	ASTM D1475
Volume solids	> 98 %	—
Pot life	30 – 40 min	—
Touch dry	6 – 8 hours	—
Recoat interval	Min. 16 hours / max. 48 hours	—
Initial cure	24 hours	—
Full cure	7 days	—
Compressive strength	> 75 N/mm²	ASTM D695
Flexural strength	> 50 N/mm²	ASTM D790
Tensile strength	> 30 N/mm²	ASTM D638
Pull-off adhesion to concrete	> 2.5 N/mm² (concrete failure)	ASTM D4541
Abrasion resistance (CS-17, 1000 g, 1000 cycles)	55 mg loss	ASTM D4060
Hardness	≥ 80 Shore D	ASTM D2240
Dry heat resistance	Up to +120 °C	—

Consumption

System	Coats	Consumption	DFT
Primer (epoxy primer)	1	0.15 – 0.20 kg/m²	—
Smooth finish	2	0.50 – 0.60 kg/m²	0.3 – 0.4 mm
Textured finish	2	0.80 – 1.00 kg/m²	0.5 – 0.6 mm
Anti-slip finish (quartz broadcast)	2	1.60 – 2.00 kg/m²	1.0 – 3.0 mm (incl. quartz)

Consumption is theoretical and varies with substrate porosity, profile and application method.

Application Conditions

- Ambient and substrate: +10 °C to +35 °C.
- Substrate at least 3 °C above dew point.
- Relative humidity: max. 85 %.
- Substrate moisture: < 4 %.
- Full chemical resistance: 7 days at 25 °C (10 days at 15 °C).

Application Notes

- Stir Part A, add all of Part B, mix at 300–400 rpm.
- Pour in a line and spread with a nap-shed resistant roller; work continuously.
- If the recoat window is missed: solvent wipe, abrade, solvent wipe.
- Broadcast aggregate within 15 minutes if anti-slip is required.
- Do not thin. Discard material that starts to gel.

Chemical Resistance

Reagent	Rating	Reagent	Rating
Acetic Acid 20%	3	Isophorone	5
Acetone	3	Iso-propanol	5
Ammonia 40%	5	Jet Fuel	3
Benzene	3	Kerosene	5
N-Butanol	5	Lactic Acid	5
N-Butyl Acetate	5	Linseed Oil	5
Calcium Hydroxide 30%	5	Methanol	5
Castor Oil	5	Methylene Chloride	0
Chlorinated Paraffin	5	Methyl Ethyl Ketone (MEK)	3
Chloroform	3	Methyl Isobutyl Ketone (MIBK)	3
Citric Acid 30%	5	Milk	5
Crude Oil	5	Mineral Oils	5
Cyclohexanone	5	Naphtha	5
Deionised / Distilled Water	5	Nitric Acid 10%	5
Diacetone Alcohol	5	Nitric Acid 30%	3
Diesel Oil	5	Nitric Acid 69%	0
Di-isobutyl Ketone	5	Nonyl Phenol	5
Dioxane	3	Phenol	5
Dipentene	5	Phosphoric Acid 10%	5
Epichlorohydrin	1	Phosphoric Acid 20%	5
Ethyl Acetate	5	Phosphoric Acid 50%	3
Ethyl Benzene	3	Potassium Hydroxide	5
Ethylene Glycol	5	Sea Water	5
Ethylene Glycol Monoethyl Ether	5	Sodium Hydroxide	5
Formaldehyde	5	Styrene	3
Formic Acid	5	Sugar Solution 30%	5
Furfural	3	Sulphuric Acid 10%	5
Glycerol	5	Sulphuric Acid 50%	3
Hydrazine	3	Sulphuric Acid 98%	0
Hydrochloric Acid 35%	3	Toluene	5
Hydrogen Peroxide	5	Toluene Diisocyanate	5
Hydrogen Sulphide	3	White Spirit	5
Iso-butanol	5	Xylene	5
Iso-butyl Acetate	5		

Rating after 7 days cure at 25 °C: 5 = excellent (long-term) 3 = medium term (1 month) 1 = short term (24 h) 0 = not resistant

Health & Safety

- Wear nitrile gloves, goggles and overalls; use an organic-vapour mask when spraying.
- Uncured epoxy may cause skin sensitisation.
- Ensure good ventilation in confined spaces.

First Aid & Cleaning

- Eyes: rinse with water for 15 minutes and seek medical advice.
- Skin: wash with soap and water.
- Clean tools with epoxy thinner before the material cures; cured material can only be removed mechanically.