Construction Chemicals

Product Datasheet
Edition: 01 | Date: Nov 2026
Protective Coating

O-Prime SB

Solvent-Based Epoxy Primer
& Protective Coat for Steel and Walls



Product Description

O-Prime SB is a two-component, solvent-based epoxy primer and protective coating. It protects carbon steel and concrete, plaster and masonry walls against atmospheric exposure, and can be used as a primer under epoxy and polyurethane systems or as a stand-alone protective coat.

Uses

- Primer and protective coat for carbon steel structures.
- Protection of concrete, plaster and brick walls.
- Primer under O MIX epoxy and polyurethane coatings.
- Atmospheric (non-immersion) exposure, interior and exterior.

Advantages

- Durable protection of steel and walls.
- Fast drying: surface dry in 1 hour.
- Heat resistance 120 °C continuous.
- Primer or stand-alone coat.
- Good adhesion to steel and masonry.

Application

1. **Surface Preparation**
   Steel blast-cleaned or power-tool cleaned; masonry sound, dry and dust-free.
2. **Mixing**
   Add Part B to Part A (4 : 1 by volume) and mix 2 – 3 min.
3. **Application**
   Brush, roller or spray at 0.20 – 0.25 kg/m² per 100 µm DFT.

Consumption

0.20 – 0.25 kg/m²
per coat at 100 µm DFT
Depends on substrate roughness, porosity and application method.

Packaging

20 kg and 5 kg sets (Part A + Part B) in metal pails.

Storage & Shelf Life

12 months in original, unopened packaging. Store dry at +5 °C to +35 °C, away from direct sunlight, heat and ignition sources.

Technical Data

Typical values at 25 °C

Property	Typical Value	Test Method
Mixing ratio (A : B)	4 : 1 by volume	—
Finish	Matt	—
Solids content	74 % by volume	—
Density (mixed)	1.6 kg/L	—
Recommended DFT	75 – 250 µm	—
Theoretical coverage	7.4 m²/L at 100 µm DFT	—
Flash point	32 °C	—
Pot life (25 °C)	2 hours	—
Surface dry	1 hour	—
Recoat interval	2 hours	—
Full cure	4 days	—
Heat resistance (dry)	120 °C continuous, 140 °C peak	—

Consumption

Substrate	DFT per coat	Consumption
Blast-cleaned steel	75 – 100 µm	0.15 – 0.25 kg/m²
Power-tool cleaned steel	100 µm	0.20 – 0.25 kg/m²
Concrete / plaster / masonry	100 µm	0.20 – 0.25 kg/m² (more on porous surfaces)

Consumption is theoretical and varies with substrate porosity, profile and application method.

Application Conditions

- Ambient and substrate temperature: +10 °C to +35 °C.
- Substrate at least 3 °C above dew point.
- Relative humidity: max. 85 %.
- Masonry and concrete dry (< 4 % moisture) and at least 28 days old.
- For atmospheric exposure only; not for immersion service.

Application Notes

- Mix complete sets; for partial mixing measure exactly 4 : 1 by volume.
- Thin with epoxy thinner only where required for spray application.
- Apply a stripe coat on edges, welds and corners of steel.
- Recoat after 2 hours; follow the system specification for maximum overcoat time.
- Do not apply in rain, fog or when condensation is expected.

Health & Safety

- Solvent-based: flammable. Keep away from heat, sparks and open flames; no smoking.
- Wear chemical-resistant gloves, safety goggles and overalls; use a respirator with organic vapour cartridges in enclosed spaces.
- Uncured epoxy may cause skin sensitisation; avoid skin and eye contact.
- Ensure good ventilation during application and curing.

First Aid & Cleaning

- Eyes: rinse immediately with plenty of clean water for at least 15 minutes and seek medical advice.
- Skin: remove contaminated clothing and wash with soap and water; do not use solvents on skin.
- Inhalation: move to fresh air; seek medical advice if symptoms persist.
- Ingestion: do not induce vomiting; seek medical advice immediately.
- Clean tools and equipment immediately with epoxy thinner.

The information in this datasheet is based on laboratory tests and practical experience and is given in good faith. Users should verify product suitability for their specific application. O MIX reserves the right to update this information without prior notice.