Construction Chemicals

Product Datasheet
Edition: 01 | Date: Nov 2026
Protective Coating



Stone Sealer BS

Water-Based Silane / Siloxane
Penetrating Water Repellent

Product Description

Stone Sealer BS is a ready-to-use, water-based silane/siloxane water repellent. It penetrates into mineral substrates and reduces capillary water absorption while keeping the natural appearance and the breathability of the surface. It has a low odour and is applied without dilution.

Uses

- Natural and artificial stone.
- Fair-faced concrete and precast elements.
- Brick, block masonry and mortar joints.
- Interlocking pavers.
- Building façades, interior and exterior.

Advantages

- Penetrating: reduces water absorption.
- Natural look; no film, no gloss.
- Breathable: allows water vapour to escape.
- Ready to use; no dilution.
- Water-based, low odour.

Application

1. **Surface Preparation**
   Clean, dry and sound surface; repair cracks and joints first.
2. **Mixing**
   Ready to use. Stir before use; do not dilute.
3. **Application**
   Flood-coat by low-pressure sprayer, brush or roller; 1 coat (2 on porous surfaces) wet-on-wet.

Consumption

3 – 10 m²/L
per coat, depending on substrate porosity
Carry out a trial area to confirm consumption.

Packaging

1 L, 5 L and 20 L jerrycans; 200 L drums.

Storage & Shelf Life

12 months in original, unopened packaging.
Store at +5 °C to +35 °C; protect from frost and direct sunlight.

Technical Data

Typical values at 25 °C

Property	Typical Value	Test Method
Base	Water-based silane / siloxane	—
Active content	8 – 12 %	—
Density (25 °C)	0.98 – 1.02 kg/L	—
pH	7 – 9	—
Flash point	> 100 °C	—
Number of coats	1 (2 on porous substrates)	—
Coverage	3 – 10 m²/L	—
Drying time	2 – 4 hours	—
Full water repellency	24 – 72 hours	—
Shelf life	12 months	—

Consumption

Substrate	Coats	Coverage
Dense concrete / precast	1	8 – 10 m²/L
Natural stone / pavers	1 – 2	5 – 8 m²/L
Porous brick / block / mortar	2	3 – 5 m²/L

Consumption is theoretical and varies with substrate porosity, profile and application method.

Application Conditions

- Ambient and substrate temperature: +5 °C to +35 °C.
- Substrate dry and clean; new concrete and mortar at least 28 days old.
- Do not apply in rain or when rain is expected within 4 hours.
- Do not apply in strong wind or direct hot sun on the surface.
- Cracks wider than 0.3 mm must be repaired before application.

Application Notes

- Apply a trial area first to confirm appearance and consumption.
- Apply until saturation (flood coat) without run-down; work from bottom to top on vertical surfaces.
- Apply the second coat wet-on-wet on porous substrates.
- Protect glass, painted surfaces, plants and adjacent areas from overspray.
- Not suitable for horizontal surfaces under standing water or for waterproofing against hydrostatic pressure.

Health & Safety

- Wear gloves and safety goggles.
- Avoid contact with eyes and prolonged contact with skin.
- Use in well-ventilated areas; avoid inhaling spray mist.

First Aid & Cleaning

- Eyes: rinse with clean water for 15 minutes and seek medical advice.
- Skin: wash with soap and water.
- Inhalation: move to fresh air.
- Clean tools and spray equipment with water immediately after use.