Construction Chemicals

Product Datasheet
Edition: 01 | Date: Nov 2026
Decorative Paints

Decora PU

Clear Matt Polyurethane
Top Coat for Decorative Concrete



Product Description

Decora PU is a two-component, clear, matt acrylic polyurethane top coat for decorative concrete and cementitious finishes. It does not yellow, protects against fungi and bacteria and resists dilute acids and alkalis. It is the protective top coat of the O MIX micro-cement systems.

Uses

- Concrete and plastered surfaces.
- Polished and decorative concrete.
- Micro-cement floors and walls (Micromix Deco systems).
- Glow-stone and cementitious quartz floors.
- Interior and exterior decorative surfaces.

Advantages

- Non-yellowing, UV stable.
- Protects against fungi and bacteria.
- Resists dilute acids and alkalis.
- Clear matt finish keeps the natural look.
- Recoat after 4 hours.

Application

1. **Surface Preparation**
   Clean, dry, sound surface free of dust and grease.
2. **Mixing**
   Add Part B to Part A (5 : 1 by weight) and mix thoroughly; thin up to 20 % if required.
3. **Application**
   Apply by roller or spray in thin coats, 12 – 24 hours between coats.

Consumption

approx. 7 m²/L
at 50 µm DFT per coat
0.25 kg/m² as top coat in micro-cement systems.

Packaging

5 L and 20 L sets (Part A + Part B) in metal containers.

Storage & Shelf Life

12 months in original, unopened packaging. Store dry at +5 °C to +35 °C, away from heat, sparks and direct sunlight.

Technical Data

Typical values at 25 °C

Property	Typical Value	Test Method
Mixing ratio (A : B)	5 : 1 by weight	—
Finish	Clear matt	—
Solids content	35 %	—
Recommended DFT	25 – 75 µm	—
Theoretical coverage	approx. 7 m²/L at 50 µm	—
Surface dry	30 minutes	—
Recoat interval	4 hours to 10 days	—
Pot life	2 hours	—
VOC	576 g/L	—
Thinning	up to 20 %	—
Min. application temperature	+8 °C	—

Consumption

Use	Consumption
Top coat, 50 µm DFT	approx. 7 m²/L per coat
Micro-cement systems	0.25 kg/m² (total)

Consumption is theoretical and varies with substrate porosity, profile and application method.

Application Conditions

- Minimum substrate and air temperature: +8 °C.
- Substrate dry and at least 3 °C above dew point.
- Relative humidity: max. 85 %.
- Cementitious substrates fully cured and dry.

Application Notes

- Mix complete sets at 5 : 1 by weight.
- Thin up to 20 % with the recommended thinner for spray or first coat on porous surfaces.
- Apply in thin, even coats; avoid puddles.
- Allow 12 – 24 hours between coats (minimum 4 hours, maximum 10 days).
- Test on a sample area for appearance before full application.

Health & Safety

- Solvent-based: flammable. Keep away from heat, sparks and open flames; no smoking.
- Wear chemical-resistant gloves, safety goggles and a respirator with organic vapour cartridges in enclosed spaces.
- Contains isocyanates; may cause sensitisation.
- Ensure good ventilation during application and drying.

First Aid & Cleaning

- Eyes: rinse immediately with plenty of clean water for at least 15 minutes and seek medical advice.
- Skin: remove contaminated clothing and wash with soap and water; do not use solvents on skin.
- Inhalation: move to fresh air; seek medical advice if symptoms persist.
- Ingestion: do not induce vomiting; seek medical advice immediately.
- Clean tools immediately with PU thinner.