Construction Chemicals

Product Datasheet
Edition: 01 | Date: Nov 2026
Flooring

Mixcoat SB

Solvent-Based Epoxy Primer
for Floors, Steel & Aluminium



Product Description

Mixcoat SB is a two-component, solvent-based epoxy primer that penetrates and seals concrete, plaster and masonry, interior and exterior. It is the base coat for epoxy and polyurethane systems and is also suitable on steel and aluminium.

Uses

- Primer for epoxy and PU floor systems.
- Sealing of concrete, plaster and brick.
- Primer on steel and aluminium.
- Interior and exterior use.

Advantages

- Penetrates and seals.
- Adhesion > 1.5 N/mm².
- Base for epoxy and PU systems.
- Foot traffic after 6 – 8 hours.
- Interior and exterior use.

Application

1. **Surface Preparation**
   Grind or shot blast; remove dust.
2. **Mixing**
   Mix Part A and Part B (2.60 : 2.40 by weight) for 2 – 3 minutes.
3. **Application**
   Roll at 0.10 – 0.15 kg/m²; overcoat within 24 hours or broadcast sand.

Consumption

0.10 – 0.15 kg/m²
one coat
Depends on porosity.

Packaging

5 kg sets: Part A 2.60 kg + Part B 2.40 kg, metal tins.

Storage & Shelf Life

12 months in original, unopened packaging. Store dry at +5 °C to +35 °C, away from direct sunlight.

Technical Data

Typical values at 25 °C

Property	Typical Value	Test Method
Mixing ratio (A : B)	2.60 : 2.40 by weight	—
Solids content	50 %	—
Pot life	1 hour	—
Number of coats	1	—
Foot traffic	6 – 8 hours	—
Recoat	within 24 hours	—
Adhesion	> 1.5 N/mm²	ASTM D4541
Shelf life	12 months	—

Consumption

Substrate	Consumption
Dense concrete	0.10 kg/m²
Porous concrete / plaster / brick	0.15 kg/m²
Steel / aluminium	0.10 kg/m²

Consumption is theoretical and varies with substrate porosity, profile and application method.

Application Conditions

- Ambient and substrate temperature: +10 °C to +35 °C.
- Substrate at least 3 °C above dew point.
- Relative humidity: max. 85 %.
- Substrate moisture: < 4 %.

Application Notes

- Overcoat within 24 hours or broadcast 0.1 – 0.4 mm quartz into the wet primer.
- Keep away from flames — contains solvent.
- Ensure ventilation.

Health & Safety

- Solvent-based: flammable. Keep away from heat, sparks and open flames; no smoking.
- Wear chemical-resistant gloves, safety goggles and overalls; use a respirator with organic vapour cartridges in enclosed spaces.
- Uncured resin may cause skin sensitisation; avoid skin and eye contact.
- Ensure good ventilation during application and curing.

First Aid & Cleaning

- Eyes: rinse immediately with plenty of clean water for at least 15 minutes and seek medical advice.
- Skin: remove contaminated clothing and wash with soap and water; do not use solvents on skin.
- Inhalation: move to fresh air; seek medical advice if symptoms persist.
- Ingestion: do not induce vomiting; seek medical advice immediately.
- Clean tools with the recommended thinner before the material cures.

The information in this datasheet is based on laboratory tests and practical experience and is given in good faith. Users should verify product suitability for their specific application. O MIX reserves the right to update this information without prior notice.