METHOD STATEMENT

O-Filler — Polymer-Modified Cementitious Filler & Skim Coat

Project Name		**Document No.**	OMX-MS-OFILLER
Main Contractor		**Revision**	01
Consultant		**Date of Issue**	Nov 2026
Product	O-Filler	**Status**	For Approval

1. Purpose

This method statement defines the procedure, sequence, resources, quality checks and safety measures for the supply and application of O-Filler on site. It ensures that the work is carried out safely, in line with the approved drawings and project specification, and achieves the performance stated in the O MIX Technical Data Sheet.

2. Scope of Work

This method statement covers preparation, mixing and application of O-Filler, a polymer-modified cementitious filler, for levelling and finishing concrete, plaster and blockwork and for filling voids and hairline cracks.

- Inspection and acceptance of the substrate and the work area.
- Surface preparation and repair of defects.
- Mixing and application of the material as described in this document.
- Curing, protection and handover of the completed area.
- Quality control, inspection and documentation of each stage.

3. Definitions

Term	Meaning
Pot life	Time the mixed material remains workable after adding water.
SSD	Saturated surface dry — substrate damp but without standing water.
Layer thickness	Thickness of one application pass.
Curing	Keeping the applied material protected from rapid drying until it gains strength.

4. Roles & Responsibilities

Role	Responsibility
Project Manager	Overall responsibility for planning, resources, approvals and coordination with the consultant and main contractor.
Site Engineer	Supervises the work daily; confirms substrate readiness, climate conditions, mixing, consumption and sequence; keeps daily records.

Role	Responsibility
QA/QC Inspector	Carries out inspections and tests at each stage, records results, raises inspection requests at hold points and signs the checklist.
HSE Officer	Conducts toolbox talks, checks PPE, ventilation, access and safe storage; stops work if unsafe conditions arise.
Foreman / Applicators	Carry out the work as per this method statement and report any deviation immediately.
Storekeeper	Receives, stores and issues materials in original packaging under the stated storage conditions; controls batch numbers.

5. Materials

Material	Description
O-Filler	Cementitious filler, 20 kg bags
Clean water	3.5 – 4.0 L per bag

5.1 Key product data

Property	Typical Value
Form	Grey powder
Mixing water	3.5 – 4.0 L per 20 kg bag
Specific gravity (mixed)	1.8
Pot life	30 – 40 min
Layer thickness	1 – 5 mm fine / 5 – 10 mm coarse
Compressive strength (28 days)	30 N/mm²
Bond strength	0.33 N/mm²
Minimum application temperature	+5 °C

6. Tools & Equipment

- Slow-speed mixer
- Mixing bucket
- Steel trowel
- Float
- Sponge
- Wire brush
- Thermo-hygrometer and surface thermometer (dew point check)
- Moisture meter
- Measuring buckets and scale
- Masking tape and protective sheeting
- Lighting and extension cables

6.1 Personal protective equipment

- Gloves
- Goggles
- Dust mask

7. Storage & Handling

- 12 months in original, unopened bags. Store dry, off the ground, protected from moisture.
- Store on pallets, off the ground, in a dry, covered and ventilated area.
- Keep containers closed until use; use materials on a first-in, first-out basis.
- Protect bags from moisture; do not use material with lumps.
- Handle with care to avoid damage to packaging; do not stack beyond the safe height.

8. Pre-Start Requirements

- Material submittal, this method statement and the inspection plan approved by the consultant.
- Work area handed over clean, free of other trades and with safe access.
- Adequate lighting, power supply and ventilation available.
- Climate conditions checked and recorded before work starts.
- A trial area prepared and approved where required by the project.
- Toolbox talk held with the work team covering this method statement and the safety measures.

9. Surface Preparation

1. Remove dust, oil, paint and loose particles.
2. Open and clean cracks and voids.
3. Pre-wet absorbent surfaces; remove standing water.
4. Pre-wet absorbent surfaces to a saturated surface-dry condition; remove standing water.
5. Protect adjacent surfaces with masking tape and sheeting.
6. Obtain QA/QC approval of the prepared surface before starting the next step.

10. Mixing

1. Check the batch number and expiry date and record them.
2. Pour 3.5 – 4.0 L of clean water into a bucket.
3. Add 20 kg powder gradually while mixing at low speed.
4. Mix 3 minutes, rest 2 minutes, remix briefly.
5. Mix only the quantity that can be applied within the pot life.

11. Application

1. Apply with a steel trowel in layers of 1 – 5 mm (fine) or 5 – 10 mm (coarse).
2. Allow each layer to set before applying the next.
3. Finish with a float or sponge as required.
4. Work in manageable areas and finish each area in one operation where possible.
5. Check layer thickness and consumption regularly and record the results.

12. Curing & Protection

- Use within 30 – 40 minutes of mixing.
- Protect from rapid drying, sun and wind for 24 hours.
- Protect from sun, wind and rain; keep moist where required during the first 24 hours.
- Barricade the area and display warning signs.

13. Quality Control & Inspection

Check	Stage	Acceptance Criteria	By
Substrate	Before application	Clean, sound, pre-wetted	QA/QC
Mix	During work	3.5 – 4.0 L water per bag, lump-free	Site Engineer
Layer thickness	During application	Within 1 – 10 mm per layer	QA/QC
Finished surface	After 24 h	Even, no cracks or hollow areas	QA/QC

13.1 Inspection and test plan

Activity	Inspection / Test	Frequency	Record
Material receipt	Product, batch, expiry, packaging condition	Each delivery	Material inspection report
Climate	Air / substrate temperature, RH, dew point	Start of shift and every 4 hours	Daily climate log
Surface preparation	Visual, moisture, soundness	Each area	Inspection request (hold point)
Application	Consumption, thickness, appearance	Each coat / area	Daily progress report
Final inspection	Visual, continuity, finish	Each completed area	Handover checklist

14. Defects & Remedies

Defect	Likely Cause	Remedy
Shrinkage cracks	Rapid drying; layer too thick; excess water	Remove, reapply in thinner layers and protect from drying
Poor adhesion / hollow areas	Dusty or dry substrate	Remove, clean and pre-wet; reapply

Defect	Likely Cause	Remedy
Dusting surface	Excess water or late finishing	Light sanding and apply a fresh thin layer
Uneven finish	Insufficient trowelling	Sand and apply a finishing layer

15. Health, Safety & Environment

Hazard	Control Measures
Skin and eye contact	Gloves, goggles, overalls; eye-wash available
Inhalation of vapours / dust	Ventilation; masks as required
Slips and trips	Housekeeping; barricades and signs
Manual handling	Correct lifting technique; mechanical aids
Electrical tools	Inspected tools; protected cables

- Contains cement: alkaline when wet. Wear gloves and goggles.
- Avoid dust inhalation; wear a dust mask when mixing.
- Eyes: rinse with clean water for 15 minutes and seek medical advice.
- Skin: wash with soap and water.

15.1 Waste & environment

- Collect empty containers and residues in designated bins.
- Do not discharge material or washings into drains or soil.
- Allow small quantities of leftover mixed material to cure before disposal; dispose of according to local regulations.

16. Cleaning

- Clean tools with water before the material sets.

17. Limitations

- Ambient and substrate temperature: +5 °C to +35 °C.
- Do not apply on frozen surfaces or in direct strong sun.
- Do not apply in rain or when rain is expected before the material has set.
- Any deviation from this method statement must be approved by the Site Engineer and the consultant.

Appendix A — Inspection Checklist

Inspection Item	Result	Remarks
Substrate clean and sound	☐ Yes ☐ No	
Absorbent areas pre-wetted	☐ Yes ☐ No	
Correct water quantity used	☐ Yes ☐ No	
Mix lump-free	☐ Yes ☐ No	
Layer thickness within limits	☐ Yes ☐ No	
Each layer set before next	☐ Yes ☐ No	
Protected from rapid drying	☐ Yes ☐ No	
Final visual inspection passed	☐ Yes ☐ No	

Inspected by	Signature	Date