Construction Chemicals

Product Datasheet
Edition: 01 | Date: Nov 2026
Flooring



O-Filler

Polymer-Modified Cementitious Filler & Skim Coat

Product Description

O-Filler is a high-performance, non-shrink, polymer-modified cementitious powder with a reactive resin matrix. Mixed with water, it levels and finishes exposed concrete, plaster and blockwork and fills voids and hairline cracks, inside and outside, on dry or damp surfaces.

Uses

- Levelling and finishing exposed concrete.
- Skim coating plaster and blockwork.
- Filling voids, blowholes and hairline cracks.
- Interior and exterior surfaces.
- Base layer before paints and coatings.

Advantages

- Non-shrink, smooth finish.
- Can be applied on dry or damp surfaces.
- Interior and exterior use.
- Compressive strength 30 N/mm².
- Single component — just add water.

Application

1. **Surface Preparation**
   Remove dust, oil and loose material. Pre-wet absorbent surfaces.
2. **Mixing**
   Add 20 kg powder to 3.5 – 4 L clean water and mix to a smooth paste.
3. **Application**
   Apply with a steel trowel: 0.5 – 1 cm coarse or 1 – 5 mm fine layers.

Consumption

0.5 – 1.0 kg/m²
as skim coat (approx. 0.3 – 0.5 mm)
Approx. 1.8 kg/m² per mm for thicker layers.

Packaging

20 kg bags.

Storage & Shelf Life

12 months in original, unopened bags. Store dry, off the ground, protected from moisture.

Technical Data

Typical values at 25 °C

Property	Typical Value	Test Method
Form	Grey powder	—
Mixing water	3.5 – 4.0 L per 20 kg bag	—
Specific gravity (mixed)	1.8	—
Pot life	30 – 40 min	—
Layer thickness	1 – 5 mm fine / 5 – 10 mm coarse	—
Compressive strength (28 days)	30 N/mm²	—
Bond strength	0.33 N/mm²	ASTM C321
Minimum application temperature	+5 °C	—

Consumption

Application	Thickness	Consumption
Skim coat	0.3 – 0.5 mm	0.5 – 1.0 kg/m²
Fine finish	1 – 5 mm	approx. 1.8 kg/m² per mm
Coarse levelling	5 – 10 mm	approx. 1.8 kg/m² per mm

Consumption is theoretical and varies with substrate porosity, profile and application method.

Application Conditions

- Ambient and substrate temperature: +5 °C to +35 °C.
- Do not apply on frozen surfaces or in direct strong sun.
- Protect fresh layers from rapid drying.

Application Notes

- Add the powder gradually to the water while mixing with a slow-speed mixer.
- Mix 3 minutes to a lump-free paste; rest 2 minutes and remix.
- Apply in thin layers; allow each layer to set before the next.
- Do not add extra water once mixed.

Health & Safety

- Contains cement: alkaline when wet. Wear gloves and goggles.
- Avoid dust inhalation; wear a dust mask when mixing.

First Aid & Cleaning

- Eyes: rinse with clean water for 15 minutes and seek medical advice.
- Skin: wash with soap and water.
- Clean tools with water before the material sets.

The information in this datasheet is based on laboratory tests and practical experience and is given in good faith. Users should verify product suitability for their specific application. O MIX reserves the right to update this information without prior notice.