Construction Chemicals

Product Datasheet
Edition: 01 | Date: Nov 2026
Flooring

O-Mix SL

Three-Component Self-Levelling Epoxy Floor, 1 – 2 mm



Product Description

O-Mix SL is a three-component, solvent-free, self-levelling epoxy floor system applied at 1 – 2 mm. It gives a seamless, glossy, easy-to-clean floor with good impact and chemical resistance and high light reflectance. An anti-slip finish can be obtained by broadcasting aggregates.

Uses

- Heavy pedestrian traffic areas and showrooms.
- Workshops and industrial floors.
- Pharmaceutical and textile plants.
- Basements and power stations.
- Decorative floors; base coat of the Terra Flakes system.

Advantages

- Solvent-free, 100 % solids.
- Seamless, glossy, easy to clean.
- Impact and chemical resistant.
- High light reflectance.
- Anti-slip finish optional.

Application

1. **Surface Preparation**
   Concrete ≥ 25 N/mm², pull-off ≥ 1.5 N/mm², moisture < 4 %; prime and fill with O-Prime SF and O-Putty.
2. **Mixing**
   Mix Parts A + B for 1 minute at 300 – 500 rpm, then add Part C and mix 1 minute.
3. **Application**
   Pour and spread with a notched trowel to 1 – 2 mm; de-aerate with a spiked roller.

Consumption

2 – 4 kg/m²
for 1 – 2 mm thickness
Approx. 1.95 kg/m² per mm.

Packaging

40 kg units (Part A + Part B + Part C).

Storage & Shelf Life

24 months in original, unopened packaging.
Store dry at +5 °C to +35 °C.

Technical Data

Typical values at 25 °C

Property	Typical Value	Test Method
Components	Part A + Part B + Part C (filler)	—
Mixing ratio	A : B ≈ 2 : 1 by volume + Part C — complete units, as recommended	—
Solids content	100 %	—
Density	1.95 kg/L	—
Viscosity	3000 – 4000 mPa·s	—
Pot life	30 min	—
Number of coats	1	—
Foot traffic	24 hours	—
Compressive strength	50 – 55 N/mm²	—
Flexural strength	20 – 25 N/mm²	—
Tensile strength	10 – 14 N/mm²	—
Abrasion	120 mg loss	—
Shelf life	24 months	—

Consumption

Layer	Product	Consumption
Primer	O-Prime SF	0.10 – 0.15 kg/m²
Filling layer	O-Putty	0.25 – 0.30 kg/m²
Self-levelling, 1 mm	O-Mix SL	approx. 2 kg/m²
Self-levelling, 2 mm	O-Mix SL	approx. 4 kg/m²

Consumption is theoretical and varies with substrate porosity, profile and application method.

Application Conditions

- Ambient and substrate temperature: +10 °C to +35 °C.
- Substrate at least 3 °C above dew point.
- Relative humidity: max. 85 %.
- Substrate moisture: < 4 %.
- Concrete at least 28 days old, ≥ 25 N/mm², pull-off ≥ 1.5 N/mm².

Application Notes

- Prime with O-Prime SF and allow 24 hours before the self-levelling layer.
- Mix complete units only.
- Pour in strips and spread with a notched trowel to the set thickness.
- De-aerate with a spiked roller within 10 – 15 minutes.

Health & Safety

- Wear chemical-resistant gloves, safety goggles and overalls.
- Uncured epoxy may cause skin sensitisation; avoid skin and eye contact.
- Ensure good ventilation in enclosed areas.

First Aid & Cleaning

- Eyes: rinse immediately with plenty of clean water for at least 15 minutes and seek medical advice.
- Skin: remove contaminated clothing and wash with soap and water; do not use solvents on skin.
- Inhalation: move to fresh air; seek medical advice if symptoms persist.
- Ingestion: do not induce vomiting; seek medical advice immediately.
- Clean tools with epoxy thinner before the material cures.

The information in this datasheet is based on laboratory tests and practical experience and is given in good faith. Users should verify product suitability for their specific application. O MIX reserves the right to update this information without prior notice.