Construction Chemicals

Product Datasheet
Edition: 01 | Date: Nov 2026
Flooring

O-Poxy Edge

Solvent-Free High-Performance Epoxy Floor Coating



Product Description

O-Poxy Edge is a two-component, solvent-free, high-performance epoxy floor coating. It provides high durability, chemical and abrasion resistance and a seamless, decorative finish for demanding industrial and commercial floors.

Uses

- Heavy-duty industrial floors.
- Warehouses and loading areas.
- Food and beverage facilities.
- Decorative commercial floors.
- Top coat in O MIX floor system HD.

Advantages

- Solvent-free, 100 % solids.
- Seamless, easy-to-clean finish.
- High abrasion resistance.
- High mechanical strength.
- Anti-slip option with additive.

Application

1. **Surface Preparation**
   Concrete ≥ 28 days, sound and dry (< 4 %). Grind or shot blast to remove laitance and contaminants.
2. **Priming**
   Prime with O-Prime SF at 0.10 – 0.15 kg/m². Fill defects with O-Putty.
3. **Application**
   Mix A + B for 2 – 3 min and spread with a notched trowel or roller.

Consumption

0.25 – 0.30 kg/m² per coat
approx. 160 – 190 µm film per coat (100 % solids)
Depends on substrate porosity and method.

Packaging

5 kg sets — pail + jerrycan: Part A 4.35 kg + Part B 0.65 kg.

Storage & Shelf Life

12 months in original, unopened packaging. Store dry at +5 °C to +35 °C, away from direct sunlight.

Technical Data

Typical values at 25 °C

Property	Typical Value	Test Method
Mixing ratio (A : B)	100 : 15 by weight	—
Solids content	100 %	—
Specific gravity	1.57	ASTM D1475
Colour	On request	—
Pot life (25 °C)	40 min	—
Recoat interval	24 hours	—
Hardening	12 – 24 hours	—
Full cure	7 days	—
Compressive strength	40 – 47 N/mm²	ASTM D695
Flexural strength	20 – 27 N/mm²	ASTM D790
Tensile strength	20 – 25 N/mm²	ASTM D638
Bond strength to concrete	4.0 – 4.5 N/mm²	ASTM D4541
Abrasion resistance	64 – 67 mg loss	ASTM D4060
Film thickness per coat	approx. 160 – 190 µm (WFT = DFT, 100 % solids)	—

Consumption

Layer	Product	Consumption
Primer	O-Prime SF	0.10 – 0.15 kg/m²
Filling / levelling	O-Putty	0.25 – 0.30 kg/m²
Top coat	O-Poxy Edge	0.25 – 0.30 kg/m² per coat

Consumption is theoretical and varies with substrate porosity, profile and application method.

Application Conditions

- Ambient and substrate temperature: +10 °C to +35 °C.
- Substrate at least 3 °C above dew point.
- Relative humidity: max. 85 %.
- Substrate moisture content: < 4 %.
- Concrete at least 28 days old, ≥ 25 N/mm², pull-off ≥ 1.5 N/mm².

Application Notes

- Stir Part A, add all of Part B and mix for 2 – 3 minutes with a slow-speed mixer.
- Spread with a notched (American) spatula or roller; finish with a spiked roller.
- For a primer coat, broadcast quartz sand into the fresh material.
- For anti-slip finish, add anti-slip additive to the top coat.
- Do not apply on damp substrates or below +10 °C.

Health & Safety

- Wear nitrile gloves, safety goggles and overalls.
- Uncured epoxy may cause skin sensitisation; avoid skin and eye contact.
- Ensure good ventilation in enclosed areas.

First Aid & Cleaning

- Eyes: rinse with clean water for 15 minutes and seek medical advice.
- Skin: wash with soap and water.
- Clean tools with epoxy thinner before the material cures.

The information in this datasheet is based on laboratory tests and practical experience and is given in good faith. Users should verify product suitability for their specific application. O MIX reserves the right to update this information without prior notice.